

Sure-Tough ST 4405

APPLIED POLYMER SOLUTIONS, LLC

PRODUCT PROFILE

GENERIC DESCRIPTION FLEXIBLE NOVOLAC EPOXY MEMBRANE COAT - a two component 100% urethane/epoxy hybrid coating designed for applications on traffic surfaces exposed to vehicular or foot traffic for either exterior or interior applications. The toughness and elongation eliminate the need to repair hairline cracks.

RECOMMENDED USAGE Recommended for a priming light to medium duty secondary containment or as a crack bridging primer for many suitable topcoats.

COLORS STANDARDS: clear (clear is opaque)

CHARACTERISTICS/FINISHES

SURFACE Smooth. Non-skid media may be used to provide additional texture.

PRIMERS None Required.

TOPCOATS/FINISHES Many novolac products are suitable such as our ST 4423 or our ST 4459 product line. Contact your sales representative for proper topcoat system selections. Multiple coats are required when topcoating over mortar.

TECHNICAL SPECIFICATIONS

SOLIDS BY WEIGHT 100% (mixed)

THICKNESS 10-50 mils

VOLATILE ORGANICS Zero pounds per gallon

MIX RATIO Part A: 1 gallon (9.05 lbs) / Part B: 1/2 gallon (4.35 lbs.) (volumes & weights approximate)

APPLICATION TEMP 60°F - 90°F (15°C - 32°C)

CURE SCHEDULE	Cure State	70°F (21°C)
	Pot Life	30 minutes
	Light Traffic/Recoat	7-10 hours
	Full Cure/Heavy Traffic	24 hours

STORAGE TEMP 65°F - 85°F (18°C - 30°C) in a dry area. Avoid excessive heat and freezing.

SHELF LIFE 1 years in an unopened container

PACKAGING All kits are premeasured, ready for blending and application

Size	Part A	Part B	Coverage (1,604/DFT) x gallons
3 gallon kit	2 gallon	1 gallon	64 - 320 sq. ft.
15 gallon kit	10 gallon (2-5 gallon)	5 gallon	320 - 1600 sq. ft.
Drum Kits	110 gallon	55 gallon	3520 - 17,600 sq. ft.

Published technical data and instructions may be modified at any time without prior notice. Please contact your Applied Polymer Solutions representative with any questions.

© January 2008, by Applied Polymer Solutions, LLC.

Sure-Tough ST 4405

APPLIED POLYMER SOLUTIONS, LLC

TECHNICAL SPECIFICATIONS (CONTINUED)

COMPRESSIVE STRENGTH	6,800 psi @ ASTM D695
FLEXURAL STRENGTH	4,035 psi @ ASTM D790
TENSILE STRENGTH	3,150 psi @ ASTM D638
BOND STRENGTH	450 psi (concrete failure)
GARDNER VARIABLE IMPACTOR	100 in/lbs direct - Passed
ABRASION RESISTANCE	CS-17 wheel with 1000 gm/500 cycles = 5 mg loss
ULTIMATE ELONGATION	20%
HARDNESS	Shore D = 70
VISCOSITY	10,000-14,000 cps (mixed)
WEATHERING	Good Stability

CHEMICAL RESISTANCE			
Ammonia	C	Sodium Hydroxide 50%	C
Citric Acid	B	Sulfuric Acid 10%	C
Corn Oil	B	HCl (aq) 36%	B
Lactic Acid	D	Nitric Acid 30%	B
Salt Brine	C	Phosphoric Acid 40%	B
Gasoline	C	Sodium Hypochlorite 3-5%	A
Motor Oil	C	MEK	B
Skydrol	C	Mineral Spirits	C

Rating key: A - not recommended, B - 2 hour term splash spill, C - 8 hour term splash spill, D - 72 hour immersion, E - long term immersion. NOTE: extensive chemical resistance information is available through your sales representative.

SURFACE PREPARATION

- SURFACE** All dirt, oil, dust, foreign contaminants and laitance must be removed to assure a trouble free bond to the substrate.
- MOISTURE** Allow concrete to cure for 28 to 45 days. Verify dryness by testing for moisture with a "plastic film" test; this can be done at room temperature by placing a 4' x 4' plastic sheet on the substrate and taping down the edges. If after 24 hours, the substrate is still dry below the plastic sheet, then the substrate is dry enough to start coating. Should moisture be present, perform Moisture Vapor Emission Rate testing using Anhydrous Calcium Chloride (ASTM F1869). Moisture content should not be in excess of 3 lbs. per 1,000 sq. ft. for coatings (5 lbs. for resurfacers) in a 24 hour period.
- MOST SURFACES** Aggressively shot-blast or mechanically prepare the substrate to properly profile the substrate and remove hardeners, curing compounds, sealers, laitance and other contaminants. All edges and around columns or beams should be mechanically scarified. All termination points should not be feather edged, but should be saw cut with the termination ending at the sawcut.
- FILLING & PATCHING** Voids, cavities, nail and bug holes should be filled with a recommended epoxy filler. All large cracks should be V cut and filled with an appropriate semi-rigid epoxy crack filler.
- JOINTS** All expansion joints should be filled with an appropriate joint filler. When overlaying an expansion joint, a single saw cut through the epoxy overlay will prevent random fracturing.

APPLICATION

- MIXING** This product has a mix ratio of 9.05# part A to 4.35 part B or two parts A to one part B by volume. Standard packages are in pre-measured kits and should be mixed as supplied in the kit. We highly recommend that the kits not be broken down unless suitable weighing equipment is available. After the two parts are combined, mix well with slow speed mixing equipment such as a jiffy mixer until the material is thoroughly mixed and streak free. After mixing, transfer the mixed material to another pail (the transfer pail) and again remix. The material in the transfer pail is now ready to be applied on the substrate. Improper mixing may result in product failure.
- THICKNESS** 10-50 mils. The mixed material can be applied by brush or roller. However, the material can also be applied by a suitable serrated squeegee and then back rolled as long as the appropriate thickness recommendations are maintained. Maintain temperatures and relative humidity within the recommended ranges during the application and curing process. If concrete conditions or over aggressive mixing causes air entrapment, then an air release roller tool should be used prior to the coating tacking off to remove the air entrapped in the coating.

Sure-Tough ST 4405

APPLIED POLYMER SOLUTIONS, LLC

APPLICATION (CONTINUED)

RECOAT/TOPCOAT If you opt to recoat or topcoat this product, you must be sure that the coating has tacked off before recoating. However, all previous coats should be deglossed to insure a trouble free bond prior to application of recoats or topcoats. Colder temperatures will require more cure time for the product before recoating or topcoating can commence. Before recoating or topcoating, check for epoxy blushes (a whitish, greasy film, or deglossing). If a blush is present, it can be removed by any standard detergent cleaner prior to topcoating or recoating. Many epoxy coatings and urethanes as well as multiple coats of this product are compatible for use as a topcoat. Contact your representative for further details.

CLEAN UP Citrus based cleaners or solvents such as Xylene.

**Restrict the use of the floor to light traffic and non-harsh chemicals until the coating is fully cured (see technical data under full cure). It is best to let the floor remain dry for the full cure cycle.*

LIMITATIONS

FLOOR CLEANING Caution! Some cleaners may affect the color of the floor installed. Test each cleaner in a small area, utilizing your cleaning technique. If no ill effects are noted, you can continue to clean with the product and process tested.

- *Color stability may be affected by environmental conditions such as high humidity or chemical exposure.
- * Product is not UV color stable and may discolor if exposed to lighting such as sodium vapor lights.
- * Colors may vary from batch to batch due to variations in the silica filler.
- * Mortar colors are not from our standard color chart.
- * Substrate temperature must be 5 degrees F above dew point.
- * For chemical exposure areas, we recommend a suitable topcoat to reduce porosity and chemical migration.
- * Test data based on neat resin.
- *This product is not intended for use as a decorative coating or where color stability or visual appearance is of any significant importance. Its sole purpose is as a protective coating.
- *If a topcoat of a different color is to be used, multiple coats will be necessary to prevent bleed-through (discoloration)

Warranty & Limitations of Seller's Liability: Applied Polymer Solutions, LLC Warrants only that our materials represented herein meet the formulation standards or Applied Polymer Solutions, LLC.

We Warrant that our products are manufactured to the specifications and that the information stated here is accurate to the best of our knowledge. Information supplied about our products is not a representation or a Warranty. It is supplied on the condition that the buyer shall conduct their own tests to determine the suitability of our product for their particular purpose. Listed physical properties are typical and should not be construed as specifications. **NO WARRANTY IS MADE, EXPRESSED OR IMPLIED, REGARDING SUCH OTHER INFORMATION, THE DATA ON WHICH IT IS BASED, OR THE RESULTS THAT WILL BE OBTAINED FROM ITS USE. NO WARRANTY IS MADE, EXPRESSED OR IMPLIED, THAT OUR PRODUCT SHALL BE MERCHANTABLE OR THAT OUR PRODUCT SHALL BE FIT FOR ANY PARTICULAR PURPOSE. NO WARRANTY IS MADE THAT THE USE OF SUCH INFORMATION OR OUR PRODUCT WILL NOT INFRINGE UPON ANY PATENT.** We have no liability for incidental or consequential damages, direct or indirect. Our liability is limited to the net selling price of our product or the replacement of our product, at our option. Acceptance of product delivery means acceptance of the terms of this Warranty whether or not purchase orders or other documents state terms that vary from this Warranty. No representative is authorized to make any representation or Warranty or assume any other liability on our behalf with any sale of our products. Our products contain chemicals that may **CAUSE SERIOUS PHYSICAL INJURY. BEFORE USING, READ THE MATERIAL SAFETY DATA SHEET AND FOLLOW ALL DIRECTIONS AND PRECAUTIONS ACCORDINGLY.**