

APPLIED POLYMER SOLUTIONS, LLC

PRODUCT PROFILE

GENERIC DESCRIPTION ST 4007 - High Solids (93%) Epoxy Coating and Seamless Binder Receiver - is a two component 93% (+/- 1%) solids epoxy colored coating designed for applications where a high solids primer is needed before applying high solids or 100% solids topcoats for build coats over concrete.

RECOMMENDED USAGE Recommended for a high build basecoat on concrete or masonry. Product is suitable in many chemical exposure environments.

COLORS Light gray, medium gray, tile red, and beige. Non-Standard and Special Colors Available

CHARACTERISTICS/FINISHES

SURFACE Smooth. Non-skid media may be used to provide additional texture.

PRIMERS None required unless substrate is very porous, then use ST3015/3245 to eliminate air release defects.

TOPCOATS/FINISHES All Sure-Tough epoxies and urethanes are compatible. Contact your sales representative for proper top-coat system selections. Multiple coats may be required when topcoating over mortar.

TECHNICAL SPECIFICATIONS

SOLIDS BY WEIGHT 93% (mixed)

THICKNESS 6-12 mils

VOLITALE ORGANICS Mixed: .79 pounds per gallon

MIX RATIO Part A: 1 gallon (12 lbs) / Part B: .5 gallon (3.85 lbs.) volumes & weights approximate)

APPLICATION TEMP 55°F - 90°F (12°C - 32°C)

CURE SCHEDULE

Cure State	70°F (21°C)
Pot Life	35-55 minutes
Light Traffic/Recoat	6-9 hours
Full Cure/Heavy Traffic	12-24 hours

STORAGE TEMP 65°F - 85°F (18°C - 30°C) in a dry area. Avoid excessive heat and freezing.

SHELF LIFE 1 years in an unopened container

PACKAGING All kits are premeasured, ready for blending and application

Size	Part A	Part B	Coverage (1,604/DFT) x gallons
3 gallon kit	2 gallon (5 gal pail)	1 gallon	405 -800 sq. ft.
15 gallon kit	10 gallon (2-5 gal pails)	5 gallon pail	2,025- 4,000 sq. ft.
Drum Kits	—	—	—

Published technical data and instructions may be modified at any time without prior notice. Please contact your Applied Polymer Solutions representative with any questions.

APPLIED POLYMER SOLUTIONS, LLC

TECHNICAL SPECIFICATIONS (CONTINUED)

COMPRESSIVE STRENGTH	8,300 psi @ ASTM D695
FLEXURAL STRENGTH	8,200 psi @ ASTM D790
TENSILE STRENGTH	6,800 psi @ ASTM D638
BOND STRENGTH	430 psi (concrete failure)
GARDNER VARIABLE IMPACTOR	50 in/lbs direct - Passed
ABRASION RESISTANCE	CS-17 wheel with 1000 gm/500 cycles = 45 mg loss (neat)
ULTIMATE ELONGATION	2.5%
HARDNESS	Shore D = 80
VISCOSITY	500-800 cps (mixed)
WEATHERING	Excellent

CHEMICAL RESISTANCE			
Ammonia	D	Sodium Hydroxide 50%	C
Citric Acid	C	Sulfuric Acid 10%	B
Corn Oil	C	HCl (aq) 36%	C
Lactic Acid	C	Nitric Acid 30%	B
Salt Brine	D	Phosphoric Acid 40%	C
Gasoline	C	Sodium Hypochlorite 3-5%	A
Motor Oil	C	MEK	A
Skydrol	B	Mineral Spirits	B

Rating key: A - not recommended, B - 2 hour term splash spill, C - 8 hour term splash spill, D - 72 hour immersion, E - long term immersion. NOTE: extensive chemical resistance information is available through your sales representative.

SURFACE PREPARATION

- SURFACE** All dirt, oil, dust, foreign contaminants and laitance must be removed to assure a trouble free bond to the substrate.
- MOISTURE** Allow concrete to cure for 28 to 45 days. Verify dryness by testing for moisture with a "plastic film" test; this can be done at room temperature by placing a 4' x 4' plastic sheet on the substrate and taping down the edges. If after 24 hours, the substrate is still dry below the plastic sheet, then the substrate is dry enough to start coating. Should moisture be present, perform Moisture Vapor Emission Rate testing using Anhydrous Calcium Chloride (ASTM F1869). Moisture content should not be in excess of 3 lbs. per 1,000 sq. ft. for coatings (5 lbs. for resurfacers) in a 24 hour period.
- MOST SURFACES** Aggressively shot-blast or mechanically prepare the substrate to properly profile the substrate and remove hardeners, curing compounds, sealers, laitance and other contaminants. All edges and around columns or beams should be mechanically scarified. All termination points should not be feather edged, but should be saw cut with the termination ending at the sawcut.
- FILLING & PATCHING** Voids, cavities, nail and bug holes should be filled with a recommended epoxy filler. All large cracks should be V cut and filled with an appropriate semi-rigid epoxy crack filler.
- JOINTS** All expansion joints should be filled with an appropriate joint filler. When overlaying an expansion joint, a single saw cut through the epoxy overlay will prevent random fracturing.

APPLICATION

- MIXING** This product has a mix ratio of 12# part A to 3.85# part B for standard colors. Standard packages are in pre-measured kits and should be mixed as supplied in the kit. We highly recommend that the kits not be broken down unless suitable weighing equipment is available. After the two parts are combined, mix well with slow speed mixing equipment such as a jiffy mixer until the material is thoroughly mixed and streak free. After mixing, transfer the mixed material to another pail (the transfer pail) and again remix. The material in the transfer pail is now ready to be applied on the primed substrate. Improper mixing may result in product failure.
- THICKNESS** 6-12 mils. The mixed material can be applied by brush, roller, or spray. However, the material can also be applied by a suitable serrated squeegee and then back rolled as long as the appropriate thickness recommendations are maintained. Maintain temperatures and relative humidity within the recommended ranges during the application and curing process. If concrete conditions or over aggressive mixing causes air entrapment, then an air release roller tool should be used prior to the coating tacking off to remove the air entrapped in the coating.

APPLIED POLYMER SOLUTIONS, LLC

APPLICATION (CONTINUED)

RECOAT/TOPCOAT Although a topcoat is recommended, it is optional. Many topcoats are suitable for placement over this coating including both urethanes and epoxies. When topcoating this product, you must first be sure that the coating has tacked off before topcoating can commence. Before topcoating, check the coating to verify no epoxy blushes were developed (a whitish, greasy film or deglossing). If a blush is present, it must be removed prior to topcoating. A standard type detergent cleaner can be used to remove any blush. Many epoxy coatings and urethanes are compatible for use as a topcoat for this product as well as multiple coats of this product as an intermediate build coat.

CLEAN UP Citrus based cleaners or solvents such as Alcohol or Xylene.

**Restrict the use of the floor to light traffic and non-harsh chemicals until the coating is fully cured (see technical data under full cure). It is best to let the floor remain dry for the full cure cycle.*

LIMITATIONS

FLOOR CLEANING Caution! Some cleaners may affect the color of the floor installed. Test each cleaner in a small area, utilizing your cleaning technique. If no ill effects are noted, you can continue to clean with the product and process tested.

*Color stability may be affected by environmental conditions such as high humidity or chemical exposure.

* Product is not UV color stable and may discolor if exposed to lighting such as sodium vapor lights.

* Colors may vary from batch to batch due to variations in the silica filler.

* Mortar colors are not from our standard color chart.

* Substrate temperature must be 5 degrees F above dew point.

* For chemical exposure areas, we recommend a suitable topcoat to reduce porosity and chemical migration.

* Test data based on neat resin.

*This product is not intended for use as a decorative coating or where color stability or visual appearance is of any significant importance. Its sole purpose is as a protective coating.

*If a topcoat of a different color is to be used, multiple coats will be necessary to prevent bleed-through (discoloration)

Warranty & Limitations of Seller's Liability: Applied Polymer Solutions, LLC warrants only that our materials represented herein meet the formulation standards or Applied Polymer Solutions, LLC.

We warrant that our products are manufactured to the specifications and that the information stated here is accurate to the best of our knowledge. Information supplied about our products is not a representation or a warranty. It is supplied on the condition that the buyer shall conduct their own tests to determine the suitability of our product for their particular purpose. Listed physical properties are typical and should not be construed as specifications. **NO WARRANTY IS MADE, EXPRESSED OR IMPLIED, REGARDING SUCH OTHER INFORMATION, THE DATA ON WHICH IT IS BASED, OR THE RESULTS THAT WILL BE OBTAINED FROM ITS USE. NO WARRANTY IS MADE, EXPRESSED OR IMPLIED, THAT OUR PRODUCT SHALL BE MERCHANTABLE OR THAT OUR PRODUCT SHALL BE FIT FOR ANY PARTICULAR PURPOSE. NO WARRANTY IS MADE THAT THE USE OF SUCH INFORMATION OR OUR PRODUCT WILL NOT INFRINGE UPON ANY PATENT.** We have no liability for incidental or consequential damages, direct or indirect. Our liability is limited to the net selling price of our product or the replacement of our product, at our option. Acceptance of product delivery means acceptance of the terms of this warranty whether or not purchase orders or other documents state terms that vary from this warranty. No representative is authorized to make any representation or warranty or assume any other liability on our behalf with any sale of our products. Our products contain chemicals that may **CAUSE SERIOUS PHYSICAL INJURY. BEFORE USING, READ THE MATERIAL SAFETY DATA SHEET AND FOLLOW ALL DIRECTIONS AND PRECAUTIONS ACCORDINGLY.**