

CHEMICAL RESISTANCE CHART

	RR 1005	RR 1010	RR 1010 AM	RR 1204	RR 1205	RR 1206	RR 1208	RR 1301	RR 1420	RR 1456
ACETALDEHYDE	A	B	B	B	B	B	B	B	C	D
ACETIC ACID 5%	B	B	B	B	B	A	B	A	B	D
ACETIC ACID 10%	A	A	A	B	B	A	A	A	A	C
ACETIC ACID 25%	A	A	A	A	A	A	A	A	A	C
ACETIC ACID GLACIAL	A	A	A	A	A	A	A	A	A	A
ACETIC ANHYDRIDE	A	A	A	B	B	B	B	B	B	D
ACETONE 10%	B	C	C	B	B	B	C	B	C	D
ACETONE 100%	A	B	B	A	A	B	B	A	B	C
ACETYL CHLORIDE	A	A	A	A	A	A	A	A	A	TD
ACETONITRILE	B	B	B	B	B	B	B	B	C	D
ACRYLIC ACID	A	A	A	TB	TB	TB	TB	TB	TB	TD
ACRYLONITRILE	A	A	A	TB	TB	TB	TB	TB	TB	TB
ADIPIIC ACID 25%	B	B	B	B	B	A	B	A	B	C
ALLYL ALCOHOL	TB	TB	TB	TC	TC	TC	TC	TC	TC	TD
ALLYL CHLORIDE	A	A	A	TB	TB	TB	TB	TB	TB	TC
ALUMINUM BROMIDE	B	C	C	C	C	C	C	C	C	E
ALUMINUM CHLORIDE	TB	TB	TB	TB	TB	TB	TB	TB	TC	TE
ALUMINUM FLUORIDE	TB	TB	TB	TC	TC	TB	TB	TB	TC	TE
ALUMINUM HYDROXIDE	B	C	C	C	C	C	C	C	C	E
ALUMINUM NITRATE	B	C	C	C	C	C	C	C	D	E
ALUMINUM SULFATE	B	B	B	C	C	C	C	C	C	E
AMMONIA	B	C	C	C	C	C	C	C	D	E
AMMONIUM CHLORIDE	TB	TB	TB	TC	TC	TB	TB	TB	TC	TD
AMMONIUM FLUORIDE	TB	TB	TB	TB	TB	TB	TB	TB	TB	TC
AMMONIUM HYDROXIDE	TB	TC	TC	TC	TC	TC	TC	TC	TC	TD
AMMONIUM NITRATE	C	C	C	C	C	C	C	C	D	E
AMMONIUM OXALATE	B	B	B	C	C	C	C	C	C	D
AMMONIUM NITRATE	TB	TC	TC	TC	TC	TC	TC	TC	TD	TE
AMMONIUM PERSULFATE	B	B	B	B	B	B	B	B	C	E
AMMONIUM PHOSPHATE	B	B	B	C	C	C	C	C	C	E
AMMONIUM SULFATE	B	C	C	C	C	C	C	C	C	E

This data is provided as a service of Applied Polymer Solutions and is believed to be accurate. However this information is neither recommendations by APS nor product specifications. APS reserves the right to change or modify data as necessary.

CHEMICAL RESISTANCE CHART

	RR 1005	RR 1010	RR 1010 AM	RR 1204	RR 1205	RR 1206	RR 1208	RR 1301	RR 1420	RR 1456
AMMONIUM SULFIDE	B	C	C	C	C	C	C	C	D	E
AMMONIUM SULFITE	B	C	C	C	C	C	C	C	D	E
AMYL ACETATE	TB	TB	TB	TC	TC	TB	TB	TB	TC	TD
AMYL ALCOHOL	B	B	B	B	B	B	B	B	C	D
ANILINE	A	A	A	B	B	B	B	B	B	D
ANILINE HYDROCHLORIDE	A	A	A	B	B	B	B	B	B	D
ANTIMONY CHLORIDE	A	A	A	A	A	A	A	A	B	TC
AQUA REGIA	A	A	A	A	A	A	A	A	A	A
ARSENOUS ACID	A	A	A	TB	TB	A	A	A	TB	TC
BARIUM ACETATE	B	C	C	C	C	C	C	C	C	E
BARIUM BROMIDE	B	B	B	C	C	C	C	C	C	E
BARIUM CARBONATE	B	B	B	B	B	C	C	C	C	E
BARIUM CHLORIDE	B	B	B	B	B	B	B	B	C	E
BARIUM HYDROXIDE	TB	TC	TC	TC	TC	TC	TC	TC	TC	TE
BARIUM SULFATE	B	B	B	C	C	C	C	C	C	E
BARIUM SULFIDE	A	B	B	B	B	B	B	B	C	D
BENZYL CHLORIDE	A	A	A	A	A	A	A	A	TB	TD
BENZOIC ACID	B	B	B	C	C	B	B	B	C	D
BENZALDEHYDE	A	A	A	TB	TB	TB	TB	TB	TB	TC
BENZENE	TB	TB	TB	TB	TB	TB	TB	TB	TC	TD
BENZYL ALCOHOL	C	C	C	C	C	C	C	C	D	E
BLACK LIQUOR (PAPER)	A	TB	TB	TB	TB	TB	TB	TB	TC	TD
BLOOD SUGAR	TB	TC	TC	TC	TC	TC	TC	TC	TC	TD
BORAX	B	C	C	C	C	C	C	C	C	D
BORIC ACID	A	B	B	B	B	B	B	B	C	D
BRINE	C	D	D	D	D	D	D	D	D	E
BROMINE LIQUID	A	A	A	A	A	A	A	A	A	A
BUTANOL	B	C	C	C	C	C	C	C	D	E
BUTYL ACETATE	B	B	B	C	C	C	C	C	C	D
BUTYL ACRYLATE	A	A	A	TB	TB	TB	TB	TB	TB	TC

This data is provided as a service of Applied Polymer Solutions and is believed to be accurate. However this information is neither recommendations by APS nor product specifications. APS reserves the right to change or modify data as necessary.

CHEMICAL RESISTANCE CHART

	RR 1005	RR 1010	RR 1010 AM	RR 1204	RR 1205	RR 1206	RR 1208	RR 1301	RR 1420	RR 1456
BUTYL AMINE	A	TB	TB	TB	TB	TB	TB	TB	TB	TC
BUTYL CARBITOL	TB	TB	TB	TC	TC	TB	TB	TB	TC	TD
BUTYL CELLOSOLVE	B	B	B	C	C	C	C	C	C	D
BUTYL ETHER	B	B	B	C	C	C	C	C	C	D
BUTYRIC ACID	A	A	A	A	A	A	A	A	A	C
CALCIUM BISULFITE	C	C	C	D	D	D	D	D	D	E
CALCIUM BROMIDE	TB	TB	TB	TB	TB	TB	TB	TB	TC	TD
CALCIUM CARBONATE	B	C	C	C	C	C	C	C	C	D
CALCIUM CHLORATE	B	B	B	B	B	B	B	B	C	D
CALCIUM CHLORIDE	B	C	C	C	C	C	B	B	D	E
CALCIUM HYDROXIDE	B	C	C	C	C	C	C	C	D	E
CALCIUM HYPOCHLORITE	A	TB	TB	TB	TB	TB	TB	TB	TB	TD
CALCIUM NITRATE	B	B	B	C	C	C	C	C	D	E
CALCIUM SULFATE	B	B	B	C	C	C	C	C	C	D
CALCIUM SULFITE	B	B	B	C	C	C	C	C	C	D
CALCIUM DISULFIDE	A	B	B	D	B	A	A	A	B	C
CARBON TETRACHLORIDE	B	B	B	C	C	C	C	C	C	E
CASTOR OIL	B	C	C	C	C	C	C	C	C	E
CELLOSOLVE	TB	TB	TB	TC	TC	TC	TC	TC	TC	TD
CELLOSOLVE ACETATE	B	B	B	C	C	C	C	C	C	D
CHLOROACETIC ACID 25%	A	A	A	B	B	A	A	A	A	C
CHLOROACETIC ACID 50%	A	A	A	A	A	A	A	A	A	A
CHLOROBENZENE	B	B	B	B	B	B	B	B	C	D
CHLOROFORM	A	TB	TB	TB	A	TB	TB	TB	TB	TC
CHLOROPHENOL	A	A	A	A	A	A	A	A	A	A
CHLOROSULFONIC ACID	A	A	A	A	A	A	A	A	A	A
CHLOROTOLUENE	A	TB	TB	TB	TB	TB	TB	TB	TB	TD
CHROMIC ACID 10%	A	A	A	B	B	A	A	A	B	C
CHROMIC ACID 40%	A	A	A	A	A	A	A	A	A	B
CHROMIC CHLORIDE	A	A	A	A	A	A	A	A	A	B
CITRIC ACID	B	B	B	C	C	B	B	B	C	E

This data is provided as a service of Applied Polymer Solutions and is believed to be accurate. However this information is neither recommendations by APS nor product specifications. APS reserves the right to change or modify data as necessary.

CHEMICAL RESISTANCE CHART

	RR 1005	RR 1010	RR 1010 AM	RR 1204	RR 1205	RR 1206	RR 1208	RR 1301	RR 1420	RR 1456
COPPER ACETATE	B	B	B	C	C	B	B	B	C	E
COPPER CHLORIDE	B	A	A	C	C	B	B	B	B	D
COPPER CYANIDE	TB	TB	TB	TC	TC	TB	TB	TB	TC	TD
COPPER NITRATE	TB	TB	TB	TC	TC	TB	TB	TB	TC	TD
COPPER SULFATE	B	B	B	C	C	B	B	B	C	D
CORN OIL	B	C	C	C	C	B	B	B	C	E
CORN STARCH SLURRY	C	D	D	D	D	C	C	C	E	E
CORN SUGAR	C	C	C	D	C	C	C	C	D	E
COTTONSEED OIL	B	C	C	C	C	B	B	C	C	E
CREOSOTE	B	B	B	B	B	B	B	B	C	E
CRESYLIC ACID	A	A	A	TB	TB	A	A	A	TB	TD
CUMENE	B	B	B	C	C	B	B	B	C	E
CUTTING OIL	B	C	C	C	C	B	C	B	C	E
CYCLOHEXANE	B	B	B	C	C	B	B	B	C	E
CYCLOHEXANONE	B	B	B	C	C	B	B	B	C	E
CYMENE	TB	TB	TB	TB	TB	TB	TB	TB	TC	TD
DETERGENTS ORGANIC	TC	TC	TC	TC	TC	TC	TD	TC	TE	TE
DETERGENTS SULFONATED	TC	TC	TC	TD	TD	TC	TD	TC	TE	TE
DEXTROSE	C	C	C	D	D	C	D	C	E	E
DIBUTYL PHTHALATE	B	C	C	C	C	B	C	B	D	E
DICHLORACETIC ACID	A	A	A	TB	TB	A	A	A	A	TC
DICHLOROBENZENE	B	B	B	C	C	B	B	B	B	E
DICHLOROETHANE	A	A	A	A	A	A	A	A	A	C
DIESEL FUEL	B	B	B	C	C	B	B	B	C	D
DIETHANOLAMINE	TB	TB	TB	TB	TB	TB	TB	TB	TB	TD
DIETHYL BENZENE	TB	TB	TB	TC	TC	TB	TB	TB	TC	TD
DIETHYL KETONE	A	TB	TB	TB	TB	A	A	A	TB	TD
DIETHYLENE GLYCOL	B	C	C	C	C	C	C	C	C	E
DIETHYL ETHER	A	B	B	B	B	B	B	B	B	D
DIMETHYL ANILINE	A	A	A	TB	TB	TB	TB	TB	TB	TD
DIMETHYL FORMAMIDE	A	A	A	A	A	A	A	A	A	A

This data is provided as a service of Applied Polymer Solutions and is believed to be accurate. However this information is neither recommendations by APS nor product specifications. APS reserves the right to change or modify data as necessary.

CHEMICAL RESISTANCE CHART

	RR 1005	RR 1010	RR 1010 AM	RR 1204	RR 1205	RR 1206	RR 1208	RR 1301	RR 1420	RR 1456
DIMETHYL SULFOXIDE	A	A	A	A	A	A	A	A	A	B
DINITRO BENZENE	A	A	A	TB	TB	TB	TB	TB	TB	TC
DINITRO TOLUENE	A	A	A	TB	TB	TB	TB	TB	TB	TC
EPICHLOROHYDRIN	A	B	B	B	B	B	B	B	B	D
ETHANOL	A	B	B	C	C	B	C	C	B	C
ETHANOLAMINE	A	B	B	B	B	B	B	B	B	D
ETHYL ACETATE	A	B	B	A	A	B	B	A	A	C
ETHYL ACRYLATE	A	A	A	A	A	A	A	A	A	C
ETHYLAMINE	A	A	A	A	A	B	TB	A	A	TC
ETHYL BENZENE	A	TB	TB	TB	TB	TB	TB	TB	TB	TD
ETHYL BROMIDE	A	A	A	A	A	A	A	A	A	B
ETHYL CHLORIDE	A	A	A	A	A	A	A	A	A	B
ETHYL DICHLORIDE	A	A	A	A	A	A	A	A	A	TB
ETHYLENE GLYCOL	B	C	C	D	D	C	C	C	D	E
ETHYL SULFATE	A	TB	TB	TB	TB	TB	TB	TB	TB	TD
FATTY ACIDS	A	TB	TB	TB	TB	TB	TB	TB	TB	TD
FERRIC CHLORIDE	C	C	C	D	D	C	C	C	E	E
FERRIC SULFATE	B	C	C	D	D	C	C	C	E	E
FERROUS NITRATE	B	C	C	C	C	C	C	C	C	E
FERROUS CHLORIDE	TB	TB	TB	TC	TC	TB	TB	TB	TD	TD
FERROUS SULFATE	TB	TC	TC	TC	TC	TD	TD	TD	TE	TE
FLUOSILICIC ACID 10-25%	A	A	A	A	A	A	A	A	A	A
FORMALDEHYDE	B	B	B	C	C	C	C	C	C	E
FORMIC ACID 10%	A	B	B	B	B	B	B	B	B	D
FORMIC ACID 50%	A	A	A	A	A	A	A	A	A	B
FUEL OIL	B	B	B	C	C	B	B	B	C	E
FURFURAL ALCOHOL	A	A	A	A	A	A	A	A	TB	TC
GASOLINE AVIATION	A	B	B	B	B	B	B	B	B	D
GASOLINE DIESEL	A	B	B	B	B	B	B	B	B	D
GASOLINE JET FUEL	A	B	B	B	B	B	B	B	B	D
GASOLINE UNLEADED	B	B	B	C	C	B	B	B	C	E

This data is provided as a service of Applied Polymer Solutions and is believed to be accurate. However this information is neither recommendations by APS nor product specifications. APS reserves the right to change or modify data as necessary.

CHEMICAL RESISTANCE CHART

	RR 1005	RR 1010	RR 1010 AM	RR 1204	RR 1205	RR 1206	RR 1208	RR 1301	RR 1420	RR 1456
GLUCOSE	C	C	C	E	E	E	E	E	E	E
GLYCERINE	TC	TC	TC	TD	TD	TC	TC	TC	TD	TE
GLYCOLIC ACID 70%	A	A	A	A	A	A	A	A	A	TB
GREEN LIQUOR (PAPER)	B	C	C	C	C	B	B	B	C	E
HEPTANE	B	C	C	C	C	C	C	C	D	E
HEXANE	B	C	C	C	C	C	C	C	D	E
HYDRAULIC FLUID	B	B	B	B	B	B	B	B	C	E
HYDRAZINE 35%	A	TB	TB	TB	TB	TB	TB	TB	TB	TC
HYDRIODIC ACID 20%	A	A	A	B	B	A	A	A	C	D
HYDROBROMIC ACID 18%	A	A	A	A	A	A	A	A	A	C
HYDROBROMIC ACID 40%	A	A	A	A	A	A	A	A	A	TC
HYDROBROMIC ACID 60%	A	A	A	A	A	A	A	A	A	TB
HYDROCHLORIC ACID 10%	B	C	C	C	C	B	C	C	C	D
HYDROCHLORIC ACID 36%	A	A	A	A	A	B	A	A	B	D
HYDROFLUORIC ACID	A	A	A	A	A	A	A	A	A	A
HYDROGEN PEROXIDE 10%	A	A	A	A	B	A	A	A	B	C
HYDROGEN PEROXIDE 50%	A	A	A	A	A	A	A	A	A	A
HYDROGEN SULFIDE 5%	B	C	C	C	C	C	C	C	C	D
HYDROGEN SULFIDE 100%	A	TB	TB	TB	TB	TB	TC	TB	TC	TD
HYPOCHLOROUS ACID	A	A	A	A	A	A	A	A	A	A
IODINE CRYSTALS/VAPOR	TB	TB	TB	TC	TC	TB	TB	TB	TC	TD
ISOPHORONE	B	C	C	C	C	C	C	C	C	E
ISOPROPYL ACETATE	B	B	B	C	C	C	C	C	C	E
ISOPROPYL ALCOHOL	B	C	C	C	C	C	C	C	C	E
JET FUEL (JP-4)	A	B	B	B	B	B	B	B	B	D
KEROSENE	B	B	B	C	C	B	B	B	C	D
LACTIC ACID 10-20%	B	B	B	C	C	C	C	C	C	D
LACTIC ACID 50%	A	A	A	A	A	A	A	A	B	C
LACTIC ACID 85%	A	A	A	A	A	A	A	A	A	A
LAURIC ACID	A	TB	TB	TB	TB	A	A	A	TB	TD
LEAD ACETATE	TB	TC	TC	TC	TC	TB	TB	TB	TD	TE

This data is provided as a service of Applied Polymer Solutions and is believed to be accurate. However this information is neither recommendations by APS nor product specifications. APS reserves the right to change or modify data as necessary.

CHEMICAL RESISTANCE CHART

	RR 1005	RR 1010	RR 1010 AM	RR 1204	RR 1205	RR 1206	RR 1208	RR 1301	RR 1420	RR 1456
LEVULINIC ACID	TB	TB	TB	TC	TC	TB	TB	TB	TC	TD
LINSEED OIL	B	B	B	B	B	B	B	B	B	D
LITHIUM BROMIDE	TB	TB	TB	TC	TC	TC	TC	TC	TC	TD
LITHIUM CHLORIDE SAT'D	A	B	B	B	B	B	B	B	B	D
LITHIUM HYDROXIDE	A	A	A	A	A	A	A	A	A	TD
MAGNESIUM BISULFITE	B	B	B	B	B	B	B	B	B	D
MAGNESIUM CARBONATE	B	B	B	C	C	C	C	C	C	D
MAGNESIUM CHLORIDE	TB	TB	TB	TB	TB	TB	TB	TB	TB	TC
MAGNESIUM HYDROXIDE	B	B	B	B	B	B	B	B	B	C
MAGNESIUM NITRATE	TB	TB	TB	TB	TB	TB	TB	TB	TB	TD
MAGNESIUM SULFATE	TB	TB	TB	TB	TB	TB	TB	TB	TB	TD
MALEIC ACID	A	A	A	A	A	A	A	A	A	C
MANGANESE CHLORIDE	TB	TB	TB	TB	TB	A	A	A	TB	TD
MANGANESE SULFATE	TB	TB	TB	TB	TB	TB	TB	TB	TB	TD
MERCURIC CHLORIDE	TB	A	A	TB	TB	A	A	A	TC	TE
MERCUROUS CHLORIDE	TB	A	A	TC	TC	TB	TB	A	TC	TE
METHANOL	A	B	B	A	A	A	A	A	A	C
METHYL ACETATE	A	A	A	A	A	A	A	A	A	C
METHYLAMYL ALCOHOL	TB	TB	TB	TC	TC	TC	TB	TB	TC	TD
METHYL BENZOATE	A	B	B	B	B	B	B	B	B	D
METHYL CHLORIDE	A	A	A	A	A	A	A	A	A	B
METHYLENE CHLORIDE	A	A	A	A	A	A	A	A	A	A
METHYL ETHYL KETONE	A	A	A	A	A	A	A	A	A	C
METHYL ISOBUTYL KETONE	A	B	B	C	C	A	B	B	B	D
MILK	C	D	D	D	D	D	D	D	D	E
MOLASSES	C	D	D	D	D	D	D	D	D	E
MINERAL OILS	TB	TC	TC	TC	TC	TC	TC	TC	TC	TE
MINERAL SPIRITS	B	B	B	B	B	C	C	B	B	D
MOTOR OIL	C	C	C	C	C	C	C	C	C	D
M-PYROL	A	A	A	A	A	A	A	A	A	B
NAPHTHA ALIPHATIC	B	B	B	B	B	B	B	B	B	E

This data is provided as a service of Applied Polymer Solutions and is believed to be accurate. However this information is neither recommendations by APS nor product specifications. APS reserves the right to change or modify data as necessary.

CHEMICAL RESISTANCE CHART

	RR 1005	RR 1010	RR 1010 AM	RR 1204	RR 1205	RR 1206	RR 1208	RR 1301	RR 1420	RR 1456
NAPHTHA AROMATIC	A	B	B	B	B	B	B	B	B	E
NICKEL CHLORIDE	A	A	A	A	A	A	A	A	A	TD
NICKEL NITRATE	B	B	B	B	B	B	B	B	B	D
NICKEL SULFATE	TB	TB	TB	TB	TB	TB	TB	TB	TB	TD
NITRIC ACID 5%	B	A	A	B	B	B	B	B	B	E
NITRIC ACID 30%	A	A	A	B	B	A	A	A	B	C
NITRIC ACID 60%	A	A	A	A	A	A	A	A	A	A
NITROBENZENE	A	A	A	A	A	A	A	A	A	TC
OIL SOUR CRUDE	B	C	C	C	C	C	C	C	C	E
OIL SWEET CRUDE	TB	TC	TC	TC	TC	TC	TC	TC	TC	TE
OLEIC ACID	A	A	A	A	A	A	A	A	A	D
OLEUM	A	A	A	A	A	A	A	A	A	C
OXALIC ACID	A	B	B	A	A	B	B	A	B	D
PERCHLORIC ACID	A	A	A	A	A	A	A	A	A	C
PERCHLOROETHYLENE	A	B	B	B	B	B	B	B	B	D
PHENOL 5%	A	B	B	A	A	A	A	A	A	C
PHENOL 85%	A	A	A	A	A	A	A	A	A	B
PHOSPHORIC ACID 40%	A	B	B	A	A	A	A	A	C	D
PHOSPHORIC ACID 85%	A	A	A	A	A	A	A	A	A	B
PICRIC ACID 10%	A	TB	TB	TB	TB	A	TB	TB	TB	TD
POTASSIUM ACETATE	B	C	C	C	C	C	C	C	C	E
POTASSIUM BROMIDE	B	C	C	C	C	C	C	C	C	E
POTASSIUM CARBONATE	B	C	C	C	C	C	C	C	D	E
POTASSIUM CHLORIDE	B	B	B	B	B	A	A	A	C	D
POTASSIUM HYDROXIDE 10%	B	C	C	C	C	C	C	C	C	E
POTASSIUM HYDROXIDE 50%	A	B	B	B	B	C	C	B	B	E
POTASSIUM IODIDE	TB	TB	TB	TB	TB	TB	TB	TB	TB	TD
POTASSIUM NITRATE	B	C	C	C	C	C	C	C	C	E
POTASSIUM PERMANGANATE	A	TB	TB	TB	TB	TB	TB	TB	TB	TD
POTASSIUM PERSULFATE	A	B	B	B	B	B	B	B	B	D
POTASSIUM SULFATE	B	C	C	C	C	C	C	C	C	E

This data is provided as a service of Applied Polymer Solutions and is believed to be accurate. However this information is neither recommendations by APS nor product specifications. APS reserves the right to change or modify data as necessary.

CHEMICAL RESISTANCE CHART

	RR 1005	RR 1010	RR 1010 AM	RR 1204	RR 1205	RR 1206	RR 1208	RR 1301	RR 1420	RR 1456
PROPIONIC ACID	A	B	B	C	C	B	B	B	B	C
PROPYLENE GLYCOL	B	C	C	D	D	D	D	D	D	E
PYRIDINE	A	A	A	A	A	A	A	A	A	A
SALICYLIC ACID	TB	TB	TB	TB	TB	TB	TB	TB	TB	TD
SALT BRINE	C	C	C	C	C	C	D	C	D	E
SILVER NITRATE	A	A	A	A	A	A	A	A	A	TD
SKYDROL	A	B	B	B	B	B	A	A	B	C
SODIUM ACETATE	B	C	C	C	C	C	C	C	D	E
SODIUM BENZOATE	B	C	C	C	C	C	C	C	D	E
SODIUM BICARBONATE	B	C	C	C	C	C	D	D	D	E
SODIUM BISULFITE	TB	TC	TC	TD	TD	TD	TD	TD	TD	TD
SODIUM BISULFATE	B	C	C	C	C	C	C	C	C	E
SODIUM CARBONATE	B	C	C	C	C	C	C	C	C	E
SODIUM CHLORATE 50%	A	TB	TB	TB	TB	TB	TB	TB	TB	TD
SODIUM CHLORIDE	B	B	B	B	B	B	B	B	B	E
SODIUM CHLORITE	A	A	A	A	A	A	A	A	A	D
SODIUM CHROMATE	A	B	B	B	B	B	B	B	B	D
SODIUM DICHROMATE	B	B	B	B	B	B	B	B	B	E
SODIUM FERROCYANIDE	TB	TB	TB	TB	TB	TB	TB	TB	TB	TD
SODIUM FLUORIDE	A	A	A	A	A	A	A	A	A	TB
SODIUM HYDROXIDE 10%	C	C	C	D	D	E	D	D	D	E
SODIUM HYDROXIDE 50%	C	C	C	C	C	D	D	C	D	E
SODIUM HYPOCHLORITE 3%	A	B	B	A	A	A	A	A	B	D
SODIUM HYPOCHLORITE 5-15%	A	A	A	A	A	A	A	A	A	A
SODIUM OXALATE	B	C	C	C	C	C	C	C	D	E
SODIUM PEROXIDE	B	B	B	B	B	B	B	B	C	E
SODIUM PHOSPHATE 10%	B	C	C	B	B	B	C	B	C	E
SODIUM SILICATE	TB	TB	TB	TC	TC	TC	TC	TC	TC	TD
SODIUM SULFATE	B	C	C	C	C	C	C	C	C	E
SODIUM SULFIDE	B	C	C	C	C	C	C	C	C	E
SODIUM SULFITE	B	C	C	C	C	C	C	C	C	E

This data is provided as a service of Applied Polymer Solutions and is believed to be accurate. However this information is neither recommendations by APS nor product specifications. APS reserves the right to change or modify data as necessary.

CHEMICAL RESISTANCE CHART

	RR 1005	RR 1010	RR 1010 AM	RR 1204	RR 1205	RR 1206	RR 1208	RR 1301	RR 1420	RR 1456
SODIUM TARTRATE	B	C	C	C	C	C	C	C	C	E
SODIUM THIOSULFATE	B	C	C	C	C	C	C	C	C	E
STEARIC ACID	A	A	A	B	B	A	A	A	B	E
STYRENE	A	B	B	B	B	B	B	B	B	D
SULFAMIC ACID 25%	A	A	A	A	A	A	A	A	A	TD
SULFURIC ACID 10%	B	B	B	C	C	C	C	B	C	E
SULFURIC ACID 30%	A	A	A	A	A	A	B	A	C	D
SULFURIC ACID 98%	A	A	A	A	A	A	A	A	A	C
TALL OIL	B	C	C	C	C	C	C	C	C	E
TARTARIC ACID	TB	TB	TB	TB	TB	TB	TB	TB	TB	TD
TETROCHLOROETHANE	A	A	A	A	A	A	A	A	B	D
TETRAHYDROFURAN	A	A	A	A	A	A	A	A	A	A
THIONYL CHLORIDE	A	A	A	A	A	A	A	A	A	A
TOLUENE	B	B	B	B	B	B	B	B	C	D
TOLUENE SULFONIC ACID	B	B	B	B	B	B	B	B	B	D
TOLUIDENE	A	B	B	B	B	B	B	B	B	E
TRICHLOROACETIC ACID 20%	A	A	A	A	A	A	A	A	A	B
TRICHLOROETHANE	A	C	C	C	C	A	C	C	C	D
TRICHLOROETHYLENE	A	A	A	A	A	A	A	A	A	TD
TRICESYL PHOSPHATE	TB	TB	TB	TB	TB	TB	TB	TB	TB	TD
TRISODIUM PHOSPHATE	B	C	C	C	C	C	C	C	C	E
TURPENTINE	B	B	B	B	B	C	B	B	B	D
UREA SOLUTIONS	TB	TC	TC	TC	TC	TC	TC	TC	TC	TE
WHITE LIQUOR (PAPER)	TB	TB	TB	TB	TB	TB	TB	TB	TB	TE
XYLENE	B	B	B	C	C	B	C	C	C	D
ZINC CHLORATE	A	TB	TB	TB	TB	TB	TB	TB	TB	TD
ZINC SULFATE	B	B	B	B	B	B	B	B	B	E

This data is provided as a service of Applied Polymer Solutions and is believed to be accurate. However this information is neither recommendations by APS nor product specifications. APS reserves the right to change or modify data as necessary.

CHEMICAL RESISTANCE CHART

	RR 1530	RR 1601	RR 1701	RR 1702	RR 2018	RR 2021	RR 2125	RR 2129	RR 2129 V	RR 2420
ACETALDEHYDE	B	B	C	B	B	B	C	B	B	C
ACETIC ACID 5%	B	B	B	A	A	A	B	B	B	D
ACETIC ACID 10%	A	A	A	A	A	A	A	A	A	C
ACETIC ACID 25%	A	A	A	A	A	A	A	A	A	A
ACETIC ACID GLACIAL	A	A	A	A	A	A	A	A	A	A
ACETIC ANHYDRIDE	B	B	B	A	A	A	B	B	B	C
ACETONE 10%	C	B	C	B	B	B	B	B	B	C
ACETONE 100%	B	A	C	B	A	B	B	A	A	C
ACETYL CHLORIDE	A	A	A	A	A	A	A	A	A	TB
ACETONITRILE	B	B	B	B	B	B	B	B	B	C
ACRYLIC ACID	TB	TB	TB	A	A	A	TB	TB	TB	TC
ACRYLONITRILE	TB	TB	TB	A	A	A	TB	TB	TB	TB
ADIPIIC ACID 25%	A	B	B	B	B	B	B	B	B	B
ALLYL ALCOHOL	TC	TC	TC	TB	TB	TB	TC	TC	TC	TC
ALLYL CHLORIDE	TB	TB	TB	A	A	A	TB	TB	TB	TB
ALUMINUM BROMIDE	C	C	D	C	C	C	D	C	C	D
ALUMINUM CHLORIDE	TB	TB	TC	TC	TC	TC	TC	TB	TB	TD
ALUMINUM FLUORIDE	TB	TC	TC	TC	TC	TC	TC	TC	TC	TD
ALUMINUM HYDROXIDE	C	C	C	C	C	C	C	C	C	D
ALUMINUM NITRATE	C	C	D	C	C	C	D	C	C	D
ALUMINUM SULFATE	C	C	C	B	B	B	C	C	C	D
AMMONIA	C	C	D	C	C	C	D	C	C	D
AMMONIUM CHLORIDE	TB	TB	TC	TB	TB	TB	TC	TC	TC	TD
AMMONIUM FLUORIDE	TB	TB	TB	TB	TB	TB	TB	TB	TB	TC
AMMONIUM HYDROXIDE	TC	TC	TC	TB	TB	TB	TC	TC	TC	TC
AMMONIUM NITRATE	C	D	D	C	C	C	D	C	C	D
AMMONIUM OXALATE	C	C	C	B	B	B	C	C	C	C
AMMONIUM NITRATE	TC	TC	TD	TC	TC	TC	TD	TC	TC	TD
AMMONIUM PERSULFATE	B	B	C	B	B	B	C	B	C	C
AMMONIUM PHOSPHATE	C	C	C	B	B	B	C	C	C	C
AMMONIUM SULFATE	C	C	D	B	B	B	D	C	C	C

This data is provided as a service of Applied Polymer Solutions and is believed to be accurate. However this information is neither recommendations by APS nor product specifications. APS reserves the right to change or modify data as necessary.

CHEMICAL RESISTANCE CHART

	RR 1530	RR 1601	RR 1701	RR 1702	RR 2018	RR 2021	RR 2125	RR 2129	RR 2129 V	RR 2420
AMMONIUM SULFIDE	C	C	D	C	C	C	D	C	C	C
AMMONIUM SULFITE	C	C	D	C	C	C	D	C	C	C
AMYL ACETATE	TB	TC	TC	TB	TB	TB	TC	TC	TC	TC
AMYL ALCOHOL	B	B	C	B	B	B	C	B	B	C
ANILINE	B	B	B	A	A	A	B	B	B	B
ANILINE HYDROCHLORIDE	B	B	B	A	A	A	B	B	B	B
ANTIMONY CHLORIDE	A	A	TB	A	A	A	TB	A	A	TB
AQUA REGIA	A	A	A	A	A	A	A	A	A	A
ARSENOUS ACID	A	TB	TB	A	A	A	TB	TB	TB	TB
BARIUM ACETATE	C	C	C	A	A	A	C	C	C	D
BARIUM BROMIDE	C	B	C	B	B	B	C	C	C	C
BARIUM CARBONATE	C	B	C	B	B	B	C	B	B	C
BARIUM CHLORIDE	B	B	C	B	B	B	B	B	B	C
BARIUM HYDROXIDE	TC	TC	TC	TB	TB	TB	TC	TC	TC	TD
BARIUM SULFATE	C	C	C	B	B	B	C	C	C	D
BARIUM SULFIDE	B	B	C	A	A	A	C	B	B	C
BENZYL CHLORIDE	A	A	TB	A	A	A	TB	A	A	TC
BENZOIC ACID	B	B	C	B	B	B	C	C	C	C
BENZALDEHYDE	TB	TB	TB	A	A	A	TB	TB	TB	TC
BENZENE	TB	TB	TC	TB	TB	TB	TC	TB	TB	TC
BENZYL ALCOHOL	C	C	D	C	C	C	B	C	C	D
BLACK LIQUOR (PAPER)	TB	TB	TC	TB	TB	TB	TC	TB	TB	TC
BLOOD SUGAR	TC	TC	TC	TB	TB	TB	TC	TC	TC	TB
BORAX	C	C	C	B	B	B	C	C	C	C
BORIC ACID	B	B	C	A	A	A	C	B	B	C
BRINE	D	D	D	D	D	D	D	D	D	D
BROMINE LIQUID	A	A	A	A	A	A	A	A	A	A
BUTANOL	C	C	D	C	C	C	C	C	C	D
BUTYL ACETATE	C	C	C	B	B	B	C	C	C	C
BUTYL ACRYLATE	TB	TB	TB	A	A	A	TB	TB	TB	TB

This data is provided as a service of Applied Polymer Solutions and is believed to be accurate. However this information is neither recommendations by APS nor product specifications. APS reserves the right to change or modify data as necessary.

CHEMICAL RESISTANCE CHART

	RR 1530	RR 1601	RR 1701	RR 1702	RR 2018	RR 2021	RR 2125	RR 2129	RR 2129 V	RR 2420
BUTYL AMINE	TB	TB	TB	A	A	A	TB	TB	TB	TB
BUTYL CARBITOL	TB	TC	TC	TB	TB	TB	TC	TC	TC	TC
BUTYL CELLOSOLVE	C	C	C	B	B	B	C	C	C	C
BUTYL ETHER	C	B	C	B	B	B	C	C	C	C
BUTYRIC ACID	A	A	A	A	A	A	A	A	A	B
CALCIUM BISULFITE	D	D	D	C	C	C	D	D	D	D
CALCIUM BROMIDE	TB	TB	TC	TB	TB	TB	TC	TB	TB	TC
CALCIUM CARBONATE	C	C	C	B	B	B	C	C	C	C
CALCIUM CHLORATE	B	B	C	B	B	B	C	B	B	C
CALCIUM CHLORIDE	C	C	D	C	C	C	D	C	C	D
CALCIUM HYDROXIDE	C	C	D	B	B	B	D	C	C	C
CALCIUM HYPOCHLORITE	TB	TB	TB	A	A	A	TB	TB	TB	TC
CALCIUM NITRATE	C	C	D	C	C	C	D	C	C	D
CALCIUM SULFATE	C	C	C	B	B	B	C	C	C	C
CALCIUM SULFITE	C	C	C	B	B	B	C	C	C	C
CALCIUM DISULFIDE	D	B	B	A	A	A	B	B	B	C
CARBON TETRACHLORIDE	C	C	C	B	B	B	B	C	C	C
CASTOR OIL	C	C	C	B	B	B	C	C	C	C
CELLOSOLVE	TC	TC	TC	TB	TB	TB	TC	TC	TC	TD
CELLOSOLVE ACETATE	C	TC	C	B	B	B	C	C	C	C
CHLOROACETIC ACID 25%	A	C	B	A	A	A	A	B	B	A
CHLOROACETIC ACID 50%	A	A	A	A	A	A	A	A	A	A
CHLOROBENZENE	B	A	C	B	B	B	C	B	B	B
CHLOROFORM	TB	B	TB	A	A	A	TB	TB	TB	A
CHLOROPHENOL	A	TB	A	A	A	A	A	A	A	A
CHLOROSULFONIC ACID	A	A	A	A	A	A	A	A	A	A
CHLOROTOLUENE	TB	A	TB	A	A	A	TB	TB	TB	TB
CHROMIC ACID 10%	A	TB	A	A	A	A	A	B	B	B
CHROMIC ACID 40%	A	B	A	A	A	A	A	A	A	A
CHROMIC CHLORIDE	A	A	A	A	A	A	A	A	A	A
CITRIC ACID	B	A	C	B	B	B	C	C	C	D

This data is provided as a service of Applied Polymer Solutions and is believed to be accurate. However this information is neither recommendations by APS nor product specifications. APS reserves the right to change or modify data as necessary.

CHEMICAL RESISTANCE CHART

	RR 1530	RR 1601	RR 1701	RR 1702	RR 2018	RR 2021	RR 2125	RR 2129	RR 2129 V	RR 2420
COPPER ACETATE	C	C	C	B	B	B	C	C	C	D
COPPER CHLORIDE	B	C	B	B	B	B	B	C	C	D
COPPER CYANIDE	TC	C	TC	TB	TB	TB	TC	TC	TC	TC
COPPER NITRATE	TC	TC	TC	TB	TB	TB	TC	TC	TC	TC
COPPER SULFATE	C	TC	C	B	B	B	C	C	C	B
CORN OIL	C	B	C	B	B	B	C	C	C	C
CORN STARCH SLURRY	D	C	E	B	C	B	E	D	D	E
CORN SUGAR	D	D	D	C	C	C	D	D	D	C
COTTONSEED OIL	C	D	C	B	B	B	C	C	C	C
CREOSOTE	B	C	C	B	B	B	C	B	B	C
CRESYLIC ACID	A	B	TB	A	A	A	TB	TB	TB	TB
CUMENE	C	TB	C	B	B	B	C	C	C	B
CUTTING OIL	C	B	C	B	B	B	C	C	C	C
CYCLOHEXANE	C	C	C	B	B	B	C	C	C	C
CYCLOHEXANONE	C	C	C	B	B	B	C	C	C	C
CYMENE	TB	C	TC	TB	TB	TB	TC	TB	TC	TC
DETERGENTS ORGANIC	TD	TB	TE	TC	TC	TC	TE	TC	TC	TC
DETERGENTS SULFONATED	TD	TC	TE	TC	TC	TC	TE	TD	TD	TC
DEXTROSE	D	TD	E	D	C	D	E	D	D	E
DIBUTYL PHTHALATE	C	D	D	C	C	C	D	D	D	D
DICHLORACETIC ACID	A	C	TC	A	A	A	TB	TB	TB	TB
DICHLOROBENZENE	B	TB	C	B	B	B	C	C	C	C
DICHLOROETHANE	A	C	A	A	A	A	A	A	A	A
DIESEL FUEL	B	A	C	B	B	B	C	C	C	B
DIETHANOLAMINE	TB	C	TB	TB	TB	TB	TB	TB	TB	TC
DIETHYL BENZENE	TB	TB	TC	TB	TB	TB	TC	TC	TC	TC
DIETHYL KETONE	TB	TB	TB	A	A	A	TB	TB	TB	TB
DIETHYLENE GLYCOL	C	C	C	B	B	B	C	C	C	C
DIETHYL ETHER	B	B	B	A	A	A	B	B	B	C
DIMETHYL ANILINE	TB	TB	TB	TB	A	TB	TB	TB	TB	TB
DIMETHYL FORMAMIDE	A	A	A	A	A	A	A	A	A	A

This data is provided as a service of Applied Polymer Solutions and is believed to be accurate. However this information is neither recommendations by APS nor product specifications. APS reserves the right to change or modify data as necessary.

CHEMICAL RESISTANCE CHART

	RR 1530	RR 1601	RR 1701	RR 1702	RR 2018	RR 2021	RR 2125	RR 2129	RR 2129 V	RR 2420
DIMETHYL SULFOXIDE	A	A	A	A	A	A	A	A	A	A
DINITRO BENZENE	TB	TB	TB	A	A	A	TB	TB	TB	TB
DINITRO TOLUENE	TB	TB	TB	A	A	A	TB	TB	TB	TB
EPICHLOROHYDRIN	B	B	B	A	A	A	B	B	B	B
ETHANOL	A	C	C	A	A	A	C	C	C	C
ETHANOLAMINE	B	B	B	A	A	A	B	B	B	B
ETHYL ACETATE	B	A	A	A	A	A	A	A	A	B
ETHYL ACRYLATE	A	A	A	A	A	A	A	A	A	B
ETHYLAMINE	TB	A	A	A	A	A	A	A	A	TB
ETHYL BENZENE	TB	TB	TB	A	A	A	TB	TB	TB	TB
ETHYL BROMIDE	A	A	A	A	A	A	A	A	A	A
ETHYL CHLORIDE	A	A	A	A	A	A	A	A	A	A
ETHYL DICHLORIDE	A	A	A	A	A	A	A	A	A	A
ETHYLENE GLYCOL	C	D	D	C	C	C	D	D	D	D
ETHYL SULFATE	TB	TB	TB	A	A	A	TB	TB	TB	TC
FATTY ACIDS	TB	TB	TB	A	A	A	TB	TB	TB	TB
FERRIC CHLORIDE	C	C	E	C	C	C	C	C	C	D
FERRIC SULFATE	C	D	E	C	C	C	C	D	D	D
FERROUS NITRATE	C	C	C	B	C	B	C	C	C	C
FERROUS CHLORIDE	TB	TC	TD	TB	TB	TB	TB	TC	TC	TD
FERROUS SULFATE	TD	TC	TE	TB	TD	TB	TD	TC	TC	TD
FLUOSILICIC ACID 10-25%	A	A	A	A	A	A	A	A	A	A
FORMALDEHYDE	C	B	C	B	B	B	C	C	C	B
FORMIC ACID 10%	B	B	B	A	A	A	B	B	B	B
FORMIC ACID 50%	A	A	A	A	A	A	A	A	A	A
FUEL OIL	B	C	C	B	B	B	C	C	C	B
FURFURAL ALCOHOL	A	A	TB	A	A	A	TB	A	A	TB
GASOLINE AVIATION	B	B	B	A	A	A	B	B	B	C
GASOLINE DIESEL	B	B	B	A	A	A	B	B	B	C
GASOLINE JET FUEL	B	B	B	A	A	A	B	B	B	C
GASOLINE UNLEADED	B	C	C	B	B	B	C	C	C	C

This data is provided as a service of Applied Polymer Solutions and is believed to be accurate. However this information is neither recommendations by APS nor product specifications. APS reserves the right to change or modify data as necessary.

CHEMICAL RESISTANCE CHART

	RR 1530	RR 1601	RR 1701	RR 1702	RR 2018	RR 2021	RR 2125	RR 2129	RR 2129 V	RR 2420
GLUCOSE	E	D	E	D	D	D	E	E	E	D
GLYCERINE	TC	TD	TD	TC	TC	TC	TD	TD	TD	TC
GLYCOLIC ACID 70%	A	A	A	A	A	A	A	A	A	A
GREEN LIQUOR (PAPER)	B	C	C	B	B	B	C	C	C	C
HEPTANE	C	C	D	C	C	C	D	C	C	C
HEXANE	C	C	D	C	C	C	D	C	C	C
HYDRAULIC FLUID	B	D	C	B	B	B	C	B	B	C
HYDRAZINE 35%	TB	TB	TB	A	A	A	TB	TB	TB	A
HYDRIODIC ACID 20%	A	B	C	A	A	A	B	B	B	B
HYDROBROMIC ACID 18%	A	A	A	A	A	A	A	A	A	B
HYDROBROMIC ACID 40%	A	A	A	A	A	A	A	A	A	A
HYDROBROMIC ACID 60%	A	A	A	A	A	A	A	A	A	A
HYDROCHLORIC ACID 10%	C	C	C	C	C	C	C	B	B	D
HYDROCHLORIC ACID 36%	B	A	B	C	B	A	B	A	A	C
HYDROFLUORIC ACID	A	A	A	A	A	A	A	A	A	A
HYDROGEN PEROXIDE 10%	A	B	B	A	A	A	B	B	B	B
HYDROGEN PEROXIDE 50%	A	A	A	A	A	B	A	A	A	A
HYDROGEN SULFIDE 5%	C	C	C	B	B	A	C	C	C	C
HYDROGEN SULFIDE 100%	TB	TB	TC	A	A	A	TC	TB	TB	TB
HYPOCHLOROUS ACID	A	A	A	A	A	A	A	A	A	A
IODINE CRYSTALS/VAPOR	TB	TC	TC	TB	TB	TB	TC	TC	TC	TC
ISOPHORONE	C	C	C	B	B	B	C	C	C	C
ISOPROPYL ACETATE	C	C	C	B	B	B	C	C	C	C
ISOPROPYL ALCOHOL	C	C	C	B	B	B	C	C	C	C
JET FUEL (JP-4)	B	B	B	A	A	A	B	B	B	C
KEROSENE	B	C	C	B	B	B	C	C	C	C
LACTIC ACID 10-20%	B	C	C	B	B	B	C	C	C	C
LACTIC ACID 50%	A	A	A	A	A	A	A	A	A	A
LACTIC ACID 85%	A	A	A	A	A	A	A	A	A	A
LAURIC ACID	A	A	TB	A	A	A	TB	A	A	TB
LEAD ACETATE	TB	TC	TD	TC	TC	TC	TC	TC	TC	TC

This data is provided as a service of Applied Polymer Solutions and is believed to be accurate. However this information is neither recommendations by APS nor product specifications. APS reserves the right to change or modify data as necessary.

CHEMICAL RESISTANCE CHART

	RR 1530	RR 1601	RR 1701	RR 1702	RR 2018	RR 2021	RR 2125	RR 2129	RR 2129 V	RR 2420
LEVULINIC ACID	TB	TC	TC	TB	TB	TB	TC	TC	TC	TC
LINSEED OIL	B	B	B	B	B	B	B	B	B	C
LITHIUM BROMIDE	TC	TB	TC	TB	TB	TB	TC	TC	TC	TB
LITHIUM CHLORIDE SAT'D	B	B	B	A	A	A	B	B	B	B
LITHIUM HYDROXIDE	A	A	A	A	A	A	A	A	A	TB
MAGNESIUM BISULFITE	B	B	B	B	B	B	B	B	B	C
MAGNESIUM CARBONATE	C	C	C	B	B	B	C	C	C	C
MAGNESIUM CHLORIDE	TB	TB	TB	TB	TB	TB	TB	TB	TB	TB
MAGNESIUM HYDROXIDE	B	B	B	B	B	B	B	B	B	B
MAGNESIUM NITRATE	TB	TB	TB	TB	TB	TB	TB	TB	TB	TB
MAGNESIUM SULFATE	TB	TB	TB	TB	TB	TB	TB	TB	TB	TB
MALEIC ACID	A	A	A	A	A	A	A	A	A	B
MANGANESE CHLORIDE	A	TB	TB	TB	TB	TB	TB	TB	TB	TB
MANGANESE SULFATE	TB	TB	TC	TB	TB	TB	TB	TB	TB	TB
MERCURIC CHLORIDE	A	TB	TC	TB	TB	TB	TB	TB	TB	TC
MERCUROUS CHLORIDE	TB	TC	TB	TB	TB	TB	TC	TC	TC	TC
METHANOL	A	A	A	A	A	A	A	A	A	B
METHYL ACETATE	A	A	A	A	A	A	A	A	A	B
METHYLAMYL ALCOHOL	TC	TC	TC	TB	TB	TB	TC	TC	TC	TC
METHYL BENZOATE	B	B	B	A	A	A	B	B	B	C
METHYL CHLORIDE	A	A	A	A	A	A	A	A	A	A
METHYLENE CHLORIDE	A	A	A	A	A	A	A	A	A	A
METHYL ETHYL KETONE	A	A	A	A	A	A	A	A	A	A
METHYL ISOBUTYL KETONE	A	B	B	A	A	A	B	B	B	B
MILK	D	D	D	C	C	C	D	D	D	D
MOLASSES	D	D	D	C	C	C	D	D	D	D
MINERAL OILS	TC	TC	TC	TB	TB	TB	TC	TC	TC	TD
MINERAL SPIRITS	C	B	B	B	B	B	C	B	B	C
MOTOR OIL	C	C	C	C	C	C	C	C	C	C
M-PYROL	A	A	A	A	A	A	A	A	A	A
NAPHTHA ALIPHATIC	B	B	B	B	B	B	B	B	B	C

This data is provided as a service of Applied Polymer Solutions and is believed to be accurate. However this information is neither recommendations by APS nor product specifications. APS reserves the right to change or modify data as necessary.

CHEMICAL RESISTANCE CHART

	RR 1530	RR 1601	RR 1701	RR 1702	RR 2018	RR 2021	RR 2125	RR 2129	RR 2129 V	RR 2420
NAPHTHA AROMATIC	B	B	B	A	A	A	B	B	B	B
NICKEL CHLORIDE	A	A	A	A	A	A	A	A	A	TB
NICKEL NITRATE	B	B	B	B	B	B	B	B	B	C
NICKEL SULFATE	TB	TB	TB	TB	TB	TB	TB	TB	TB	TC
NITRIC ACID 5%	B	B	B	B	B	B	B	B	B	D
NITRIC ACID 30%	B	A	B	A	A	A	B	A	A	C
NITRIC ACID 60%	A	A	A	A	A	A	A	A	A	A
NITROBENZENE	A	A	A	A	A	A	A	A	A	TB
OIL SOUR CRUDE	C	C	C	B	B	B	C	C	C	C
OIL SWEET CRUDE	TC	TC	TC	TB	TB	TB	TC	TC	TC	TC
OLEIC ACID	A	A	A	A	A	A	A	A	A	B
OLEUM	A	A	A	A	A	A	A	A	A	A
OXALIC ACID	B	A	A	A	A	A	A	A	A	B
PERCHLORIC ACID	A	A	A	A	A	A	A	A	A	A
PERCHLOROETHYLENE	B	B	B	A	A	A	B	B	B	B
PHENOL 5%	A	A	A	A	A	A	A	A	A	A
PHENOL 85%	A	A	A	A	A	A	A	A	A	A
PHOSPHORIC ACID 40%	B	A	B	A	A	A	B	A	A	C
PHOSPHORIC ACID 85%	A	A	A	A	A	A	A	A	A	A
PICRIC ACID 10%	A	TB	TB	A	A	A	TB	TB	TB	TB
POTASSIUM ACETATE	C	C	C	B	B	B	C	C	C	D
POTASSIUM BROMIDE	C	C	C	B	B	B	C	C	C	D
POTASSIUM CARBONATE	C	C	D	B	B	B	D	C	C	D
POTASSIUM CHLORIDE	A	B	C	B	B	B	C	B	B	D
POTASSIUM HYDROXIDE 10%	C	C	C	B	B	B	C	C	C	D
POTASSIUM HYDROXIDE 50%	C	B	B	A	A	A	B	B	B	C
POTASSIUM IODIDE	TB	TB	TB	TB	TB	TB	TB	TB	TB	TB
POTASSIUM NITRATE	C	C	C	B	B	B	C	C	C	D
POTASSIUM PERMANGANATE	TB	TB	TB	A	A	A	TB	TB	TB	TB
POTASSIUM PERSULFATE	B	B	B	A	A	A	B	B	B	C
POTASSIUM SULFATE	C	C	C	B	B	B	C	C	C	C

This data is provided as a service of Applied Polymer Solutions and is believed to be accurate. However this information is neither recommendations by APS nor product specifications. APS reserves the right to change or modify data as necessary.

CHEMICAL RESISTANCE CHART

	RR 1530	RR 1601	RR 1701	RR 1702	RR 2018	RR 2021	RR 2125	RR 2129	RR 2129 V	RR 2420
PROPIONIC ACID	B	A	A	A	A	A	A	B	B	A
PROPYLENE GLYCOL	D	D	D	C	C	C	D	D	D	D
PYRIDINE	A	A	A	A	A	A	A	A	A	A
SALICYLIC ACID	TB	TB	TB	TB	TB	TB	TB	TB	TB	TB
SALT BRINE	C	C	D	C	C	C	D	C	C	D
SILVER NITRATE	A	A	A	A	A	A	A	A	A	TB
SKYDROL	B	B	B	B	B	B	B	B	B	C
SODIUM ACETATE	C	C	D	C	C	C	D	C	C	D
SODIUM BENZOATE	C	C	D	C	C	C	D	C	C	D
SODIUM BICARBONATE	C	C	D	C	C	C	D	C	C	D
SODIUM BISULFITE	TD	TD	TD	TC	TC	TC	TD	TD	TD	TD
SODIUM BISULFATE	C	C	C	B	B	B	C	C	C	D
SODIUM CARBONATE	C	C	C	B	B	B	C	C	C	D
SODIUM CHLORATE 50%	TB	TB	TB	A	A	A	TB	TB	TB	TB
SODIUM CHLORIDE	B	B	B	B	B	B	B	B	B	C
SODIUM CHLORITE	A	A	A	A	A	A	A	A	A	B
SODIUM CHROMATE	B	B	B	A	A	A	B	B	B	B
SODIUM DICHROMATE	B	B	B	B	B	B	B	B	B	B
SODIUM FERROCYANIDE	TB	TB	TB	TB	TB	TB	TB	TB	TB	TC
SODIUM FLUORIDE	A	A	A	A	A	A	A	A	A	A
SODIUM HYDROXIDE 10%	C	D	E	E	E	E	E	D	D	D
SODIUM HYDROXIDE 50%	C	C	E	D	D	D	E	D	D	D
SODIUM HYPOCHLORITE 3%	A	A	A	A	A	A	A	A	A	B
SODIUM HYPOCHLORITE 5-15%	A	A	A	A	A	A	A	A	A	A
SODIUM OXALATE	C	C	D	B	B	B	D	C	C	D
SODIUM PEROXIDE	B	B	C	B	B	B	C	B	B	C
SODIUM PHOSPHATE 10%	B	B	C	B	B	B	C	B	B	C
SODIUM SILICATE	TC	TC	TC	TB	TB	TB	TC	TC	TC	TC
SODIUM SULFATE	C	C	C	B	B	B	C	C	C	D
SODIUM SULFIDE	C	C	C	B	B	B	C	C	C	D
SODIUM SULFITE	C	C	C	B	B	B	C	C	C	D

This data is provided as a service of Applied Polymer Solutions and is believed to be accurate. However this information is neither recommendations by APS nor product specifications. APS reserves the right to change or modify data as necessary.

CHEMICAL RESISTANCE CHART

	RR 1530	RR 1601	RR 1701	RR 1702	RR 2018	RR 2021	RR 2125	RR 2129	RR 2129 V	RR 2420
SODIUM TARTRATE	C	C	C	B	B	B	C	C	C	D
SODIUM THIOSULFATE	C	C	C	B	B	B	C	C	C	C
STEARIC ACID	A	B	B	A	A	A	B	B	B	B
STYRENE	B	B	B	A	A	A	B	B	B	B
SULFAMIC ACID 25%	A	A	A	A	A	A	A	A	A	A
SULFURIC ACID 10%	B	C	C	C	C	C	C	B	B	D
SULFURIC ACID 30%	B	A	B	B	B	B	B	A	A	C
SULFURIC ACID 98%	A	A	A	A	A	A	A	A	A	B
TALL OIL	C	C	C	B	B	B	C	C	C	C
TARTARIC ACID	TB	TB	TB	TB	TB	TB	TB	TB	TB	TB
TETROCHLOROETHANE	A	A	B	A	A	A	A	A	A	B
TETRAHYDROFURAN	A	A	A	A	A	A	A	A	A	A
THIONYL CHLORIDE	A	A	A	A	A	A	A	A	A	A
TOLUENE	B	B	B	B	B	B	B	B	B	C
TOLUENE SULFONIC ACID	B	B	B	B	B	B	B	B	B	B
TOLUIDENE	B	B	B	A	A	A	B	B	B	B
TRICHLOROACETIC ACID 20%	A	A	A	A	A	A	A	A	A	A
TRICHLOROETHANE	C	C	B	B	A	B	B	B	B	C
TRICHLOROETHYLENE	A	A	A	A	A	A	A	A	A	TB
TRICESYL PHOSPHATE	TB	TB	TB	TB	TB	TB	TB	TB	TB	TB
TRISODIUM PHOSPHATE	C	C	C	B	B	B	C	C	C	C
TURPENTINE	C	B	B	B	B	B	B	B	B	C
UREA SOLUTIONS	TC	TC	TC	TB	TB	TB	TC	TC	TC	TC
WHITE LIQUOR (PAPER)	TB	TB	TB	TB	TB	TB	TB	TB	TB	TB
XYLENE	C	C	C	B	B	B	C	B	B	D
ZINC CHLORATE	TB	TB	TB	A	A	A	TB	TB	TB	TC
ZINC SULFATE	B	C	C	B	B	B	B	B	B	D

This data is provided as a service of Applied Polymer Solutions and is believed to be accurate. However this information is neither recommendations by APS nor product specifications. APS reserves the right to change or modify data as necessary.

CHEMICAL RESISTANCE CHART

	RR 2429	RR 2429 V	RR 2601	RR 2602	ST 3015 AM	ST 3103	ST 3105	ST 3105V	ST 3145	ST 3145 c
ACETALDEHYDE	C	C	B	B	B	B	B	B	B	B
ACETIC ACID 5%	D	D	B	B	B	B	B	B	A	A
ACETIC ACID 10%	C	C	A	A	A	A	A	A	A	A
ACETIC ACID 25%	A	A	A	A	A	A	A	A	A	A
ACETIC ACID GLACIAL	A	A	A	A	A	A	A	A	A	A
ACETIC ANHYDRIDE	C	C	B	B	A	A	A	A	A	A
ACETONE 10%	C	C	B	B	B	B	B	B	B	B
ACETONE 100%	C	C	A	A	A	A	A	A	B	B
ACETYL CHLORIDE	TB	TB	A	A	A	A	A	A	A	A
ACETONITRILE	C	C	B	B	B	B	B	B	B	B
ACRYLIC ACID	TC	TC	TB	TB	A	A	A	A	A	A
ACRYLONITRILE	TB	TB	TB	TB	A	A	A	A	A	A
ADIPIIC ACID 25%	B	B	B	B	B	B	B	B	B	B
ALLYL ALCOHOL	TC	TC	TC	TC	TB	TB	TB	TB	TB	TB
ALLYL CHLORIDE	TB	TB	TB	TB	A	A	A	A	A	A
ALUMINUM BROMIDE	D	D	C	C	C	C	C	C	C	C
ALUMINUM CHLORIDE	TD	TD	TB	TB	TC	TC	TC	TC	TC	TC
ALUMINUM FLUORIDE	TD	TD	TC	TC	TC	TC	TC	TC	TC	TC
ALUMINUM HYDROXIDE	D	D	C	C	C	C	C	C	C	C
ALUMINUM NITRATE	D	D	C	C	C	C	C	C	C	C
ALUMINUM SULFATE	D	D	C	C	B	B	B	B	B	B
AMMONIA	D	D	C	C	C	C	C	C	C	C
AMMONIUM CHLORIDE	TD	TD	TB	TB	TB	TB	TB	TB	TB	TB
AMMONIUM FLUORIDE	TC	TC	TB	TB	TB	TB	TB	TB	TB	TB
AMMONIUM HYDROXIDE	TC	TC	TC	TC	TB	TB	TB	TB	TB	TB
AMMONIUM NITRATE	D	D	D	D	C	C	C	C	C	C
AMMONIUM OXALATE	C	C	C	C	C	C	C	C	B	B
AMMONIUM NITRATE	TD	TD	TC	TC	TC	TC	TC	TC	TC	TC
AMMONIUM PERSULFATE	C	C	B	B	B	B	B	B	B	B
AMMONIUM PHOSPHATE	C	C	C	C	B	B	B	B	B	B
AMMONIUM SULFATE	C	C	C	C	C	C	C	C	B	B

This data is provided as a service of Applied Polymer Solutions and is believed to be accurate. However this information is neither recommendations by APS nor product specifications. APS reserves the right to change or modify data as necessary.

CHEMICAL RESISTANCE CHART

	RR 2429	RR 2429 V	RR 2601	RR 2602	ST 3015 AM	ST 3103	ST 3105	ST 3105V	ST 3145	ST 3145 c
AMMONIUM SULFIDE	C	C	C	C	C	C	C	C	C	C
AMMONIUM SULFITE	C	C	C	C	C	C	C	C	C	C
AMYL ACETATE	TC	TC	TC	TC	TB	TB	TB	TB	TB	TB
AMYL ALCOHOL	C	C	B	B	B	B	B	B	B	B
ANILINE	B	B	B	B	A	A	A	A	A	A
ANILINE HYDROCHLORIDE	B	B	B	B	A	A	A	A	A	A
ANTIMONY CHLORIDE	TB	TB	A	A	A	A	A	A	A	A
AQUA REGIA	A	A	A	A	A	A	A	A	A	A
ARSENOUS ACID	TB	TB	TB	TB	A	A	A	A	A	A
BARIUM ACETATE	D	D	C	C	B	B	B	B	A	A
BARIUM BROMIDE	C	C	B	B	B	B	B	B	B	B
BARIUM CARBONATE	C	C	B	B	B	B	B	B	B	B
BARIUM CHLORIDE	C	C	B	B	B	B	B	B	B	B
BARIUM HYDROXIDE	TD	TD	TC	TC	TB	TB	TB	TB	TB	TB
BARIUM SULFATE	D	D	C	C	B	B	B	B	B	B
BARIUM SULFIDE	C	C	B	B	A	A	A	A	A	A
BENZYL CHLORIDE	TC	TC	A	A	A	A	A	A	A	A
BENZOIC ACID	C	C	B	C	B	B	B	B	B	B
BENZALDEHYDE	TC	TC	TB	TB	A	A	A	A	A	A
BENZENE	TC	TC	TB	TB	TB	TB	TB	TB	TB	TB
BENZYL ALCOHOL	D	D	C	C	C	B	C	C	C	C
BLACK LIQUOR (PAPER)	TC	TC	TB	TB	TB	TB	TB	TB	TB	TB
BLOOD SUGAR	TB	TB	TC	TC	TB	TB	TB	TB	TB	TB
BORAX	C	C	C	C	B	B	B	B	B	B
BORIC ACID	C	C	B	B	A	A	A	A	A	A
BRINE	D	D	D	D	D	D	D	D	D	D
BROMINE LIQUID	A	A	A	A	A	A	A	A	A	A
BUTANOL	D	D	C	C	C	C	C	C	C	C
BUTYL ACETATE	C	C	C	C	B	B	B	B	B	B
BUTYL ACRYLATE	TB	TB	TB	TB	A	A	A	A	A	A

This data is provided as a service of Applied Polymer Solutions and is believed to be accurate. However this information is neither recommendations by APS nor product specifications. APS reserves the right to change or modify data as necessary.

CHEMICAL RESISTANCE CHART

	RR 2429	RR 2429 V	RR 2601	RR 2602	ST 3015 AM	ST 3103	ST 3105	ST 3105V	ST 3145	ST 3145 c
BUTYL AMINE	TB	TB	TB	TB	A	A	A	A	A	A
BUTYL CARBITOL	TC	TC	TC	TC	TB	TB	TB	TB	TB	TB
BUTYL CELLOSOLVE	C	C	C	C	B	B	B	B	B	B
BUTYL ETHER	C	C	B	B	B	B	B	B	B	B
BUTYRIC ACID	B	B	A	A	A	A	A	A	A	A
CALCIUM BISULFITE	D	D	D	D	C	C	C	C	C	C
CALCIUM BROMIDE	TC	TC	TB	TB	TB	TB	TB	TB	TB	TB
CALCIUM CARBONATE	C	C	C	C	B	B	B	B	B	B
CALCIUM CHLORATE	C	C	B	B	B	B	B	B	B	B
CALCIUM CHLORIDE	D	D	C	C	C	C	C	C	C	C
CALCIUM HYDROXIDE	C	C	C	C	B	B	B	B	B	B
CALCIUM HYPOCHLORITE	TC	TC	TB	TB	A	A	A	A	A	A
CALCIUM NITRATE	D	D	C	C	C	C	C	C	C	C
CALCIUM SULFATE	C	C	C	C	B	B	B	B	B	B
CALCIUM SULFITE	C	C	C	C	B	B	B	B	B	B
CALCIUM DISULFIDE	C	C	B	B	A	A	A	A	A	A
CARBON TETRACHLORIDE	C	C	C	C	B	B	B	B	B	B
CASTOR OIL	C	C	C	C	B	B	B	B	B	B
CELLOSOLVE	TD	TD	TC	TC	TB	TB	TB	TB	TB	TB
CELLOSOLVE ACETATE	C	C	C	C	B	B	B	B	B	B
CHLOROACETIC ACID 25%	A	A	A	A	A	A	A	A	A	A
CHLOROACETIC ACID 50%	A	A	A	A	A	A	A	A	A	A
CHLOROBENZENE	B	B	B	B	B	B	B	B	B	B
CHLOROFORM	A	A	TB	TB	A	A	A	A	A	A
CHLOROPHENOL	A	A	A	A	A	A	A	A	A	A
CHLOROSULFONIC ACID	A	A	A	A	A	A	A	A	A	A
CHLOROTOLUENE	TB	TB	TB	TB	A	A	A	A	A	A
CHROMIC ACID 10%	B	B	B	B	A	A	A	A	A	A
CHROMIC ACID 40%	A	A	A	A	A	A	A	A	A	A
CHROMIC CHLORIDE	A	A	A	A	A	A	A	A	A	A
CITRIC ACID	D	D	C	C	B	B	B	B	B	B

This data is provided as a service of Applied Polymer Solutions and is believed to be accurate. However this information is neither recommendations by APS nor product specifications. APS reserves the right to change or modify data as necessary.

CHEMICAL RESISTANCE CHART

	RR 2429	RR 2429 V	RR 2601	RR 2602	ST 3015 AM	ST 3103	ST 3105	ST 3105V	ST 3145	ST 3145 c
COPPER ACETATE	D	D	C	C	B	B	B	B	B	B
COPPER CHLORIDE	D	D	C	C	B	B	B	B	B	B
COPPER CYANIDE	TC	TC	TC	TC	TB	TB	TB	TB	TB	TB
COPPER NITRATE	TC	TC	TC	TC	TB	TB	TB	TB	TB	TB
COPPER SULFATE	B	B	B	B	B	B	B	B	B	B
CORN OIL	C	C	C	C	B	B	B	B	B	B
CORN STARCH SLURRY	E	E	D	D	D	D	D	D	B	B
CORN SUGAR	C	C	D	D	C	C	C	C	C	C
COTTONSEED OIL	C	C	C	C	B	B	B	B	B	B
CREOSOTE	C	C	B	B	B	B	B	B	B	B
CRESYLIC ACID	TB	TB	TB	TB	A	A	A	A	A	A
CUMENE	B	B	B	B	B	B	B	B	B	B
CUTTING OIL	C	C	C	C	C	C	C	C	B	B
CYCLOHEXANE	C	C	C	C	B	B	B	B	B	B
CYCLOHEXANONE	C	C	C	C	C	C	C	C	B	B
CYMENE	TC	TC	TB	TB	TB	TB	TB	TB	TB	TB
DETERGENTS ORGANIC	TC	TC	TC	TC	TC	TC	TC	TC	TC	TC
DETERGENTS SULFONATED	TC	TC	TD	TD	TC	TC	TC	TC	TC	TC
DEXTROSE	E	E	D	D	D	D	D	D	D	D
DIBUTYL PHTHALATE	D	D	C	C	C	C	C	C	C	C
DICHLORACETIC ACID	TB	TB	TB	TB	A	A	A	A	A	A
DICHLOROBENZENE	C	C	C	C	B	B	B	B	B	B
DICHLOROETHANE	A	A	A	A	A	A	A	A	A	A
DIESEL FUEL	B	B	C	C	B	B	B	B	B	B
DIETHANOLAMINE	TC	TC	TB	TB	TB	TB	TB	TB	TB	TB
DIETHYL BENZENE	TC	TC	TC	TC	TB	TB	TB	TB	TB	TB
DIETHYL KETONE	TB	TB	TB	TB	A	A	A	A	A	A
DIETHYLENE GLYCOL	C	C	C	C	B	B	B	B	B	B
DIETHYL ETHER	C	C	B	B	A	A	A	A	A	A
DIMETHYL ANILINE	TB	TB	TB	TB	A	A	A	A	A	A
DIMETHYL FORMAMIDE	A	A	A	A	A	A	A	A	A	A

This data is provided as a service of Applied Polymer Solutions and is believed to be accurate. However this information is neither recommendations by APS nor product specifications. APS reserves the right to change or modify data as necessary.

CHEMICAL RESISTANCE CHART

	RR 2429	RR 2429 V	RR 2601	RR 2602	ST 3015 AM	ST 3103	ST 3105	ST 3105V	ST 3145	ST 3145 c
DIMETHYL SULFOXIDE	A	A	A	A	A	A	A	A	A	A
DINITRO BENZENE	TB	TB	TB	TB	A	A	A	A	A	A
DINITRO TOLUENE	TB	TB	TB	TB	A	A	A	A	A	A
EPICHLOROHYDRIN	B	B	B	B	B	B	B	B	A	A
ETHANOL	C	C	C	C	B	B	B	B	B	B
ETHANOLAMINE	B	B	B	B	A	A	A	A	A	A
ETHYL ACETATE	B	B	A	A	A	A	A	A	A	A
ETHYL ACRYLATE	B	B	A	A	A	A	A	A	A	A
ETHYLAMINE	TB	TB	A	A	A	A	A	A	A	A
ETHYL BENZENE	TB	TB	TB	TB	A	A	A	A	A	A
ETHYL BROMIDE	A	A	A	A	A	A	A	A	A	A
ETHYL CHLORIDE	A	A	A	A	A	A	A	A	A	A
ETHYL DICHLORIDE	A	A	A	A	A	A	A	A	A	A
ETHYLENE GLYCOL	D	D	D	D	C	C	C	C	C	C
ETHYL SULFATE	TC	TC	TB	TB	A	A	A	A	A	A
FATTY ACIDS	TB	TB	TB	TB	TB	TB	TB	TB	A	A
FERRIC CHLORIDE	D	D	C	C	D	D	D	D	C	C
FERRIC SULFATE	D	D	D	D	C	C	C	C	C	C
FERROUS NITRATE	C	C	C	C	B	B	B	B	B	B
FERROUS CHLORIDE	TD	TD	TC	TC	TB	TB	TB	TB	TB	TB
FERROUS SULFATE	TD	TD	TC	TC	TC	TC	TC	TC	TB	TB
FLUOSILICIC ACID 10-25%	A	A	A	A	A	A	A	A	A	A
FORMALDEHYDE	B	B	B	B	B	B	B	B	B	B
FORMIC ACID 10%	B	B	B	B	A	A	A	A	A	A
FORMIC ACID 50%	A	A	A	A	A	A	A	A	A	A
FUEL OIL	B	B	C	C	B	B	B	B	B	B
FURFURAL ALCOHOL	TB	TB	A	A	A	A	A	A	A	A
GASOLINE AVIATION	C	C	B	B	A	A	A	A	B	B
GASOLINE DIESEL	C	C	B	B	A	A	A	A	B	B
GASOLINE JET FUEL	C	C	B	B	A	A	A	A	B	B
GASOLINE UNLEADED	C	C	C	C	B	B	B	B	B	B

This data is provided as a service of Applied Polymer Solutions and is believed to be accurate. However this information is neither recommendations by APS nor product specifications. APS reserves the right to change or modify data as necessary.

CHEMICAL RESISTANCE CHART

	RR 2429	RR 2429 V	RR 2601	RR 2602	ST 3015 AM	ST 3103	ST 3105	ST 3105V	ST 3145	ST 3145 c
GLUCOSE	D	D	D	D	D	D	D	D	D	D
GLYCERINE	TC	TC	TD	TD	TC	TC	TC	TC	TC	TC
GLYCOLIC ACID 70%	A	A	A	A	A	A	A	A	A	A
GREEN LIQUOR (PAPER)	C	C	C	C	B	B	B	B	B	B
HEPTANE	C	C	C	C	C	C	C	C	C	C
HEXANE	C	C	C	C	C	C	C	C	C	C
HYDRAULIC FLUID	C	C	D	D	B	B	B	B	B	B
HYDRAZINE 35%	A	A	TB	TB	A	A	A	A	A	A
HYDRIODIC ACID 20%	B	B	B	B	A	A	A	A	A	A
HYDROBROMIC ACID 18%	B	B	A	A	A	A	A	A	A	A
HYDROBROMIC ACID 40%	A	A	A	A	A	A	A	A	A	A
HYDROBROMIC ACID 60%	A	A	A	A	A	A	A	A	A	A
HYDROCHLORIC ACID 10%	D	D	C	C	B	B	B	B	C	C
HYDROCHLORIC ACID 36%	C	C	A	A	B	B	B	B	B	B
HYDROFLUORIC ACID	A	A	A	A	A	A	A	A	A	A
HYDROGEN PEROXIDE 10%	B	B	B	B	A	A	A	A	A	A
HYDROGEN PEROXIDE 50%	A	A	A	A	A	A	A	A	A	A
HYDROGEN SULFIDE 5%	C	C	C	C	B	B	B	B	B	B
HYDROGEN SULFIDE 100%	TB	TB	TB	TB	A	A	A	A	A	A
HYPOCHLOROUS ACID	A	A	A	A	A	A	A	A	A	A
IODINE CRYSTALS/VAPOR	TC	TC	TC	TC	TB	TB	TB	TB	TB	TB
ISOPHORONE	C	C	C	C	B	B	B	B	B	B
ISOPROPYL ACETATE	C	C	C	C	B	B	B	B	B	B
ISOPROPYL ALCOHOL	C	C	C	C	B	B	B	B	B	B
JET FUEL (JP-4)	C	C	B	B	A	A	A	A	A	A
KEROSENE	C	C	C	C	B	B	B	B	B	B
LACTIC ACID 10-20%	C	C	C	C	B	B	B	B	B	B
LACTIC ACID 50%	A	A	A	A	A	A	A	A	A	A
LACTIC ACID 85%	A	A	A	A	A	A	A	A	A	A
LAURIC ACID	TB	TB	A	A	A	A	A	A	A	A
LEAD ACETATE	TC	TC	TC	TC	TC	TC	TC	TC	TC	TC

This data is provided as a service of Applied Polymer Solutions and is believed to be accurate. However this information is neither recommendations by APS nor product specifications. APS reserves the right to change or modify data as necessary.

CHEMICAL RESISTANCE CHART

	RR 2429	RR 2429 V	RR 2601	RR 2602	ST 3015 AM	ST 3103	ST 3105	ST 3105V	ST 3145	ST 3145 c
LEVULINIC ACID	TC	TC	TC	TC	TB	TB	TB	TB	TB	TB
LINSEED OIL	C	C	B	B	B	B	B	B	B	B
LITHIUM BROMIDE	TB	TB	TB	TB	TB	TB	TB	TB	TB	TB
LITHIUM CHLORIDE SAT'D	B	B	B	B	A	A	A	A	A	A
LITHIUM HYDROXIDE	TB	TB	A	A	A	A	A	A	A	A
MAGNESIUM BISULFITE	C	C	B	B	B	B	B	B	B	B
MAGNESIUM CARBONATE	C	C	C	C	B	B	B	B	B	B
MAGNESIUM CHLORIDE	TB	TB	TB	TB	TB	TB	TB	TB	TB	TB
MAGNESIUM HYDROXIDE	B	B	B	B	B	B	B	B	B	B
MAGNESIUM NITRATE	TB	TB	TB	TB	TB	TB	TB	TB	TB	TB
MAGNESIUM SULFATE	TB	TB	TB	TB	TB	TB	TB	TB	TB	TB
MALEIC ACID	B	B	A	A	A	A	A	A	A	A
MANGANESE CHLORIDE	TB	TB	TB	TB	TB	TB	TB	TB	TB	TB
MANGANESE SULFATE	TB	TB	TB	TB	TB	TB	TB	TB	TB	TB
MERCURIC CHLORIDE	TC	TC	TB	TB	TB	TB	TB	TB	TB	TB
MERCUROUS CHLORIDE	TC	TC	TC	TC	TB	TB	TB	TB	TB	TB
METHANOL	B	B	A	A	A	A	A	A	A	A
METHYL ACETATE	B	B	A	A	A	A	A	A	A	A
METHYLAMYL ALCOHOL	TC	TC	TC	TC	TB	TB	TB	TB	TB	TB
METHYL BENZOATE	C	C	B	B	A	A	A	A	A	A
METHYL CHLORIDE	A	A	A	A	A	A	A	A	A	A
METHYLENE CHLORIDE	A	A	A	A	A	A	A	A	A	A
METHYL ETHYL KETONE	A	A	A	A	A	A	A	A	A	A
METHYL ISOBUTYL KETONE	B	B	B	B	A	A	A	A	A	A
MILK	D	D	D	D	C	C	C	C	C	C
MOLASSES	D	D	D	D	C	C	C	C	C	C
MINERAL OILS	TD	TD	TC	TC	TB	TB	TB	TB	TB	TB
MINERAL SPIRITS	C	C	B	B	B	B	B	B	B	B
MOTOR OIL	C	C	C	C	C	C	C	C	C	C
M-PYROL	A	A	A	A	A	A	A	A	A	A
NAPHTHA ALIPHATIC	C	C	B	B	B	B	B	B	B	B

This data is provided as a service of Applied Polymer Solutions and is believed to be accurate. However this information is neither recommendations by APS nor product specifications. APS reserves the right to change or modify data as necessary.

CHEMICAL RESISTANCE CHART

	RR 2429	RR 2429 V	RR 2601	RR 2602	ST 3015 AM	ST 3103	ST 3105	ST 3105V	ST 3145	ST 3145 c
NAPHTHA AROMATIC	B	B	B	B	A	A	A	A	A	A
NICKEL CHLORIDE	TB	TB	A	A	A	A	A	A	A	A
NICKEL NITRATE	C	C	B	B	B	B	B	B	B	B
NICKEL SULFATE	TC	TC	TB	TB	TB	TB	TB	TB	TB	TB
NITRIC ACID 5%	D	D	B	B	B	B	B	B	B	B
NITRIC ACID 30%	C	C	A	A	A	A	A	A	A	A
NITRIC ACID 60%	A	A	A	A	A	A	A	A	A	A
NITROBENZENE	TB	TB	A	A	A	A	A	A	A	A
OIL SOUR CRUDE	C	C	C	C	B	B	B	B	B	B
OIL SWEET CRUDE	TC	TC	TC	TC	TB	TB	TB	TB	TB	TB
OLEIC ACID	B	B	A	A	A	A	A	A	A	A
OLEUM	A	A	A	A	A	A	A	A	A	A
OXALIC ACID	B	B	A	A	A	A	A	A	A	A
PERCHLORIC ACID	A	A	A	A	A	A	A	A	A	A
PERCHLOROETHYLENE	B	B	B	B	A	A	A	A	A	A
PHENOL 5%	A	A	A	A	A	A	A	A	A	A
PHENOL 85%	A	A	A	A	A	A	A	A	A	A
PHOSPHORIC ACID 40%	C	C	A	A	B	B	B	B	A	A
PHOSPHORIC ACID 85%	A	A	A	A	A	A	A	A	A	A
PICRIC ACID 10%	TB	TB	TB	TB	A	A	A	A	A	A
POTASSIUM ACETATE	D	D	C	C	B	B	B	B	B	B
POTASSIUM BROMIDE	D	D	C	C	B	B	B	B	B	B
POTASSIUM CARBONATE	D	D	C	C	B	B	B	B	B	B
POTASSIUM CHLORIDE	D	D	B	B	B	B	B	B	B	B
POTASSIUM HYDROXIDE 10%	D	D	C	C	B	B	B	B	B	B
POTASSIUM HYDROXIDE 50%	C	C	B	B	A	A	A	A	A	A
POTASSIUM IODIDE	TB	TB	TB	TB	TB	TB	TB	TB	TB	TB
POTASSIUM NITRATE	D	D	C	C	B	B	B	B	B	B
POTASSIUM PERMANGANATE	TB	TB	TB	TB	A	A	A	A	A	A
POTASSIUM PERSULFATE	C	C	B	B	A	A	A	A	A	A
POTASSIUM SULFATE	C	C	C	C	B	B	B	B	B	B

This data is provided as a service of Applied Polymer Solutions and is believed to be accurate. However this information is neither recommendations by APS nor product specifications. APS reserves the right to change or modify data as necessary.

CHEMICAL RESISTANCE CHART

	RR 2429	RR 2429 V	RR 2601	RR 2602	ST 3015 AM	ST 3103	ST 3105	ST 3105V	ST 3145	ST 3145 c
PROPIONIC ACID	A	A	A	A	A	A	A	A	A	A
PROPYLENE GLYCOL	D	D	D	D	C	C	C	C	C	C
PYRIDINE	A	A	A	A	A	A	A	A	A	A
SALICYLIC ACID	TB	TB	TB	TB	TB	TB	TB	TB	TB	TB
SALT BRINE	D	D	C	C	C	C	C	C	C	C
SILVER NITRATE	TB	TB	A	A	A	A	A	A	A	A
SKYDROL	C	C	B	B	B	B	B	B	B	B
SODIUM ACETATE	D	D	C	C	C	C	C	C	C	C
SODIUM BENZOATE	D	D	C	C	C	C	C	C	C	C
SODIUM BICARBONATE	D	D	C	C	C	C	C	C	C	C
SODIUM BISULFITE	TD	TD	TD	TD	TC	TC	TC	TC	TC	TC
SODIUM BISULFATE	D	D	C	C	B	B	B	B	B	B
SODIUM CARBONATE	D	D	C	C	B	B	B	B	B	B
SODIUM CHLORATE 50%	TB	TB	TB	TB	A	A	A	A	A	A
SODIUM CHLORIDE	C	C	B	B	B	B	B	B	B	B
SODIUM CHLORITE	B	B	A	A	A	A	A	A	A	A
SODIUM CHROMATE	B	B	B	B	A	A	A	A	A	A
SODIUM DICHROMATE	B	B	B	B	B	B	B	B	B	B
SODIUM FERROCYANIDE	TC	TC	TB	TB	TB	TB	TB	TB	TB	TB
SODIUM FLUORIDE	A	A	A	A	A	A	A	A	A	A
SODIUM HYDROXIDE 10%	D	D	D	D	C	C	C	C	E	E
SODIUM HYDROXIDE 50%	D	D	C	C	B	B	B	B	D	D
SODIUM HYPOCHLORITE 3%	B	B	A	A	A	A	A	A	A	A
SODIUM HYPOCHLORITE 5-15%	A	A	A	A	A	A	A	A	A	A
SODIUM OXALATE	D	D	C	C	B	B	B	B	B	B
SODIUM PEROXIDE	C	C	B	B	B	B	B	B	B	B
SODIUM PHOSPHATE 10%	C	C	B	B	B	B	B	B	B	B
SODIUM SILICATE	TC	TC	TC	TC	TB	TB	TB	TB	TB	TB
SODIUM SULFATE	D	D	C	C	B	B	B	B	B	B
SODIUM SULFIDE	D	D	C	C	B	B	B	B	B	B
SODIUM SULFITE	D	D	C	C	B	B	B	B	B	B

This data is provided as a service of Applied Polymer Solutions and is believed to be accurate. However this information is neither recommendations by APS nor product specifications. APS reserves the right to change or modify data as necessary.

CHEMICAL RESISTANCE CHART

	RR 2429	RR 2429 V	RR 2601	RR 2602	ST 3015 AM	ST 3103	ST 3105	ST 3105V	ST 3145	ST 3145 c
SODIUM TARTRATE	D	D	C	C	B	B	B	B	B	B
SODIUM THIOSULFATE	C	C	C	C	B	B	B	B	B	B
STEARIC ACID	B	B	B	B	A	A	A	A	A	A
STYRENE	B	B	B	B	A	A	A	A	A	A
SULFAMIC ACID 25%	A	A	A	A	A	A	A	A	A	A
SULFURIC ACID 10%	D	D	C	C	B	B	B	B	C	C
SULFURIC ACID 30%	C	C	A	A	A	A	A	A	B	B
SULFURIC ACID 98%	B	B	A	A	A	A	A	A	A	A
TALL OIL	C	C	C	C	B	B	B	B	B	B
TARTARIC ACID	TB	TB	TB	TB	TB	TB	TB	TB	TB	TB
TETROCHLOROETHANE	B	B	A	A	A	A	A	A	A	A
TETRAHYDROFURAN	A	A	A	A	A	A	A	A	A	A
THIONYL CHLORIDE	A	A	A	A	A	A	A	A	A	A
TOLUENE	C	C	B	B	B	B	B	B	B	B
TOLUENE SULFONIC ACID	B	B	B	B	B	B	B	B	B	B
TOLUIDENE	B	B	B	B	A	A	A	A	A	A
TRICHLOROACETIC ACID 20%	A	A	A	A	A	A	A	A	A	A
TRICHLOROETHANE	C	C	C	C	B	B	B	B	A	A
TRICHLOROETHYLENE	TB	TB	A	A	A	A	A	A	A	A
TRICESYL PHOSPHATE	TB	TB	TB	TB	TB	TB	TB	TB	TB	TB
TRISODIUM PHOSPHATE	C	C	C	C	B	B	B	B	B	B
TURPENTINE	C	C	B	B	B	B	B	B	B	B
UREA SOLUTIONS	TC	TC	TC	TC	TB	TB	TB	TB	TB	TB
WHITE LIQUOR (PAPER)	TB	TB	TB	TB	TB	TB	TB	TB	TB	TB
XYLENE	D	D	C	C	B	B	B	B	B	B
ZINC CHLORATE	TC	TC	TB	TB	A	A	A	A	A	A
ZINC SULFATE	D	D	C	C	B	B	B	B	B	B

This data is provided as a service of Applied Polymer Solutions and is believed to be accurate. However this information is neither recommendations by APS nor product specifications. APS reserves the right to change or modify data as necessary.

CHEMICAL RESISTANCE CHART

	ST 3146	ST 3146 SP	ST 3246 AM	ST 3300	ST 3315	ST 3320	ST 3320 AM	ST 3320 HWS
ACETALDEHYDE	B	B	B	A	C	C	C	C
ACETIC ACID 5%	A	A	A	A	C	B	C	B
ACETIC ACID 10%	A	A	A	A	B	B	B	B
ACETIC ACID 25%	A	A	A	A	A	A	A	A
ACETIC ACID GLACIAL	A	A	A	A	A	A	A	A
ACETIC ANHYDRIDE	A	A	A	A	C	C	C	C
ACETONE 10%	B	B	B	A	B	B	B	B
ACETONE 100%	B	B	B	A	B	B	B	B
ACETYL CHLORIDE	A	A	A	A	TB	TB	TB	TB
ACETONITRILE	B	B	B	A	C	C	C	C
ACRYLIC ACID	A	A	A	A	TB	TB	TB	TB
ACRYLONITRILE	A	A	A	A	A	A	A	A
ADIPIIC ACID 25%	B	B	B	A	B	B	B	B
ALLYL ALCOHOL	TB	TB	TB	A	TC	TC	TC	TC
ALLYL CHLORIDE	A	A	A	A	TB	TB	TB	TB
ALUMINUM BROMIDE	C	C	C	B	D	D	D	D
ALUMINUM CHLORIDE	TC	TC	TC	B	TD	TD	TD	TD
ALUMINUM FLUORIDE	TC	TC	TC	B	TB	TB	TB	TB
ALUMINUM HYDROXIDE	C	C	C	B	C	C	C	C
ALUMINUM NITRATE	C	C	C	B	C	C	C	C
ALUMINUM SULFATE	B	B	B	A	C	C	C	C
AMMONIA	C	C	C	B	D	D	D	D
AMMONIUM CHLORIDE	TB	TB	TB	A	TC	TC	TC	TC
AMMONIUM FLUORIDE	TB	TB	TB	A	TB	TB	TB	TB
AMMONIUM HYDROXIDE	TB	TB	TB	A	TC	TC	TC	TC
AMMONIUM NITRATE	C	C	C	B	D	D	D	D
AMMONIUM OXALATE	B	B	B	B	C	C	C	C
AMMONIUM NITRATE	TC	TC	TC	TB	TD	TD	TD	TD
AMMONIUM PERSULFATE	B	B	B	A	C	C	C	C
AMMONIUM PHOSPHATE	B	B	B	A	D	C	C	C
AMMONIUM SULFATE	B	B	B	B	D	C	C	C

This data is provided as a service of Applied Polymer Solutions and is believed to be accurate. However this information is neither recommendations by APS nor product specifications. APS reserves the right to change or modify data as necessary.

CHEMICAL RESISTANCE CHART

	ST 3146	ST 3146 SP	ST 3246 AM	ST 3300	ST 3315	ST 3320	ST 3320 AM	ST 3320 HWS
AMMONIUM SULFIDE	C	C	C	B	C	C	C	C
AMMONIUM SULFITE	C	C	C	B	C	C	C	C
AMYL ACETATE	TB	TB	TB	A	TB	TB	TB	TB
AMYL ALCOHOL	B	B	B	A	C	C	C	C
ANILINE	A	A	A	A	B	B	B	B
ANILINE HYDROCHLORIDE	A	A	A	A	B	B	B	B
ANTIMONY CHLORIDE	A	A	A	A	TB	TB	TB	TB
AQUA REGIA	A	A	A	A	A	A	A	A
ARSENOUS ACID	A	A	A	A	TB	TB	TB	TB
BARIUM ACETATE	A	A	A	A	C	C	C	C
BARIUM BROMIDE	B	B	B	A	B	B	B	B
BARIUM CARBONATE	B	B	B	A	B	B	B	B
BARIUM CHLORIDE	B	B	B	A	D	D	D	D
BARIUM HYDROXIDE	TB	TB	TB	A	TC	TC	TC	TC
BARIUM SULFATE	B	B	B	A	C	C	C	C
BARIUM SULFIDE	A	A	A	A	B	B	B	B
BENZYL CHLORIDE	A	A	A	A	TB	TB	TB	TB
BENZOIC ACID	B	B	B	A	B	B	B	B
BENZALDEHYDE	A	A	A	A	TB	TB	TB	TB
BENZENE	TB	TB	TB	A	TB	TB	TB	TB
BENZYL ALCOHOL	C	C	C	B	D	C	C	C
BLACK LIQUOR (PAPER)	TB	TB	TB	A	TC	TC	TC	TC
BLOOD SUGAR	TB	TB	TB	A	TD	TC	TC	TC
BORAX	B	B	B	A	D	C	C	C
BORIC ACID	A	A	A	A	B	B	B	B
BRINE	D	D	D	B	D	D	D	D
BROMINE LIQUID	A	A	A	A	A	A	A	A
BUTANOL	C	C	C	B	D	D	D	D
BUTYL ACETATE	B	B	B	A	C	C	C	C
BUTYL ACRYLATE	A	A	A	A	TB	TB	TB	TB

This data is provided as a service of Applied Polymer Solutions and is believed to be accurate. However this information is neither recommendations by APS nor product specifications. APS reserves the right to change or modify data as necessary.

CHEMICAL RESISTANCE CHART

	ST 3146	ST 3146 SP	ST 3246 AM	ST 3300	ST 3315	ST 3320	ST 3320 AM	ST 3320 HWS
BUTYL AMINE	A	A	A	A	TB	TB	TB	TB
BUTYL CARBITOL	TB	TB	TB	A	TC	TC	TC	TC
BUTYL CELLOSOLVE	B	B	B	A	C	B	B	B
BUTYL ETHER	B	B	B	A	B	B	B	B
BUTYRIC ACID	A	A	A	A	B	B	B	B
CALCIUM BISULFITE	C	C	C	B	D	D	D	D
CALCIUM BROMIDE	TB	TB	TB	A	TC	TC	TC	TC
CALCIUM CARBONATE	B	B	B	A	D	C	C	C
CALCIUM CHLORATE	B	B	B	A	C	C	C	C
CALCIUM CHLORIDE	C	C	C	B	D	D	D	D
CALCIUM HYDROXIDE	B	B	B	A	C	C	C	C
CALCIUM HYPOCHLORITE	A	A	A	A	TC	TC	TC	TC
CALCIUM NITRATE	C	C	C	B	D	D	D	D
CALCIUM SULFATE	B	B	B	A	C	C	C	C
CALCIUM SULFITE	B	B	B	A	D	C	C	C
CALCIUM DISULFIDE	A	A	A	A	C	B	B	B
CARBON TETRACHLORIDE	B	B	B	A	C	C	C	C
CASTOR OIL	B	B	B	B	D	D	D	D
CELLOSOLVE	TB	TB	TB	A	TD	TC	TC	TC
CELLOSOLVE ACETATE	B	B	B	A	TD	TC	C	TC
CHLOROACETIC ACID 25%	A	A	A	A	D	C	A	C
CHLOROACETIC ACID 50%	A	A	A	A	A	A	A	A
CHLOROBENZENE	B	B	B	A	A	A	B	A
CHLOROFORM	A	A	A	A	B	B	A	B
CHLOROPHENOL	A	A	A	A	A	A	A	A
CHLOROSULFONIC ACID	A	A	A	A	A	A	A	A
CHLOROTOLUENE	A	A	A	A	A	A	TB	A
CHROMIC ACID 10%	A	A	A	A	TB	TB	B	TB
CHROMIC ACID 40%	A	A	A	A	B	B	A	B
CHROMIC CHLORIDE	A	A	A	A	A	A	A	A
CITRIC ACID	B	B	B	A	A	A	D	A

This data is provided as a service of Applied Polymer Solutions and is believed to be accurate. However this information is neither recommendations by APS nor product specifications. APS reserves the right to change or modify data as necessary.

CHEMICAL RESISTANCE CHART

	ST 3146	ST 3146 SP	ST 3246 AM	ST 3300	ST 3315	ST 3320	ST 3320 AM	ST 3320 HWS
COPPER ACETATE	B	B	B	A	D	D	D	D
COPPER CHLORIDE	B	B	B	A	D	D	C	D
COPPER CYANIDE	TB	TB	TB	A	C	C	TC	C
COPPER NITRATE	TB	TB	TB	A	TC	TC	TC	TC
COPPER SULFATE	B	B	B	A	TC	TC	B	TC
CORN OIL	B	B	B	A	B	B	C	B
CORN STARCH SLURRY	B	B	B	B	C	C	E	C
CORN SUGAR	C	C	C	B	E	E	D	E
COTTONSEED OIL	B	B	B	A	D	D	C	D
CREOSOTE	B	B	B	A	D	C	C	C
CRESYLIC ACID	A	A	A	A	C	C	TB	C
CUMENE	B	B	B	A	TB	TB	B	TB
CUTTING OIL	B	B	B	A	B	B	C	B
CYCLOHEXANE	B	B	B	A	D	C	C	C
CYCLOHEXANONE	B	B	B	B	D	C	C	C
CYMENE	TB	TB	TB	A	C	C	TC	C
DETERGENTS ORGANIC	TC	TC	TC	TB	TC	TC	TC	TC
DETERGENTS SULFONATED	TC	TC	TC	TB	TD	TC	TC	TC
DEXTROSE	D	D	D	B	TD	TC	E	TC
DIBUTYL PHTHALATE	C	C	C	B	E	E	D	E
DICHLORACETIC ACID	A	A	A	A	D	D	TB	D
DICHLOROBENZENE	B	B	B	A	TB	TB	C	TB
DICHLOROETHANE	A	A	A	A	C	C	B	C
DIESEL FUEL	B	B	B	A	B	B	C	B
DIETHANOLAMINE	TB	TB	TB	A	C	C	TC	C
DIETHYL BENZENE	TB	TB	TB	A	TC	TC	TC	TC
DIETHYL KETONE	A	A	A	A	TB	TB	TB	TB
DIETHYLENE GLYCOL	B	B	B	A	C	C	C	C
DIETHYL ETHER	A	A	A	A	C	C	C	C
DIMETHYL ANILINE	A	A	A	A	TB	TB	TB	TB
DIMETHYL FORMAMIDE	A	A	A	A	A	A	A	A

This data is provided as a service of Applied Polymer Solutions and is believed to be accurate. However this information is neither recommendations by APS nor product specifications. APS reserves the right to change or modify data as necessary.

CHEMICAL RESISTANCE CHART

	ST 3146	ST 3146 SP	ST 3246 AM	ST 3300	ST 3315	ST 3320	ST 3320 AM	ST 3320 HWS
DIMETHYL SULFOXIDE	A	A	A	A	A	A	A	A
DINITRO BENZENE	A	A	A	A	TB	TB	TB	TB
DINITRO TOLUENE	A	A	A	A	TB	TB	TB	TB
EPICHLOROHYDRIN	A	A	A	A	B	B	B	B
ETHANOL	B	B	B	A	D	C	D	C
ETHANOLAMINE	A	A	A	A	C	C	C	C
ETHYL ACETATE	A	A	A	A	C	B	B	B
ETHYL ACRYLATE	A	A	A	A	C	B	B	B
ETHYLAMINE	A	A	A	A	TC	TB	TB	TB
ETHYL BENZENE	A	A	A	A	TB	TB	TB	TB
ETHYL BROMIDE	A	A	A	A	A	A	A	A
ETHYL CHLORIDE	A	A	A	A	A	A	A	A
ETHYL DICHLORIDE	A	A	A	A	A	A	A	A
ETHYLENE GLYCOL	C	C	C	B	D	D	D	D
ETHYL SULFATE	A	A	A	A	TB	TB	TB	TB
FATTY ACIDS	A	A	A	A	TC	TB	TB	TB
FERRIC CHLORIDE	C	C	C	B	E	E	E	E
FERRIC SULFATE	C	C	C	B	E	E	E	E
FERROUS NITRATE	B	B	B	A	C	C	C	C
FERROUS CHLORIDE	TB	TB	TB	A	TD	TD	TD	TD
FERROUS SULFATE	TB	TB	TB	TB	TD	TD	TD	TD
FLUOSILICIC ACID 10-25%	A	A	A	A	A	A	A	A
FORMALDEHYDE	B	B	B	A	B	B	B	B
FORMIC ACID 10%	A	A	A	A	C	C	C	C
FORMIC ACID 50%	A	A	A	A	A	A	A	A
FUEL OIL	B	B	B	A	D	C	C	C
FURFURAL ALCOHOL	A	A	A	A	TB	TB	TB	TB
GASOLINE AVIATION	B	B	B	A	D	D	D	D
GASOLINE DIESEL	B	B	B	A	D	C	D	C
GASOLINE JET FUEL	B	B	B	A	D	C	D	C
GASOLINE UNLEADED	B	B	B	A	D	D	D	D

This data is provided as a service of Applied Polymer Solutions and is believed to be accurate. However this information is neither recommendations by APS nor product specifications. APS reserves the right to change or modify data as necessary.

CHEMICAL RESISTANCE CHART

	ST 3146	ST 3146 SP	ST 3246 AM	ST 3300	ST 3315	ST 3320	ST 3320 AM	ST 3320 HWS
GLUCOSE	D	D	D	B	D	D	D	D
GLYCERINE	TC	TC	TC	TB	TD	TD	TD	TD
GLYCOLIC ACID 70%	A	A	A	A	A	A	A	A
GREEN LIQUOR (PAPER)	B	B	B	A	C	C	C	C
HEPTANE	C	C	C	B	D	D	D	D
HEXANE	C	C	C	B	D	D	D	D
HYDRAULIC FLUID	B	B	B	B	D	C	C	C
HYDRAZINE 35%	A	A	A	A	TC	TB	TB	TB
HYDRIODIC ACID 20%	A	A	A	A	C	C	C	C
HYDROBROMIC ACID 18%	A	A	A	A	A	A	A	A
HYDROBROMIC ACID 40%	A	A	A	A	A	A	A	A
HYDROBROMIC ACID 60%	A	A	A	A	A	A	A	A
HYDROCHLORIC ACID 10%	C	C	C	B	D	C	D	C
HYDROCHLORIC ACID 36%	B	B	B	B	C	B	C	B
HYDROFLUORIC ACID	A	A	A	A	A	A	A	A
HYDROGEN PEROXIDE 10%	A	A	A	A	C	C	C	C
HYDROGEN PEROXIDE 50%	A	A	A	A	A	A	A	A
HYDROGEN SULFIDE 5%	B	B	B	A	D	D	D	D
HYDROGEN SULFIDE 100%	A	A	A	A	TB	TB	TB	TB
HYPOCHLOROUS ACID	A	A	A	A	A	A	A	A
IODINE CRYSTALS/VAPOR	TB	TB	TB	A	TC	TC	TC	TC
ISOPHORONE	B	B	B	A	C	C	C	C
ISOPROPYL ACETATE	B	B	B	A	D	C	C	C
ISOPROPYL ALCOHOL	B	B	B	A	C	C	C	C
JET FUEL (JP-4)	A	A	A	A	D	C	D	C
KEROSENE	B	B	B	A	C	C	C	C
LACTIC ACID 10-20%	B	B	B	A	D	D	D	D
LACTIC ACID 50%	A	A	A	A	A	A	A	A
LACTIC ACID 85%	A	A	A	A	A	A	A	A
LAURIC ACID	A	A	A	A	TB	TB	TB	TB
LEAD ACETATE	TC	TC	TC	TB	TD	TD	TD	TD

This data is provided as a service of Applied Polymer Solutions and is believed to be accurate. However this information is neither recommendations by APS nor product specifications. APS reserves the right to change or modify data as necessary.

CHEMICAL RESISTANCE CHART

	ST 3146	ST 3146 SP	ST 3246 AM	ST 3300	ST 3315	ST 3320	ST 3320 AM	ST 3320 HWS
LEVULINIC ACID	TB	TB	TB	A	TC	TC	TC	TC
LINSEED OIL	B	B	B	A	D	C	C	C
LITHIUM BROMIDE	TB	TB	TB	A	TB	TB	TB	TB
LITHIUM CHLORIDE SAT'D	A	A	A	A	B	B	B	B
LITHIUM HYDROXIDE	A	A	A	A	TB	TB	TB	TB
MAGNESIUM BISULFITE	B	B	B	A	D	C	C	C
MAGNESIUM CARBONATE	B	B	B	A	D	C	C	C
MAGNESIUM CHLORIDE	TB	TB	TB	A	TB	TB	TB	TB
MAGNESIUM HYDROXIDE	B	B	B	A	C	B	B	B
MAGNESIUM NITRATE	TB	TB	TB	A	TC	TC	TC	TC
MAGNESIUM SULFATE	TB	TB	TB	A	TB	TB	TB	TB
MALEIC ACID	A	A	A	A	C	B	B	B
MANGANESE CHLORIDE	TB	TB	TB	A	TB	TB	TB	TB
MANGANESE SULFATE	TB	TB	TB	A	TB	TB	TB	TB
MERCURIC CHLORIDE	TB	TB	TB	A	TC	TC	TC	TC
MERCUROUS CHLORIDE	TB	TB	TB	A	TC	TC	TC	TC
METHANOL	A	A	A	A	B	B	B	B
METHYL ACETATE	A	A	A	A	C	B	B	B
METHYLAMYL ALCOHOL	TB	TB	TB	A	TC	TC	TC	TC
METHYL BENZOATE	A	A	A	A	B	B	B	B
METHYL CHLORIDE	A	A	A	A	A	A	A	A
METHYLENE CHLORIDE	A	A	A	A	A	A	A	A
METHYL ETHYL KETONE	A	A	B	A	B	A	B	A
METHYL ISOBUTYL KETONE	A	A	A	A	B	B	B	B
MILK	C	C	C	B	D	D	D	D
MOLASSES	C	C	C	B	D	D	D	D
MINERAL OILS	TB	TB	TB	A	TD	TD	TD	TD
MINERAL SPIRITS	B	B	B	A	D	C	C	C
MOTOR OIL	C	C	C	B	D	C	C	C
M-PYROL	A	A	A	A	A	A	A	A
NAPHTHA ALIPHATIC	B	B	B	A	D	C	C	C

This data is provided as a service of Applied Polymer Solutions and is believed to be accurate. However this information is neither recommendations by APS nor product specifications. APS reserves the right to change or modify data as necessary.

CHEMICAL RESISTANCE CHART

	ST 3146	ST 3146 SP	ST 3246 AM	ST 3300	ST 3315	ST 3320	ST 3320 AM	ST 3320 HWS
NAPHTHA AROMATIC	A	A	A	A	D	C	B	C
NICKEL CHLORIDE	A	A	A	A	TB	TB	TB	TB
NICKEL NITRATE	B	B	B	A	D	C	C	C
NICKEL SULFATE	TB	TB	TB	A	TB	TB	TB	TB
NITRIC ACID 5%	B	B	B	A	D	C	D	C
NITRIC ACID 30%	A	A	A	A	C	B	C	B
NITRIC ACID 60%	A	A	A	A	A	A	A	A
NITROBENZENE	A	A	A	A	TB	TB	TB	TB
OIL SOUR CRUDE	B	B	B	A	D	C	C	C
OIL SWEET CRUDE	TB	TB	TB	A	TD	TC	TC	TC
OLEIC ACID	A	A	A	A	B	B	B	B
OLEUM	A	A	A	A	A	A	A	A
OXALIC ACID	A	A	A	A	B	B	B	B
PERCHLORIC ACID	A	A	A	A	A	A	A	A
PERCHLOROETHYLENE	A	A	A	A	B	B	B	B
PHENOL 5%	A	A	A	A	C	B	B	B
PHENOL 85%	A	A	A	A	A	A	A	A
PHOSPHORIC ACID 40%	A	A	A	B	D	C	D	C
PHOSPHORIC ACID 85%	A	A	A	A	B	B	B	B
PICRIC ACID 10%	A	A	A	A	TB	TB	TB	TB
POTASSIUM ACETATE	B	B	B	A	C	C	C	C
POTASSIUM BROMIDE	B	B	B	A	D	D	D	D
POTASSIUM CARBONATE	B	B	B	A	D	D	D	D
POTASSIUM CHLORIDE	B	B	B	A	C	C	C	C
POTASSIUM HYDROXIDE 10%	B	B	B	A	D	D	D	D
POTASSIUM HYDROXIDE 50%	A	A	A	A	D	C	C	C
POTASSIUM IODIDE	TB	TB	TB	A	TB	TB	TB	TB
POTASSIUM NITRATE	B	B	B	A	D	D	D	D
POTASSIUM PERMANGANATE	A	A	A	A	TB	TB	TB	TB
POTASSIUM PERSULFATE	A	A	A	A	C	B	B	B
POTASSIUM SULFATE	B	B	B	A	D	C	C	C

This data is provided as a service of Applied Polymer Solutions and is believed to be accurate. However this information is neither recommendations by APS nor product specifications. APS reserves the right to change or modify data as necessary.

CHEMICAL RESISTANCE CHART

	ST 3146	ST 3146 SP	ST 3246 AM	ST 3300	ST 3315	ST 3320	ST 3320 AM	ST 3320 HWS
PROPIONIC ACID	A	A	A	A	B	A	A	A
PROPYLENE GLYCOL	C	C	C	B	D	D	D	D
PYRIDINE	A	A	A	A	A	A	A	A
SALICYLIC ACID	TB	TB	TB	A	TC	TB	TB	TB
SALT BRINE	C	C	C	B	D	D	D	D
SILVER NITRATE	A	A	A	A	TB	TB	TB	TB
SKYDROL	B	B	B	A	D	C	D	C
SODIUM ACETATE	C	C	C	B	D	D	D	D
SODIUM BENZOATE	C	C	C	B	D	D	D	D
SODIUM BICARBONATE	C	C	C	B	D	D	D	D
SODIUM BISULFITE	TC	TC	TC	TB	TD	TD	TD	TD
SODIUM BISULFATE	B	B	B	A	D	D	D	D
SODIUM CARBONATE	B	B	B	A	D	D	D	D
SODIUM CHLORATE 50%	A	A	A	A	TC	TC	TC	TC
SODIUM CHLORIDE	B	B	B	A	C	C	C	C
SODIUM CHLORITE	A	A	A	A	C	C	C	C
SODIUM CHROMATE	A	A	A	A	B	B	B	B
SODIUM DICHROMATE	B	B	B	A	B	B	B	B
SODIUM FERROCYANIDE	TB	TB	TB	A	TC	TC	TC	TC
SODIUM FLUORIDE	A	A	A	A	A	A	A	A
SODIUM HYDROXIDE 10%	E	E	E	B	E	E	E	E
SODIUM HYDROXIDE 50%	D	D	D	B	D	D	D	D
SODIUM HYPOCHLORITE 3%	A	A	A	A	C	B	B	B
SODIUM HYPOCHLORITE 5-15%	A	A	A	A	A	A	A	A
SODIUM OXALATE	B	B	B	A	D	D	D	D
SODIUM PEROXIDE	B	B	B	A	C	C	C	C
SODIUM PHOSPHATE 10%	B	B	B	A	C	C	C	C
SODIUM SILICATE	TB	TB	TB	A	TC	TC	TC	TC
SODIUM SULFATE	B	B	B	A	D	D	D	D
SODIUM SULFIDE	B	B	B	A	D	D	D	D
SODIUM SULFITE	B	B	B	A	D	D	D	D

This data is provided as a service of Applied Polymer Solutions and is believed to be accurate. However this information is neither recommendations by APS nor product specifications. APS reserves the right to change or modify data as necessary.

CHEMICAL RESISTANCE CHART

	ST 3146	ST 3146 SP	ST 3246 AM	ST 3300	ST 3315	ST 3320	ST 3320 AM	ST 3320 HWS
SODIUM TARTRATE	B	B	B	A	D	D	D	D
SODIUM THIOSULFATE	B	B	B	A	C	C	C	C
STEARIC ACID	A	A	A	A	B	B	B	B
STYRENE	A	A	A	A	B	B	B	B
SULFAMIC ACID 25%	A	A	A	A	TB	TB	TB	TB
SULFURIC ACID 10%	C	C	C	B	D	D	D	D
SULFURIC ACID 30%	B	B	B	A	C	C	C	C
SULFURIC ACID 98%	A	A	A	A	A	A	A	A
TALL OIL	B	B	B	A	D	C	C	C
TARTARIC ACID	TB	TB	TB	A	TB	TB	TB	TB
TETROCHLOROETHANE	A	A	A	A	B	B	B	B
TETRAHYDROFURAN	A	A	A	A	A	A	A	A
THIONYL CHLORIDE	A	A	A	A	A	A	A	A
TOLUENE	B	B	B	A	D	C	C	C
TOLUENE SULFONIC ACID	B	B	B	A	C	B	B	B
TOLUIDENE	A	A	A	A	B	B	B	B
TRICHLOROACETIC ACID 20%	A	A	A	A	A	A	A	A
TRICHLOROETHANE	A	A	A	A	C	C	C	C
TRICHLOROETHYLENE	A	A	A	A	TB	TB	TB	TB
TRICESYL PHOSPHATE	TB	TB	TB	A	TC	TB	TB	TB
TRISODIUM PHOSPHATE	B	B	B	A	D	C	C	C
TURPENTINE	B	B	B	A	D	C	C	C
UREA SOLUTIONS	TB	TB	TB	A	TD	TC	TC	TC
WHITE LIQUOR (PAPER)	TB	TB	TB	A	TC	TC	TC	TC
XYLENE	B	B	B	A	E	D	E	D
ZINC CHLORATE	A	A	A	A	TC	TC	TC	TC
ZINC SULFATE	B	B	B	A	D	C	C	C

This data is provided as a service of Applied Polymer Solutions and is believed to be accurate. However this information is neither recommendations by APS nor product specifications. APS reserves the right to change or modify data as necessary.

CHEMICAL RESISTANCE CHART

	ST 3324 C	ST 3350	ST 3407	ST 3408	ST 3710	ST 3720	ST 4002	ST 4009	ST 4009 AM	ST 4033
ACETALDEHYDE	C	C	D	D	B	C	B	B	B	C
ACETIC ACID 5%	B	C	D	D	B	B	B	A	A	B
ACETIC ACID 10%	B	B	B	B	A	A	A	A	A	A
ACETIC ACID 25%	A	A	B	B	A	A	A	A	A	A
ACETIC ACID GLACIAL	A	A	A	A	A	A	A	A	A	A
ACETIC ANHYDRIDE	C	C	D	D	A	B	A	A	A	B
ACETONE 10%	B	B	C	C	B	C	C	A	A	B
ACETONE 100%	B	B	C	C	A	C	B	A	A	A
ACETYL CHLORIDE	TB	TB	TC	TC	A	A	A	A	A	A
ACETONITRILE	C	C	D	D	B	B	B	B	B	B
ACRYLIC ACID	TB	TB	TD	TD	A	TB	A	A	A	TB
ACRYLONITRILE	A	A	TB	TB	A	TB	A	A	A	TB
ADIPIIC ACID 25%	B	B	C	C	B	B	B	A	A	B
ALLYL ALCOHOL	TC	TC	TD	TD	TB	TC	TB	A	A	TC
ALLYL CHLORIDE	TB	TB	TC	TC	A	TB	A	A	A	TB
ALUMINUM BROMIDE	D	D	D	D	C	D	C	B	B	TD
ALUMINUM CHLORIDE	TD	TD	TD	TD	TC	TC	TB	A	A	TC
ALUMINUM FLUORIDE	TB	TB	TD	TD	TC	TC	TB	A	A	TC
ALUMINUM HYDROXIDE	C	C	D	D	C	C	C	B	B	C
ALUMINUM NITRATE	C	C	E	E	C	D	C	B	B	TD
ALUMINUM SULFATE	C	C	D	D	B	C	B	B	B	C
AMMONIA	D	D	E	E	C	D	C	B	B	TD
AMMONIUM CHLORIDE	TC	TC	TD	TD	TB	TC	TB	A	A	TC
AMMONIUM FLUORIDE	TB	TB	TC	TC	TB	TB	TB	A	A	TB
AMMONIUM HYDROXIDE	TC	TC	TD	TD	TB	TC	TC	TB	TB	TC
AMMONIUM NITRATE	D	D	E	E	C	D	C	B	B	TD
AMMONIUM OXALATE	C	C	D	D	C	C	B	B	B	C
AMMONIUM NITRATE	TD	TD	TE	TE	TC	TD	TC	TB	TB	TD
AMMONIUM PERSULFATE	C	C	D	D	B	C	B	B	B	C
AMMONIUM PHOSPHATE	C	C	D	D	B	C	B	B	B	C
AMMONIUM SULFATE	C	C	D	D	C	D	B	B	B	TD

This data is provided as a service of Applied Polymer Solutions and is believed to be accurate. However this information is neither recommendations by APS nor product specifications. APS reserves the right to change or modify data as necessary.

CHEMICAL RESISTANCE CHART

	ST 3324 C	ST 3350	ST 3407	ST 3408	ST 3710	ST 3720	ST 4002	ST 4009	ST 4009 AM	ST 4033
AMMONIUM SULFIDE	C	C	E	E	C	D	C	B	B	TD
AMMONIUM SULFITE	C	C	E	E	C	D	C	B	B	TD
AMYL ACETATE	TB	TB	TD	TD	TB	TC	TB	A	A	TC
AMYL ALCOHOL	C	C	D	D	B	C	B	A	A	TC
ANILINE	B	B	C	C	A	B	A	A	A	B
ANILINE HYDROCHLORIDE	B	B	C	C	A	B	A	A	A	B
ANTIMONY CHLORIDE	TB	TB	TC	TC	A	TB	A	A	A	TB
AQUA REGIA	A	A	A	A	A	A	A	A	A	A
ARSENOUS ACID	TB	TB	TC	TC	A	TB	A	A	A	TB
BARIUM ACETATE	C	C	D	D	B	C	B	B	B	C
BARIUM BROMIDE	B	B	D	D	B	C	B	B	B	C
BARIUM CARBONATE	B	B	D	D	B	C	B	A	A	TC
BARIUM CHLORIDE	D	D	D	D	B	C	B	B	B	B
BARIUM HYDROXIDE	TC	TC	TD	TD	TB	TC	TB	A	A	TC
BARIUM SULFATE	C	C	D	D	B	C	B	B	B	C
BARIUM SULFIDE	B	B	C	C	A	C	A	B	B	TC
BENZYL CHLORIDE	TB	TB	TC	TC	A	TB	A	A	A	TB
BENZOIC ACID	B	B	C	C	B	C	B	B	B	C
BENZALDEHYDE	TB	TB	TC	TC	A	TB	A	TB	TB	TB
BENZENE	TB	TB	TC	TC	TB	TC	TB	TB	TB	TB
BENZYL ALCOHOL	C	C	E	E	C	D	C	A	A	C
BLACK LIQUOR (PAPER)	TC	TC	TD	TD	TB	TC	TB	A	A	TB
BLOOD SUGAR	TC	TC	TD	TD	TB	TC	TB	TB	TB	TC
BORAX	C	C	D	D	B	C	B	B	B	C
BORIC ACID	B	B	C	C	A	C	A	B	B	TC
BRINE	D	D	E	E	D	D	D	C	C	D
BROMINE LIQUID	A	A	A	A	A	A	A	A	A	A
BUTANOL	D	D	E	E	C	D	C	A	A	C
BUTYL ACETATE	C	C	D	D	B	C	B	B	B	C
BUTYL ACRYLATE	TB	TB	TC	TC	A	TB	A	A	A	TB

This data is provided as a service of Applied Polymer Solutions and is believed to be accurate. However this information is neither recommendations by APS nor product specifications. APS reserves the right to change or modify data as necessary.

CHEMICAL RESISTANCE CHART

	ST 3324 C	ST 3350	ST 3407	ST 3408	ST 3710	ST 3720	ST 4002	ST 4009	ST 4009 AM	ST 4033
BUTYL AMINE	TB	TB	TC	TC	A	TB	TB	TB	TB	TB
BUTYL CARBITOL	TC	TC	TD	TD	TB	TC	A	TB	TB	TC
BUTYL CELLOSOLVE	B	B	C	C	B	C	B	A	A	C
BUTYL ETHER	B	B	D	D	B	C	B	B	B	C
BUTYRIC ACID	B	B	B	B	A	A	A	A	A	A
CALCIUM BISULFITE	D	D	E	E	C	D	C	B	B	D
CALCIUM BROMIDE	TC	TC	TD	TD	TD	TC	TB	A	A	TC
CALCIUM CARBONATE	C	C	D	D	B	C	B	B	B	C
CALCIUM CHLORATE	C	C	D	D	B	C	B	B	B	TC
CALCIUM CHLORIDE	D	D	E	E	C	D	C	B	B	TD
CALCIUM HYDROXIDE	C	C	E	E	B	D	B	B	B	TD
CALCIUM HYPOCHLORITE	TC	TC	TC	TC	A	TB	A	A	A	TB
CALCIUM NITRATE	D	D	E	E	C	D	C	B	B	TD
CALCIUM SULFATE	C	C	C	C	B	C	B	B	B	C
CALCIUM SULFITE	C	C	C	C	B	C	B	B	B	C
CALCIUM DISULFIDE	B	B	B	B	A	B	A	A	A	B
CARBON TETRACHLORIDE	C	C	D	D	B	C	B	A	A	C
CASTOR OIL	D	D	D	D	B	C	B	B	B	C
CELLOSOLVE	TC	TC	TD	TD	TB	TC	TB	A	A	TC
CELLOSOLVE ACETATE	TC	C	C	C	B	C	B	A	A	C
CHLOROACETIC ACID 25%	C	A	C	C	A	B	A	A	A	B
CHLOROACETIC ACID 50%	A	A	A	A	A	A	A	A	A	A
CHLOROBENZENE	A	B	D	D	B	C	B	A	A	B
CHLOROFORM	B	A	TC	TC	A	TB	A	A	A	TB
CHLOROPHENOL	A	A	A	A	A	A	A	A	A	A
CHLOROSULFONIC ACID	A	A	A	A	A	A	A	A	A	A
CHLOROTOLUENE	A	TB	TC	TC	A	TB	A	A	A	TB
CHROMIC ACID 10%	TB	B	C	C	A	A	A	A	A	TB
CHROMIC ACID 40%	B	A	B	B	A	A	A	A	A	A
CHROMIC CHLORIDE	A	A	B	B	A	A	A	A	A	A
CITRIC ACID	A	D	E	E	B	C	B	B	B	C

This data is provided as a service of Applied Polymer Solutions and is believed to be accurate. However this information is neither recommendations by APS nor product specifications. APS reserves the right to change or modify data as necessary.

CHEMICAL RESISTANCE CHART

	ST 3324 C	ST 3350	ST 3407	ST 3408	ST 3710	ST 3720	ST 4002	ST 4009	ST 4009 AM	ST 4033
COPPER ACETATE	D	D	E	E	B	C	B	B	B	C
COPPER CHLORIDE	D	C	D	D	B	B	A	A	A	C
COPPER CYANIDE	C	TC	TD	TD	TB	TC	TB	TB	TB	TC
COPPER NITRATE	TC	TC	TD	TD	TB	TC	TB	TB	TB	TC
COPPER SULFATE	TC	B	D	D	B	C	B	B	B	C
CORN OIL	B	C	D	D	B	C	B	B	B	C
CORN STARCH SLURRY	C	D	E	E	D	E	C	C	C	D
CORN SUGAR	E	D	E	E	C	D	C	C	C	D
COTTONSEED OIL	D	C	D	D	B	C	B	C	C	C
CREOSOTE	C	C	D	D	B	C	B	A	A	TC
CRESYLIC ACID	C	TB	TC	TC	A	TB	A	A	A	TB
CUMENE	TB	TB	D	D	B	C	B	A	A	C
CUTTING OIL	B	C	D	D	C	C	B	B	B	C
CYCLOHEXANE	C	C	E	E	B	C	B	A	A	C
CYCLOHEXANONE	C	C	E	E	C	C	B	A	A	C
CYMENE	C	TC	TD	TD	TB	TC	TB	TB	TB	TC
DETERGENTS ORGANIC	TC	TC	TD	TD	TC	TE	TC	TC	TC	TD
DETERGENTS SULFONATED	TC	TC	TD	TD	TC	TE	TC	TC	TC	TD
DEXTROSE	TC	TD	E	E	D	E	C	C	C	TD
DIBUTYL PHTHALATE	E	D	E	E	C	D	C	B	B	D
DICHLORACETIC ACID	D	TC	TB	TB	A	TC	A	A	A	TB
DICHLOROBENZENE	TB	TC	D	D	B	C	B	A	A	C
DICHLOROETHANE	C	B	C	C	A	A	A	A	A	A
DIESEL FUEL	B	B	D	D	B	C	B	A	A	C
DIETHANOLAMINE	C	TC	TD	TD	TB	TB	TB	A	A	TB
DIETHYL BENZENE	TC	TC	TD	TD	TB	TC	TB	A	A	TC
DIETHYL KETONE	TB	TB	TD	TD	A	TB	TB	A	A	TB
DIETHYLENE GLYCOL	C	C	E	E	B	C	B	B	B	C
DIETHYL ETHER	C	C	D	D	A	B	B	A	A	B
DIMETHYL ANILINE	TB	TB	TC	TC	A	TB	A	A	A	TB
DIMETHYL FORMAMIDE	A	A	A	A	A	A	A	A	A	A

This data is provided as a service of Applied Polymer Solutions and is believed to be accurate. However this information is neither recommendations by APS nor product specifications. APS reserves the right to change or modify data as necessary.

CHEMICAL RESISTANCE CHART

	ST 3324 C	ST 3350	ST 3407	ST 3408	ST 3710	ST 3720	ST 4002	ST 4009	ST 4009 AM	ST 4033
DIMETHYL SULFOXIDE	A	A	B	B	A	A	A	A	A	A
DINITRO BENZENE	TB	TB	TC	TC	A	TB	A	A	A	TB
DINITRO TOLUENE	TB	TB	TC	TC	A	TB	A	A	A	TB
EPICHLOROHYDRIN	B	B	C	C	B	B	A	B	B	B
ETHANOL	C	D	C	C	B	C	B	A	A	C
ETHANOLAMINE	C	C	D	D	A	B	B	A	A	B
ETHYL ACETATE	B	B	C	C	A	A	B	A	A	A
ETHYL ACRYLATE	B	B	C	C	A	A	A	A	A	A
ETHYLAMINE	TB	TB	TC	TC	A	A	A	A	A	A
ETHYL BENZENE	TB	TB	TD	TD	A	TB	A	A	A	TB
ETHYL BROMIDE	A	A	B	B	A	A	A	A	A	A
ETHYL CHLORIDE	A	A	B	B	A	A	A	A	A	A
ETHYL DICHLORIDE	A	A	TB	TB	A	A	A	A	A	A
ETHYLENE GLYCOL	D	D	E	E	C	D	C	B	B	D
ETHYL SULFATE	TB	TB	TD	TD	A	TB	TB	A	A	TB
FATTY ACIDS	TB	TB	TD	TD	TB	TB	TB	TB	TB	TB
FERRIC CHLORIDE	E	E	E	E	D	E	C	B	B	C
FERRIC SULFATE	E	E	E	E	C	E	C	B	B	D
FERROUS NITRATE	C	C	E	E	B	C	C	B	B	C
FERROUS CHLORIDE	TD	TD	TD	TD	TB	TD	TB	TB	TB	TC
FERROUS SULFATE	TD	TD	TE	TE	TC	TE	TB	TB	TB	TC
FLUOSILICIC ACID 10-25%	A	A	A	A	A	A	A	A	A	A
FORMALDEHYDE	B	B	D	D	B	C	B	B	B	C
FORMIC ACID 10%	C	C	D	D	A	B	A	B	B	B
FORMIC ACID 50%	A	A	B	B	A	A	A	A	A	A
FUEL OIL	C	C	E	E	B	C	B	A	A	C
FURFURAL ALCOHOL	TB	TB	TC	TC	A	TB	A	A	A	A
GASOLINE AVIATION	D	D	D	D	A	B	B	A	A	B
GASOLINE DIESEL	C	D	D	D	A	B	B	A	A	B
GASOLINE JET FUEL	C	D	D	D	A	B	B	A	A	B
GASOLINE UNLEADED	D	D	E	E	B	C	B	A	A	C

This data is provided as a service of Applied Polymer Solutions and is believed to be accurate. However this information is neither recommendations by APS nor product specifications. APS reserves the right to change or modify data as necessary.

CHEMICAL RESISTANCE CHART

	ST 3324 C	ST 3350	ST 3407	ST 3408	ST 3710	ST 3720	ST 4002	ST 4009	ST 4009 AM	ST 4033
GLUCOSE	D	D	E	E	D	E	D	TC	TC	E
GLYCERINE	TD	TD	TE	TE	TC	TD	TC	TB	TB	TD
GLYCOLIC ACID 70%	A	A	TB	TB	A	A	A	A	A	A
GREEN LIQUOR (PAPER)	C	C	E	E	B	C	B	A	A	C
HEPTANE	D	D	E	E	C	D	C	A	A	C
HEXANE	D	D	E	E	C	D	C	A	A	C
HYDRAULIC FLUID	C	C	E	E	B	C	B	B	B	TC
HYDRAZINE 35%	TB	TB	TC	TC	A	TB	A	A	A	TB
HYDRIODIC ACID 20%	C	C	D	D	A	C	A	A	A	B
HYDROBROMIC ACID 18%	A	A	C	C	A	A	A	A	A	A
HYDROBROMIC ACID 40%	A	A	TB	TB	A	A	A	A	A	A
HYDROBROMIC ACID 60%	A	A	TB	TB	A	A	A	A	A	A
HYDROCHLORIC ACID 10%	C	D	D	D	B	C	C	C	C	TC
HYDROCHLORIC ACID 36%	B	C	D	D	B	B	A	B	B	TB
HYDROFLUORIC ACID	A	A	A	A	A	A	A	A	A	A
HYDROGEN PEROXIDE 10%	C	C	C	C	A	B	A	A	A	B
HYDROGEN PEROXIDE 50%	A	A	A	A	A	A	A	A	A	A
HYDROGEN SULFIDE 5%	D	D	D	D	B	C	B	B	B	C
HYDROGEN SULFIDE 100%	TB	TB	TD	TD	A	TC	A	TB	TB	TC
HYPOCHLOROUS ACID	A	A	A	A	A	A	A	A	A	A
IODINE CRYSTALS/VAPOR	TC	TC	TD	TD	TB	TC	TB	TB	TB	TC
ISOPHORONE	C	C	E	E	B	C	B	B	B	C
ISOPROPYL ACETATE	C	C	E	E	B	C	B	B	B	C
ISOPROPYL ALCOHOL	C	C	E	E	B	C	B	A	A	C
JET FUEL (JP-4)	C	D	D	D	A	B	A	A	A	B
KEROSENE	C	C	D	D	B	C	B	A	A	C
LACTIC ACID 10-20%	D	D	D	D	B	C	B	B	B	C
LACTIC ACID 50%	A	A	C	C	A	A	A	A	A	A
LACTIC ACID 85%	A	A	A	A	A	A	A	A	A	A
LAURIC ACID	TB	TB	TD	TD	A	TB	A	A	A	TB
LEAD ACETATE	TD	TD	TE	TE	TC	TD	TC	TB	TB	TC

This data is provided as a service of Applied Polymer Solutions and is believed to be accurate. However this information is neither recommendations by APS nor product specifications. APS reserves the right to change or modify data as necessary.

CHEMICAL RESISTANCE CHART

	ST 3324 C	ST 3350	ST 3407	ST 3408	ST 3710	ST 3720	ST 4002	ST 4009	ST 4009 AM	ST 4033
LEVULINIC ACID	TC	TC	TD	TD	TB	TC	TB	TB	TB	TC
LINSEED OIL	C	C	D	D	B	B	B	B	B	B
LITHIUM BROMIDE	TB	TB	TD	TD	TB	TC	TB	TB	TB	TC
LITHIUM CHLORIDE SAT'D	B	B	D	D	A	B	A	A	A	B
LITHIUM HYDROXIDE	TB	TB	TC	TC	A	A	A	A	A	A
MAGNESIUM BISULFITE	C	C	D	D	B	B	B	B	B	B
MAGNESIUM CARBONATE	C	C	D	D	B	C	B	B	B	C
MAGNESIUM CHLORIDE	TB	TB	TC	TC	TB	TB	TB	TB	TB	TB
MAGNESIUM HYDROXIDE	B	B	C	C	B	B	B	B	B	B
MAGNESIUM NITRATE	TC	TC	TD	TD	TB	TB	TB	TB	TB	TB
MAGNESIUM SULFATE	TB	TB	TD	TD	TB	TB	TB	TB	TB	TB
MALEIC ACID	B	B	C	C	A	A	A	A	A	A
MANGANESE CHLORIDE	TB	TB	TD	TD	TB	TB	TB	A	A	TB
MANGANESE SULFATE	TB	TB	TD	TD	TB	TB	TB	TB	TB	TB
MERCURIC CHLORIDE	TC	TC	TE	TE	TB	TC	A	A	A	TB
MERCUROUS CHLORIDE	TC	TC	TE	TE	TB	TC	A	TB	TB	TC
METHANOL	B	B	C	C	A	A	A	A	A	A
METHYL ACETATE	B	B	C	C	A	A	A	A	A	A
METHYLAMYL ALCOHOL	TC	TC	TD	TD	TB	TC	TB	A	A	TC
METHYL BENZOATE	B	B	D	D	A	B	B	A	A	B
METHYL CHLORIDE	A	A	B	B	A	A	A	A	A	A
METHYLENE CHLORIDE	A	A	A	A	A	A	A	A	A	A
METHYL ETHYL KETONE	A	B	C	C	A	A	A	A	A	A
METHYL ISOBUTYL KETONE	B	B	D	D	A	B	B	A	A	B
MILK	D	D	E	E	C	D	D	C	C	D
MOLASSES	D	D	E	E	C	D	D	B	B	D
MINERAL OILS	TD	TD	TE	TE	TB	TC	TC	TB	TB	TC
MINERAL SPIRITS	C	C	D	D	B	B	B	B	B	TC
MOTOR OIL	C	C	D	D	C	C	C	C	C	C
M-PYROL	A	A	A	A	A	A	A	A	A	A
NAPHTHA ALIPHATIC	C	C	E	E	B	B	B	A	A	B

This data is provided as a service of Applied Polymer Solutions and is believed to be accurate. However this information is neither recommendations by APS nor product specifications. APS reserves the right to change or modify data as necessary.

CHEMICAL RESISTANCE CHART

	ST 3324 C	ST 3350	ST 3407	ST 3408	ST 3710	ST 3720	ST 4002	ST 4009	ST 4009 AM	ST 4033
NAPHTHA AROMATIC	C	B	D	D	A	B	A	A	A	B
NICKEL CHLORIDE	TB	TB	TC	TC	A	A	A	A	A	A
NICKEL NITRATE	C	C	D	D	B	B	B	A	A	B
NICKEL SULFATE	TB	TB	TD	TD	TB	TB	TB	A	A	TB
NITRIC ACID 5%	C	D	E	E	B	B	B	B	B	B
NITRIC ACID 30%	B	B	C	C	A	B	A	A	A	B
NITRIC ACID 60%	A	A	A	A	A	A	A	A	A	A
NITROBENZENE	TB	TB	TC	TC	A	A	A	A	A	A
OIL SOUR CRUDE	C	C	E	E	B	C	C	B	B	C
OIL SWEET CRUDE	TC	TC	TE	TE	TB	TC	TC	TB	TB	TC
OLEIC ACID	B	B	D	D	A	A	A	A	A	A
OLEUM	A	A	B	B	A	A	A	A	A	A
OXALIC ACID	B	B	D	D	A	A	A	A	A	A
PERCHLORIC ACID	A	A	C	C	A	A	A	A	A	A
PERCHLOROETHYLENE	B	B	D	D	A	B	A	A	A	B
PHENOL 5%	B	B	C	C	A	A	B	A	A	A
PHENOL 85%	A	A	A	A	A	A	A	A	A	A
PHOSPHORIC ACID 40%	C	D	D	D	B	B	B	B	B	TB
PHOSPHORIC ACID 85%	B	B	B	B	A	A	A	A	A	A
PICRIC ACID 10%	TB	TB	TD	TD	A	TB	A	A	A	TB
POTASSIUM ACETATE	C	C	E	E	B	C	C	B	B	C
POTASSIUM BROMIDE	D	D	E	E	B	C	B	B	B	C
POTASSIUM CARBONATE	D	D	E	E	B	D	B	C	C	TD
POTASSIUM CHLORIDE	C	C	D	D	B	C	B	A	A	TC
POTASSIUM HYDROXIDE 10%	D	D	E	E	B	C	B	B	B	C
POTASSIUM HYDROXIDE 50%	C	C	D	D	A	B	B	B	B	B
POTASSIUM IODIDE	TB	TB	TD	TD	TB	TB	TB	TB	TB	TB
POTASSIUM NITRATE	D	D	E	E	B	C	C	B	B	C
POTASSIUM PERMANGANATE	TB	TB	TD	TD	A	TB	A	TB	TB	TB
POTASSIUM PERSULFATE	B	B	D	D	A	B	A	B	B	B
POTASSIUM SULFATE	C	C	E	E	B	C	C	B	B	C

This data is provided as a service of Applied Polymer Solutions and is believed to be accurate. However this information is neither recommendations by APS nor product specifications. APS reserves the right to change or modify data as necessary.

CHEMICAL RESISTANCE CHART

	ST 3324 C	ST 3350	ST 3407	ST 3408	ST 3710	ST 3720	ST 4002	ST 4009	ST 4009 AM	ST 4033
PROPIONIC ACID	A	A	C	C	A	A	A	A	A	TB
PROPYLENE GLYCOL	D	D	E	E	C	D	C	B	B	D
PYRIDINE	A	A	A	A	A	A	A	A	A	A
SALICYLIC ACID	TB	TB	TD	TD	TB	TB	TB	TB	TB	TB
SALT BRINE	D	D	E	E	C	D	C	C	C	TD
SILVER NITRATE	TB	TB	TD	TD	A	A	A	A	A	A
SKYDROL	C	D	C	C	B	B	B	A	A	B
SODIUM ACETATE	D	D	E	E	C	D	C	B	B	TD
SODIUM BENZOATE	D	D	E	E	C	D	C	B	B	TD
SODIUM BICARBONATE	D	D	E	E	C	D	C	B	B	TD
SODIUM BISULFITE	TD	TD	TD	TD	TC	TD	TC	TB	TB	TD
SODIUM BISULFATE	D	D	E	E	B	C	C	B	B	C
SODIUM CARBONATE	D	D	E	E	B	C	C	B	B	C
SODIUM CHLORATE 50%	TC	TC	TD	TD	A	TB	TB	TB	TB	TB
SODIUM CHLORIDE	C	C	E	E	B	B	B	B	B	B
SODIUM CHLORITE	C	C	D	D	A	A	A	A	A	A
SODIUM CHROMATE	B	B	D	D	A	B	B	B	B	B
SODIUM DICHROMATE	B	B	D	D	B	B	B	B	B	B
SODIUM FERROCYANIDE	TC	TC	TD	TD	TB	TB	TB	TB	TB	TB
SODIUM FLUORIDE	A	A	TB	TB	A	A	A	A	A	A
SODIUM HYDROXIDE 10%	E	E	E	E	C	E	D	D	D	D
SODIUM HYDROXIDE 50%	D	D	E	E	B	E	C	D	D	D
SODIUM HYPOCHLORITE 3%	B	B	D	D	A	A	A	A	A	A
SODIUM HYPOCHLORITE 5-15%	A	A	A	A	A	A	A	A	A	A
SODIUM OXALATE	D	D	E	E	B	D	C	B	B	TD
SODIUM PEROXIDE	C	C	E	E	B	C	B	B	B	B
SODIUM PHOSPHATE 10%	C	C	E	E	B	C	C	B	B	B
SODIUM SILICATE	TC	TC	TD	TD	TB	TC	TB	TB	TB	TC
SODIUM SULFATE	D	D	E	E	B	C	C	B	B	C
SODIUM SULFIDE	D	D	E	E	B	C	C	B	B	C
SODIUM SULFITE	D	D	E	E	B	C	C	B	B	C

This data is provided as a service of Applied Polymer Solutions and is believed to be accurate. However this information is neither recommendations by APS nor product specifications. APS reserves the right to change or modify data as necessary.

CHEMICAL RESISTANCE CHART

	ST 3324 C	ST 3350	ST 3407	ST 3408	ST 3710	ST 3720	ST 4002	ST 4009	ST 4009 AM	ST 4033
SODIUM TARTRATE	D	D	E	E	B	C	C	B	B	C
SODIUM THIOSULFATE	C	C	E	E	B	C	C	B	B	C
STEARIC ACID	B	B	D	D	A	B	A	A	A	B
STYRENE	B	B	D	D	A	B	A	A	A	B
SULFAMIC ACID 25%	TB	TB	TC	TC	A	A	A	A	A	A
SULFURIC ACID 10%	D	D	E	E	B	C	B	C	C	B
SULFURIC ACID 30%	C	C	D	D	A	B	A	B	B	TB
SULFURIC ACID 98%	A	A	C	C	A	A	A	A	A	A
TALL OIL	C	C	E	E	B	C	C	B	B	C
TARTARIC ACID	TB	TB	TD	TD	TB	TB	TB	TB	TB	TB
TETROCHLOROETHANE	B	B	D	D	A	B	A	A	A	A
TETRAHYDROFURAN	A	A	A	A	A	A	A	A	A	A
THIONYL CHLORIDE	A	A	A	A	A	A	A	A	A	A
TOLUENE	C	C	D	D	B	B	B	A	A	B
TOLUENE SULFONIC ACID	B	B	D	D	B	B	B	B	B	B
TOLUIDENE	B	B	D	D	A	B	B	A	A	B
TRICHLOROACETIC ACID 20%	A	A	B	B	A	A	A	A	A	A
TRICHLOROETHANE	C	C	C	C	B	B	C	A	A	B
TRICHLOROETHYLENE	TB	TB	TC	TC	A	A	A	A	A	A
TRICESYL PHOSPHATE	TB	TB	TD	TD	TB	TB	TB	A	A	TB
TRISODIUM PHOSPHATE	C	C	E	E	B	C	C	B	B	C
TURPENTINE	C	C	D	D	B	B	B	A	A	B
UREA SOLUTIONS	TC	TC	TE	TE	TB	TC	TC	TB	TB	TC
WHITE LIQUOR (PAPER)	TC	TC	TD	TD	TB	TB	TB	A	A	TC
XYLENE	D	D	D	D	B	C	B	A	A	TC
ZINC CHLORATE	TC	TC	TD	TD	A	TB	TB	TB	TB	TB
ZINC SULFATE	C	C	E	E	B	B	B	B	B	B

This data is provided as a service of Applied Polymer Solutions and is believed to be accurate. However this information is neither recommendations by APS nor product specifications. APS reserves the right to change or modify data as necessary.

CHEMICAL RESISTANCE CHART

	ST 4045	ST 4055	ST 4100	ST 4107	ST 4107 AM	ST 4157	ST 4157 AM	ST 4281	ST 4283
ACETALDEHYDE	C	C	C	C	C	C	C	C	C
ACETIC ACID 5%	C	B	B	C	C	B	B	C	C
ACETIC ACID 10%	B	A	A	B	B	A	A	B	B
ACETIC ACID 25%	A	A	A	A	A	A	A	A	A
ACETIC ACID GLACIAL	A	A	A	A	A	A	A	A	A
ACETIC ANHYDRIDE	B	B	B	B	B	B	B	B	C
ACETONE 10%	C	C	C	C	C	B	B	C	C
ACETONE 100%	B	C	C	B	B	B	B	B	B
ACETYL CHLORIDE	A	A	A	A	A	A	A	A	A
ACETONITRILE	B	B	B	B	B	B	B	B	C
ACRYLIC ACID	TB	TB	TB	TB	TB	TB	TB	TB	TB
ACRYLONITRILE	TB	TB	TB	TB	TB	TB	TB	TB	TB
ADIPIIC ACID 25%	B	B	B	B	B	B	B	B	C
ALLYL ALCOHOL	TC	TC	TC	TC	TC	TC	TC	TC	TC
ALLYL CHLORIDE	TB	TB	TB	TB	TB	TB	TB	TB	TB
ALUMINUM BROMIDE	D	D	D	D	D	D	D	D	D
ALUMINUM CHLORIDE	TC	TC	TC	TC	TC	TC	TC	TC	TC
ALUMINUM FLUORIDE	TC	TC	TC	TC	TC	TC	TC	TC	TC
ALUMINUM HYDROXIDE	C	C	C	C	C	C	C	C	C
ALUMINUM NITRATE	D	D	D	D	D	D	D	C	C
ALUMINUM SULFATE	C	C	C	C	C	C	C	C	C
AMMONIA	D	D	D	D	D	D	D	C	C
AMMONIUM CHLORIDE	TC	TC	TC	TC	TC	TC	TC	TC	TB
AMMONIUM FLUORIDE	TB	TB	TB	TB	TB	TB	TB	TB	TB
AMMONIUM HYDROXIDE	TC	TC	TC	TC	TC	TC	TC	TC	TC
AMMONIUM NITRATE	D	D	D	D	D	D	D	D	D
AMMONIUM OXALATE	C	C	C	C	C	C	C	C	C
AMMONIUM NITRATE	TD	TD	TD	TD	TD	TD	TD	TD	TD
AMMONIUM PERSULFATE	C	C	C	C	C	C	C	C	C
AMMONIUM PHOSPHATE	C	C	C	C	C	C	C	C	C
AMMONIUM SULFATE	D	D	D	D	D	D	D	C	C

This data is provided as a service of Applied Polymer Solutions and is believed to be accurate. However this information is neither recommendations by APS nor product specifications. APS reserves the right to change or modify data as necessary.

CHEMICAL RESISTANCE CHART

	ST 4045	ST 4055	ST 4100	ST 4107	ST 4107 AM	ST 4157	ST 4157 AM	ST 4281	ST 4283
AMMONIUM SULFIDE	D	D	D	D	D	D	D	C	C
AMMONIUM SULFITE	D	D	D	D	D	D	D	C	C
AMYL ACETATE	TC	TC	TC	TC	TC	TC	TC	TC	TC
AMYL ALCOHOL	C	C	C	C	C	C	C	C	C
ANILINE	B	B	B	B	B	B	B	B	B
ANILINE HYDROCHLORIDE	B	B	B	B	B	B	B	B	B
ANTIMONY CHLORIDE	TB	TB	TB	TB	TB	TB	TB	TB	TB
AQUA REGIA	A	A	A	A	A	A	A	A	A
ARSENOUS ACID	TB	TB	TB	TB	TB	TB	TB	TC	TB
BARIUM ACETATE	C	C	C	C	C	C	C	C	C
BARIUM BROMIDE	C	C	C	C	C	C	C	C	C
BARIUM CARBONATE	C	C	C	C	C	C	C	C	C
BARIUM CHLORIDE	C	C	C	C	C	B	B	C	C
BARIUM HYDROXIDE	TC	TC	TC	TC	TC	TC	TC	TC	TC
BARIUM SULFATE	C	C	C	C	C	C	C	C	C
BARIUM SULFIDE	C	C	C	C	C	C	C	C	C
BENZYL CHLORIDE	TB	TB	TB	TB	TB	TB	TB	TB	TB
BENZOIC ACID	C	C	C	C	C	C	C	C	C
BENZALDEHYDE	TB	TB	TB	TB	TB	TB	TB	TB	TB
BENZENE	TC	TC	TC	TC	TC	TC	TC	TC	TC
BENZYL ALCOHOL	D	D	D	D	D	B	B	D	D
BLACK LIQUOR (PAPER)	TC	TC	TC	TC	TC	TC	TC	TC	TC
BLOOD SUGAR	TC	TC	TC	TC	TC	TC	TC	TC	TC
BORAX	C	C	C	C	C	C	C	C	C
BORIC ACID	C	C	C	C	C	C	C	C	C
BRINE	D	D	D	D	D	D	D	D	D
BROMINE LIQUID	A	A	A	A	A	A	A	A	A
BUTANOL	D	D	D	D	D	C	C	C	C
BUTYL ACETATE	C	C	C	C	C	C	C	C	C
BUTYL ACRYLATE	TB	TB	TB	TB	TB	TB	TB	TB	TB

This data is provided as a service of Applied Polymer Solutions and is believed to be accurate. However this information is neither recommendations by APS nor product specifications. APS reserves the right to change or modify data as necessary.

CHEMICAL RESISTANCE CHART

	ST 4045	ST 4055	ST 4100	ST 4107	ST 4107 AM	ST 4157	ST 4157 AM	ST 4281	ST 4283
BUTYL AMINE	TB	TB	TB	TB	TB	TB	TB	TB	TB
BUTYL CARBITOL	TC	TC	TC	TC	TC	TC	TC	TB	TB
BUTYL CELLOSOLVE	C	C	C	C	C	C	C	C	C
BUTYL ETHER	C	C	C	C	C	C	C	C	C
BUTYRIC ACID	A	A	A	A	A	A	A	A	A
CALCIUM BISULFITE	D	D	D	D	D	D	D	D	D
CALCIUM BROMIDE	TC	TC	TC	TC	TC	TC	TC	TB	TB
CALCIUM CARBONATE	C	C	C	C	C	C	C	C	C
CALCIUM CHLORATE	C	C	C	C	C	C	C	C	C
CALCIUM CHLORIDE	D	D	D	D	D	D	D	C	C
CALCIUM HYDROXIDE	D	D	D	D	D	D	D	C	C
CALCIUM HYPOCHLORITE	TB	TB	TB	TB	TB	TB	TB	TB	TB
CALCIUM NITRATE	D	D	D	D	D	D	D	D	D
CALCIUM SULFATE	C	C	C	C	C	C	C	C	C
CALCIUM SULFITE	C	C	C	C	C	C	C	C	C
CALCIUM DISULFIDE	B	B	B	B	B	B	B	B	B
CARBON TETRACHLORIDE	C	C	C	C	C	B	B	C	C
CASTOR OIL	C	C	C	C	C	C	C	C	C
CELLOSOLVE	TC	TC	TC	TC	TC	TC	TC	TC	TC
CELLOSOLVE ACETATE	C	C	C	C	C	C	C	C	TC
CHLOROACETIC ACID 25%	B	B	B	B	B	A	A	B	C
CHLOROACETIC ACID 50%	A	A	A	A	A	A	A	A	A
CHLOROBENZENE	C	C	C	C	C	C	C	B	B
CHLOROFORM	TB	TB	TB	TB	TB	TB	TB	A	A
CHLOROPHENOL	A	A	A	A	A	A	A	A	A
CHLOROSULFONIC ACID	A	A	A	A	A	A	A	A	A
CHLOROTOLUENE	TB	TB	TB	TB	TB	TB	TB	TB	TB
CHROMIC ACID 10%	A	A	A	A	A	A	A	B	TC
CHROMIC ACID 40%	A	A	A	A	A	A	A	A	B
CHROMIC CHLORIDE	A	A	A	A	A	A	A	A	A
CITRIC ACID	C	C	C	C	C	C	C	C	C

This data is provided as a service of Applied Polymer Solutions and is believed to be accurate. However this information is neither recommendations by APS nor product specifications. APS reserves the right to change or modify data as necessary.

CHEMICAL RESISTANCE CHART

	ST 4045	ST 4055	ST 4100	ST 4107	ST 4107 AM	ST 4157	ST 4157 AM	ST 4281	ST 4283
COPPER ACETATE	C	C	C	C	C	C	C	C	C
COPPER CHLORIDE	B	B	B	B	B	B	B	B	C
COPPER CYANIDE	TC	TC	TC	TC	TC	TC	TC	TC	B
COPPER NITRATE	TC	TC	TC	TC	TC	TC	TC	TC	TC
COPPER SULFATE	C	C	C	C	C	C	C	C	TC
CORN OIL	C	C	C	C	C	C	C	C	C
CORN STARCH SLURRY	E	E	E	E	E	E	E	E	D
CORN SUGAR	D	D	D	D	D	D	D	D	D
COTTONSEED OIL	C	C	C	C	C	C	C	C	C
CREOSOTE	C	C	C	C	C	C	C	C	C
CRESYLIC ACID	TB	TB	TB	TB	TB	TB	TB	TB	TB
CUMENE	C	C	C	C	C	C	C	C	TB
CUTTING OIL	C	C	C	C	C	C	C	C	C
CYCLOHEXANE	C	C	C	C	C	C	C	C	C
CYCLOHEXANONE	C	C	C	C	C	C	C	C	C
CYMENE	TC	TC	TC	TC	TC	TC	TC	TC	TC
DETERGENTS ORGANIC	TE	TE	TE	TE	TE	TE	TE	TE	TD
DETERGENTS SULFONATED	TE	TE	TE	TE	TE	TE	TE	TE	TD
DEXTROSE	E	E	E	E	E	E	E	E	TD
DIBUTYL PHTHALATE	D	D	D	D	D	D	D	D	D
DICHLORACETIC ACID	TC	TC	TC	TC	TC	TB	TB	TC	TC
DICHLOROBENZENE	C	C	C	C	C	C	C	C	TC
DICHLOROETHANE	A	A	A	A	A	A	A	A	B
DIESEL FUEL	C	C	C	C	C	C	C	C	B
DIETHANOLAMINE	TB	TB	TB	TB	TB	TB	TB	TB	TB
DIETHYL BENZENE	TC	TC	TC	TC	TC	TC	TC	TC	TB
DIETHYL KETONE	TB	TB	TB	TB	TB	TB	TB	TB	TB
DIETHYLENE GLYCOL	C	C	C	C	C	C	C	C	C
DIETHYL ETHER	B	B	B	B	B	B	B	B	B
DIMETHYL ANILINE	TB	TB	TB	TB	TB	TB	TB	TB	TC
DIMETHYL FORMAMIDE	A	A	A	A	A	A	A	A	A

This data is provided as a service of Applied Polymer Solutions and is believed to be accurate. However this information is neither recommendations by APS nor product specifications. APS reserves the right to change or modify data as necessary.

CHEMICAL RESISTANCE CHART

	ST 4045	ST 4055	ST 4100	ST 4107	ST 4107 AM	ST 4157	ST 4157 AM	ST 4281	ST 4283
DIMETHYL SULFOXIDE	A	A	A	A	A	A	A	A	A
DINITRO BENZENE	TB	TB	TB	TB	TB	TB	TB	TB	TB
DINITRO TOLUENE	TB	TB	TB	TB	TB	TB	TB	TB	TB
EPICHLOROHYDRIN	B	B	B	E	E	B	B	D	C
ETHANOL	B	C	C	B	B	C	C	B	B
ETHANOLAMINE	B	B	B	B	B	B	B	B	B
ETHYL ACETATE	A	A	A	A	A	A	A	A	A
ETHYL ACRYLATE	A	A	A	A	A	A	A	A	A
ETHYLAMINE	A	A	A	A	A	A	A	A	A
ETHYL BENZENE	TB	TB	TB	TB	TB	TB	TB	TB	TB
ETHYL BROMIDE	A	A	A	A	A	A	A	A	A
ETHYL CHLORIDE	A	A	A	A	A	A	A	A	A
ETHYL DICHLORIDE	A	A	A	A	A	A	A	A	A
ETHYLENE GLYCOL	D	D	D	D	D	D	D	D	D
ETHYL SULFATE	TB	TB	TB	TB	TB	TB	TB	TB	TB
FATTY ACIDS	TB	TB	TB	TB	TB	TB	TB	TC	TC
FERRIC CHLORIDE	E	E	E	E	E	C	C	E	D
FERRIC SULFATE	E	E	E	E	E	C	C	E	D
FERROUS NITRATE	C	C	C	C	C	C	C	C	C
FERROUS CHLORIDE	TD	TD	TD	TD	TD	TB	TB	TD	TD
FERROUS SULFATE	TE	TE	TE	TE	TE	TD	TD	TE	TE
FLUOSILICIC ACID 10-25%	A	A	A	A	A	A	A	A	A
FORMALDEHYDE	C	C	C	C	C	C	C	C	C
FORMIC ACID 10%	B	B	B	B	B	B	B	C	C
FORMIC ACID 50%	A	A	A	A	A	A	A	A	B
FUEL OIL	C	C	C	C	C	C	C	C	C
FURFURAL ALCOHOL	TB	TB	TB	TB	TB	TB	TB	TB	TB
GASOLINE AVIATION	B	B	B	B	B	B	B	C	C
GASOLINE DIESEL	B	B	B	B	B	B	B	C	C
GASOLINE JET FUEL	B	B	B	B	B	B	B	C	C
GASOLINE UNLEADED	C	C	C	C	C	C	C	C	C

This data is provided as a service of Applied Polymer Solutions and is believed to be accurate. However this information is neither recommendations by APS nor product specifications. APS reserves the right to change or modify data as necessary.

CHEMICAL RESISTANCE CHART

	ST 4045	ST 4055	ST 4100	ST 4107	ST 4107 AM	ST 4157	ST 4157 AM	ST 4281	ST 4283
GLUCOSE	E	E	E	E	E	E	E	D	D
GLYCERINE	TC	TD	TD	TC	TC	TD	TD	TB	TC
GLYCOLIC ACID 70%	A	A	A	A	A	A	A	A	A
GREEN LIQUOR (PAPER)	C	C	C	C	C	C	C	C	C
HEPTANE	D	D	D	D	D	D	D	C	C
HEXANE	D	D	D	D	D	D	D	D	D
HYDRAULIC FLUID	C	C	C	C	C	C	C	C	C
HYDRAZINE 35%	TB	TB	TB	TB	TB	TB	TB	TB	TB
HYDRIODIC ACID 20%	C	C	C	C	C	B	B	C	C
HYDROBROMIC ACID 18%	A	A	A	A	A	A	A	A	A
HYDROBROMIC ACID 40%	A	A	A	A	A	A	A	A	A
HYDROBROMIC ACID 60%	A	A	A	A	A	A	A	A	A
HYDROCHLORIC ACID 10%	C	C	C	C	C	C	C	C	C
HYDROCHLORIC ACID 36%	C	B	B	C	C	B	B	B	C
HYDROFLUORIC ACID	A	A	A	A	A	A	A	A	A
HYDROGEN PEROXIDE 10%	B	B	B	B	B	B	B	A	A
HYDROGEN PEROXIDE 50%	A	A	A	A	A	A	A	A	A
HYDROGEN SULFIDE 5%	C	C	C	C	C	C	C	C	C
HYDROGEN SULFIDE 100%	TC	TC	TC	TC	TC	TC	TC	TC	TB
HYPOCHLOROUS ACID	A	A	A	A	A	A	A	A	A
IODINE CRYSTALS/VAPOR	TC	TC	TC	TC	TC	TC	TC	TD	TC
ISOPHORONE	C	C	C	C	C	C	C	C	C
ISOPROPYL ACETATE	C	C	C	C	C	C	C	C	C
ISOPROPYL ALCOHOL	C	C	C	C	C	C	C	C	C
JET FUEL (JP-4)	B	B	B	B	B	B	B	C	B
KEROSENE	C	C	C	C	C	C	C	C	C
LACTIC ACID 10-20%	C	C	C	C	C	C	C	C	C
LACTIC ACID 50%	A	A	A	A	A	A	A	B	A
LACTIC ACID 85%	A	A	A	A	A	A	A	A	A
LAURIC ACID	TB	TB	TB	TB	TB	TB	TB	TB	TB
LEAD ACETATE	TD	TD	TD	TD	TD	TC	TC	TD	TD

This data is provided as a service of Applied Polymer Solutions and is believed to be accurate. However this information is neither recommendations by APS nor product specifications. APS reserves the right to change or modify data as necessary.

CHEMICAL RESISTANCE CHART

	ST 4045	ST 4055	ST 4100	ST 4107	ST 4107 AM	ST 4157	ST 4157 AM	ST 4281	ST 4283
LEVULINIC ACID	TC	TC	TC	TC	TC	TC	TC	TC	TC
LINSEED OIL	B	B	B	B	B	B	B	B	C
LITHIUM BROMIDE	TC	TC	TC	TC	TC	TC	TC	TC	TC
LITHIUM CHLORIDE SAT'D	B	B	B	B	B	B	B	B	B
LITHIUM HYDROXIDE	A	A	A	A	A	A	A	A	A
MAGNESIUM BISULFITE	B	B	B	B	B	B	B	C	B
MAGNESIUM CARBONATE	C	C	C	C	C	C	C	C	C
MAGNESIUM CHLORIDE	TB	TB	TB	TB	TB	TB	TB	TB	TB
MAGNESIUM HYDROXIDE	B	B	B	B	B	B	B	B	B
MAGNESIUM NITRATE	TB	TB	TB	TB	TB	TB	TB	TB	TB
MAGNESIUM SULFATE	TB	TB	TB	TB	TB	TB	TB	TB	TB
MALEIC ACID	A	A	A	A	A	A	A	A	A
MANGANESE CHLORIDE	TB	TB	TB	TB	TB	TB	TB	TB	TB
MANGANESE SULFATE	TB	TB	TB	TB	TB	TB	TB	TB	TB
MERCURIC CHLORIDE	TC	TC	TC	TC	TC	TB	TB	TC	TC
MERCUROUS CHLORIDE	TC	TC	TC	TC	TC	TC	TC	TC	TC
METHANOL	A	A	A	A	A	A	A	A	A
METHYL ACETATE	A	A	A	A	A	A	A	A	A
METHYLAMYL ALCOHOL	TC	TC	TC	TC	TC	TC	TC	TC	TC
METHYL BENZOATE	B	B	B	B	B	B	B	B	B
METHYL CHLORIDE	A	A	A	A	A	A	A	A	A
METHYLENE CHLORIDE	A	A	A	A	A	A	A	A	A
METHYL ETHYL KETONE	A	A	A	A	A	A	A	A	A
METHYL ISOBUTYL KETONE	B	B	B	B	B	B	B	B	B
MILK	D	D	D	D	D	D	D	D	D
MOLASSES	D	D	D	D	D	D	D	D	D
MINERAL OILS	TC	TC	TC	TC	TC	TC	TC	TD	TD
MINERAL SPIRITS	B	B	B	B	B	C	C	C	C
MOTOR OIL	C	C	C	C	C	C	C	D	D
M-PYROL	A	A	A	A	A	A	A	A	A
NAPHTHA ALIPHATIC	B	B	B	B	B	B	B	B	C

This data is provided as a service of Applied Polymer Solutions and is believed to be accurate. However this information is neither recommendations by APS nor product specifications. APS reserves the right to change or modify data as necessary.

CHEMICAL RESISTANCE CHART

	ST 4045	ST 4055	ST 4100	ST 4107	ST 4107 AM	ST 4157	ST 4157 AM	ST 4281	ST 4283
NAPHTHA AROMATIC	B	B	B	B	B	B	B	B	B
NICKEL CHLORIDE	A	A	A	A	A	A	A	A	A
NICKEL NITRATE	B	B	B	B	B	B	B	B	B
NICKEL SULFATE	TB	TB	TB	TB	TB	TB	TB	TB	TB
NITRIC ACID 5%	C	B	B	C	C	B	B	C	C
NITRIC ACID 30%	B	B	B	B	B	B	B	B	B
NITRIC ACID 60%	A	A	A	A	A	A	A	A	A
NITROBENZENE	A	A	A	A	A	A	A	A	A
OIL SOUR CRUDE	C	C	C	C	C	C	C	D	D
OIL SWEET CRUDE	TC	TC	TC	TC	TC	TC	TC	TD	TC
OLEIC ACID	A	A	A	A	A	A	A	A	A
OLEUM	A	A	A	A	A	A	A	A	A
OXALIC ACID	A	A	A	A	A	A	A	A	A
PERCHLORIC ACID	A	A	A	A	A	A	A	A	A
PERCHLOROETHYLENE	B	B	B	B	B	B	B	B	B
PHENOL 5%	A	A	B	A	A	A	A	A	A
PHENOL 85%	A	A	A	A	A	A	A	A	A
PHOSPHORIC ACID 40%	C	B	B	C	C	B	B	C	C
PHOSPHORIC ACID 85%	A	A	A	A	A	A	A	A	A
PICRIC ACID 10%	TB	TB	TB	TB	TB	TB	TB	TB	TB
POTASSIUM ACETATE	C	C	C	C	C	C	C	C	C
POTASSIUM BROMIDE	C	C	C	C	C	C	C	D	C
POTASSIUM CARBONATE	D	D	D	D	D	D	D	D	C
POTASSIUM CHLORIDE	C	C	C	C	C	C	C	C	C
POTASSIUM HYDROXIDE 10%	C	C	C	C	C	C	C	C	C
POTASSIUM HYDROXIDE 50%	B	B	B	B	B	B	B	B	B
POTASSIUM IODIDE	TB	TB	TB	TB	TB	TB	TB	TB	TC
POTASSIUM NITRATE	C	C	C	C	C	C	C	C	C
POTASSIUM PERMANGANATE	TB	TB	TB	TB	TB	TB	TB	TC	TC
POTASSIUM PERSULFATE	B	B	B	B	B	B	B	B	B
POTASSIUM SULFATE	C	C	C	C	C	C	C	C	C

This data is provided as a service of Applied Polymer Solutions and is believed to be accurate. However this information is neither recommendations by APS nor product specifications. APS reserves the right to change or modify data as necessary.

CHEMICAL RESISTANCE CHART

	ST 4045	ST 4055	ST 4100	ST 4107	ST 4107 AM	ST 4157	ST 4157 AM	ST 4281	ST 4283
PROPIONIC ACID	A	A	A	A	A	A	A	A	A
PROPYLENE GLYCOL	D	D	D	D	D	D	D	D	D
PYRIDINE	A	A	A	A	A	A	A	A	A
SALICYLIC ACID	TB	TB	TB	TB	TB	TB	TB	TC	TC
SALT BRINE	D	D	D	D	D	D	D	D	D
SILVER NITRATE	A	A	A	A	A	A	A	A	A
SKYDROL	C	B	B	C	C	B	B	C	C
SODIUM ACETATE	D	D	D	D	D	D	D	D	D
SODIUM BENZOATE	D	D	D	D	D	D	D	D	D
SODIUM BICARBONATE	D	D	D	D	D	D	D	D	D
SODIUM BISULFITE	TD	TD	TD	TD	TD	TD	TD	TD	TD
SODIUM BISULFATE	C	C	C	C	C	C	C	C	C
SODIUM CARBONATE	C	C	C	C	C	C	C	C	C
SODIUM CHLORATE 50%	TB	TB	TB	TB	TB	TB	TB	TB	TB
SODIUM CHLORIDE	B	B	B	B	B	B	B	B	B
SODIUM CHLORITE	A	A	A	A	A	A	A	A	A
SODIUM CHROMATE	B	B	B	B	B	B	B	B	B
SODIUM DICHROMATE	B	B	B	B	B	B	B	B	B
SODIUM FERROCYANIDE	TB	TB	TB	TB	TB	TB	TB	TC	TB
SODIUM FLUORIDE	A	A	A	A	A	A	A	A	A
SODIUM HYDROXIDE 10%	D	E	E	D	D	E	E	E	E
SODIUM HYDROXIDE 50%	C	E	E	C	C	E	E	E	E
SODIUM HYPOCHLORITE 3%	A	A	B	A	A	A	A	B	A
SODIUM HYPOCHLORITE 5-15%	A	A	A	A	A	A	A	A	A
SODIUM OXALATE	D	D	D	D	D	D	D	D	D
SODIUM PEROXIDE	C	C	C	C	C	C	C	C	C
SODIUM PHOSPHATE 10%	C	C	C	C	C	C	C	C	C
SODIUM SILICATE	TC	TC	TC	TC	TC	TC	TC	TC	TC
SODIUM SULFATE	C	C	C	C	C	C	C	D	C
SODIUM SULFIDE	C	C	C	C	C	C	C	C	C
SODIUM SULFITE	C	C	C	C	C	C	C	C	C

This data is provided as a service of Applied Polymer Solutions and is believed to be accurate. However this information is neither recommendations by APS nor product specifications. APS reserves the right to change or modify data as necessary.

CHEMICAL RESISTANCE CHART

	ST 4045	ST 4055	ST 4100	ST 4107	ST 4107 AM	ST 4157	ST 4157 AM	ST 4281	ST 4283
SODIUM TARTRATE	C	C	C	C	C	C	C	C	C
SODIUM THIOSULFATE	C	C	C	C	C	C	C	D	D
STEARIC ACID	B	B	B	B	B	B	B	C	C
STYRENE	B	B	B	B	B	B	B	B	B
SULFAMIC ACID 25%	A	A	A	A	A	A	A	A	A
SULFURIC ACID 10%	C	C	C	C	C	C	C	D	D
SULFURIC ACID 30%	B	B	B	B	B	B	B	C	C
SULFURIC ACID 98%	A	A	A	A	A	A	A	A	A
TALL OIL	C	C	C	C	C	C	C	C	C
TARTARIC ACID	TB	TB	TB	TB	TB	TB	TB	TB	TB
TETROCHLOROETHANE	B	B	B	B	B	A	A	B	B
TETRAHYDROFURAN	A	A	A	A	A	A	A	A	A
THIONYL CHLORIDE	A	A	A	A	A	A	A	A	A
TOLUENE	B	B	B	B	B	B	B	B	B
TOLUENE SULFONIC ACID	B	B	B	B	B	B	B	B	C
TOLUIDENE	B	B	B	B	B	B	B	B	B
TRICHLOROACETIC ACID 20%	A	A	A	A	A	A	A	A	A
TRICHLOROETHANE	C	B	B	C	C	B	B	B	B
TRICHLOROETHYLENE	A	A	A	A	A	A	A	A	A
TRICESYL PHOSPHATE	TB	TB	TB	TB	TB	TB	TB	TB	TC
TRISODIUM PHOSPHATE	C	C	C	C	C	C	C	D	D
TURPENTINE	B	B	B	B	B	B	B	B	B
UREA SOLUTIONS	TC	TC	TC	TC	TC	TC	TC	TC	TC
WHITE LIQUOR (PAPER)	TB	TB	TB	TB	TB	TB	TB	TB	TB
XYLENE	C	C	C	C	C	C	C	B	B
ZINC CHLORATE	TB	TB	TB	TB	TB	TB	TB	TB	TB
ZINC SULFATE	B	B	B	B	B	B	B	B	B

This data is provided as a service of Applied Polymer Solutions and is believed to be accurate. However this information is neither recommendations by APS nor product specifications. APS reserves the right to change or modify data as necessary.

CHEMICAL RESISTANCE CHART

	ST 4283 c	ST 4301	ST 4349	ST 4405	ST 4409	ST 4453	ST 4456	ST 4700	ST 4710	ST 4805
ACETALDEHYDE	C	B	C	B	TD	D	D	C	C	C
ACETIC ACID 5%	C	B	C	B	D	D	D	B	B	C
ACETIC ACID 10%	B	A	B	A	B	B	C	A	A	B
ACETIC ACID 25%	A	A	A	A	B	B	C	A	A	A
ACETIC ACID GLACIAL	A	A	A	A	A	A	A	A	A	A
ACETIC ANHYDRIDE	C	B	C	B	D	D	D	B	B	B
ACETONE 10%	C	B	B	B	C	C	D	C	C	C
ACETONE 100%	B	A	B	B	C	C	C	C	C	B
ACETYL CHLORIDE	A	A	TB	TB	TC	TC	TD	A	A	A
ACETONITRILE	C	B	C	B	D	D	D	B	B	B
ACRYLIC ACID	TB	TB	TB	TB	TD	TD	TD	TB	TB	TB
ACRYLONITRILE	TB	TB	A	A	TB	TB	TB	TB	TB	TB
ADIPIIC ACID 25%	C	A	B	B	C	C	C	B	B	B
ALLYL ALCOHOL	TC	TC	TC	TB	TD	TD	TD	TC	TC	TC
ALLYL CHLORIDE	TB	TB	TB	A	TC	TC	TC	TB	TB	TB
ALUMINUM BROMIDE	D	C	D	C	D	D	E	D	D	D
ALUMINUM CHLORIDE	TC	TB	TD	TC	TD	TD	TE	TC	TC	TC
ALUMINUM FLUORIDE	TC	TB	TB	TC	TD	TD	TE	TC	TC	TC
ALUMINUM HYDROXIDE	C	C	C	C	D	D	E	C	C	C
ALUMINUM NITRATE	C	C	C	C	E	E	E	D	D	D
ALUMINUM SULFATE	C	C	C	C	D	D	E	C	C	C
AMMONIA	C	C	D	C	E	E	E	C	D	C
AMMONIUM CHLORIDE	TB	TB	TC	TC	TD	TD	TD	TC	TC	TC
AMMONIUM FLUORIDE	TB	TB	TB	TB	TC	TC	TC	TB	TB	TB
AMMONIUM HYDROXIDE	TC	TC	TC	TC	TD	TD	TD	TC	TC	TC
AMMONIUM NITRATE	D	C	D	D	E	E	E	D	D	D
AMMONIUM OXALATE	C	C	C	TC	D	D	D	C	C	C
AMMONIUM NITRATE	TD	TC	TD	TC	TE	TE	TE	TD	TD	TD
AMMONIUM PERSULFATE	C	B	C	B	D	D	E	C	C	C
AMMONIUM PHOSPHATE	C	C	C	B	D	D	E	C	C	C
AMMONIUM SULFATE	C	C	C	C	D	D	E	D	D	D

This data is provided as a service of Applied Polymer Solutions and is believed to be accurate. However this information is neither recommendations by APS nor product specifications. APS reserves the right to change or modify data as necessary.

CHEMICAL RESISTANCE CHART

	ST 4283 c	ST 4301	ST 4349	ST 4405	ST 4409	ST 4453	ST 4456	ST 4700	ST 4710	ST 4805
AMMONIUM SULFIDE	C	C	C	C	E	E	E	D	D	D
AMMONIUM SULFITE	C	C	C	C	E	E	E	D	D	D
AMYL ACETATE	TC	TB	TB	TB	TD	TD	TD	TC	TC	TC
AMYL ALCOHOL	C	B	C	B	D	D	D	C	C	C
ANILINE	B	B	B	A	C	C	D	B	B	B
ANILINE HYDROCHLORIDE	B	B	B	A	C	C	D	B	B	B
ANTIMONY CHLORIDE	TB	A	TB	A	TC	TC	TC	TB	TB	TB
AQUA REGIA	A	A	A	A	A	A	A	A	A	A
ARSENOUS ACID	TB	A	TB	A	TC	TC	TC	TB	TB	TB
BARIUM ACETATE	C	C	C	B	D	D	E	C	C	C
BARIUM BROMIDE	C	C	B	B	D	D	E	C	C	C
BARIUM CARBONATE	C	C	B	B	D	D	E	C	C	C
BARIUM CHLORIDE	C	B	D	B	D	D	E	C	C	C
BARIUM HYDROXIDE	TC	TC	TC	TB	TD	TD	TE	TC	TC	TC
BARIUM SULFATE	C	C	C	B	D	D	E	C	C	C
BARIUM SULFIDE	C	B	B	B	C	C	D	C	C	C
BENZYL CHLORIDE	TB	A	TB	A	TC	TC	TD	TB	TB	TB
BENZOIC ACID	C	B	B	B	C	C	D	C	C	C
BENZALDEHYDE	TB	TB	TB	TB	TC	TC	TC	TB	TB	TB
BENZENE	TC	TB	TB	TB	TC	TC	TD	TC	TC	TC
BENZYL ALCOHOL	D	C	C	C	E	E	E	D	D	D
BLACK LIQUOR (PAPER)	TC	TB	TC	TB	TD	TD	TD	TC	TC	TC
BLOOD SUGAR	TC	TC	TC	TB	TD	TD	TD	TC	TC	TC
BORAX	C	C	C	B	D	D	D	C	C	C
BORIC ACID	C	B	B	B	C	C	D	C	C	C
BRINE	D	D	D	D	E	E	E	D	D	D
BROMINE LIQUID	A	A	A	A	A	A	A	A	A	A
BUTANOL	C	C	D	C	E	E	E	D	D	D
BUTYL ACETATE	C	C	C	B	D	D	D	C	C	C
BUTYL ACRYLATE	TB	TB	TB	A	TC	TC	TC	TB	TB	TB

This data is provided as a service of Applied Polymer Solutions and is believed to be accurate. However this information is neither recommendations by APS nor product specifications. APS reserves the right to change or modify data as necessary.

CHEMICAL RESISTANCE CHART

	ST 4283 c	ST 4301	ST 4349	ST 4405	ST 4409	ST 4453	ST 4456	ST 4700	ST 4710	ST 4805
BUTYL AMINE	TB	TB	TB	A	TC	TC	TC	TB	TB	TB
BUTYL CARBITOL	TB	TB	TC	TB	TD	TD	TD	TC	TC	TC
BUTYL CELLOSOLVE	C	C	B	B	C	C	D	C	C	C
BUTYL ETHER	C	C	B	B	D	D	D	C	C	C
BUTYRIC ACID	A	A	B	A	B	B	C	A	A	A
CALCIUM BISULFITE	D	D	D	C	E	E	E	D	D	D
CALCIUM BROMIDE	TB	TB	TC	TB	TD	TD	TD	TC	TC	TC
CALCIUM CARBONATE	C	C	C	B	D	D	D	C	C	C
CALCIUM CHLORATE	C	B	C	B	D	D	D	C	C	C
CALCIUM CHLORIDE	C	B	D	C	E	E	E	D	D	D
CALCIUM HYDROXIDE	C	C	C	B	E	E	E	D	D	D
CALCIUM HYPOCHLORITE	TB	TB	TC	TB	TC	TC	TD	TB	TB	TB
CALCIUM NITRATE	D	C	D	D	E	E	E	D	D	D
CALCIUM SULFATE	C	C	C	B	C	C	D	C	C	C
CALCIUM SULFITE	C	C	C	B	C	C	D	C	C	C
CALCIUM DISULFIDE	B	A	B	A	B	B	C	B	B	B
CARBON TETRACHLORIDE	C	C	C	B	D	D	E	C	C	C
CASTOR OIL	C	C	D	B	D	D	E	C	C	C
CELLOSOLVE	TC	TC	TC	TC	TD	TD	TD	TC	TC	TC
CELLOSOLVE ACETATE	TC	C	C	B	C	C	D	C	C	C
CHLOROACETIC ACID 25%	C	A	A	A	C	C	C	B	B	B
CHLOROACETIC ACID 50%	A	A	A	A	A	A	A	A	A	A
CHLOROBENZENE	B	B	B	B	D	D	D	C	C	C
CHLOROFORM	A	TB	A	A	TC	TC	TC	TB	TB	TB
CHLOROPHENOL	A	A	A	A	A	A	A	A	A	A
CHLOROSULFONIC ACID	A	A	A	A	A	A	A	A	A	A
CHLOROTOLUENE	TB	TB	TB	A	TC	TC	TD	TB	TB	TB
CHROMIC ACID 10%	TC	A	B	A	B	B	C	A	A	A
CHROMIC ACID 40%	B	A	A	A	B	B	B	A	A	A
CHROMIC CHLORIDE	A	A	A	A	B	B	B	A	A	A
CITRIC ACID	C	B	D	B	E	E	E	C	C	C

This data is provided as a service of Applied Polymer Solutions and is believed to be accurate. However this information is neither recommendations by APS nor product specifications. APS reserves the right to change or modify data as necessary.

CHEMICAL RESISTANCE CHART

	ST 4283 c	ST 4301	ST 4349	ST 4405	ST 4409	ST 4453	ST 4456	ST 4700	ST 4710	ST 4805
COPPER ACETATE	C	B	D	C	E	E	E	C	C	C
COPPER CHLORIDE	C	B	C	B	D	D	D	B	B	B
COPPER CYANIDE	B	TB	TC	TC	TD	TD	TD	TC	TC	TC
COPPER NITRATE	TC	TB	TC	TC	TD	TD	TD	TC	TC	TC
COPPER SULFATE	TC	B	B	B	D	D	D	C	C	C
CORN OIL	C	B	C	B	D	D	E	C	C	C
CORN STARCH SLURRY	D	C	E	E	E	E	E	E	E	E
CORN SUGAR	D	C	D	C	E	E	E	D	D	D
COTTONSEED OIL	C	C	C	B	D	D	E	C	C	C
CREOSOTE	C	B	C	B	D	D	E	C	C	C
CRESYLIC ACID	TB	A	TB	A	TC	TC	TD	TB	TB	TB
CUMENE	TB	B	B	B	D	D	E	C	C	C
CUTTING OIL	C	B	C	B	D	D	E	C	C	C
CYCLOHEXANE	C	B	C	C	E	E	E	C	C	C
CYCLOHEXANONE	C	B	C	C	D	D	E	C	C	C
CYMENE	TC	TB	TC	TC	TD	TD	TD	TC	TC	TC
DETERGENTS ORGANIC	TD	TC	TC	TC	TD	TD	TE	TE	TE	TE
DETERGENTS SULFONATED	TD	TC	TC	TC	TD	TD	TE	TE	TE	TE
DEXTROSE	TD	C	E	E	E	E	E	E	E	E
DIBUTYL PHTHALATE	D	B	D	C	E	E	E	D	D	D
DICHLORACETIC ACID	TC	A	TB	TB	TB	TB	TC	TC	TC	TC
DICHLOROBENZENE	TC	B	C	B	D	D	E	C	C	C
DICHLOROETHANE	B	A	B	A	C	C	C	A	A	A
DIESEL FUEL	B	B	C	B	D	D	D	C	C	C
DIETHANOLAMINE	TB	TB	TC	TB	TD	TD	TD	TB	TB	TB
DIETHYL BENZENE	TB	TB	TC	TB	TD	TD	TD	TC	TC	TC
DIETHYL KETONE	TB	A	TB	A	TD	TD	TD	TB	TB	TB
DIETHYLENE GLYCOL	C	C	C	B	E	E	E	C	C	C
DIETHYL ETHER	B	B	C	B	D	D	D	B	B	B
DIMETHYL ANILINE	TC	TB	TB	A	TC	TC	TD	TB	TB	TB
DIMETHYL FORMAMIDE	A	A	A	A	A	A	A	A	A	A

This data is provided as a service of Applied Polymer Solutions and is believed to be accurate. However this information is neither recommendations by APS nor product specifications. APS reserves the right to change or modify data as necessary.

CHEMICAL RESISTANCE CHART

	ST 4283 c	ST 4301	ST 4349	ST 4405	ST 4409	ST 4453	ST 4456	ST 4700	ST 4710	ST 4805
DIMETHYL SULFOXIDE	A	A	A	A	B	B	B	A	A	A
DINITRO BENZENE	TB	TB	TB	A	TC	TC	TC	TB	TB	TB
DINITRO TOLUENE	TB	TB	TB	A	TC	TC	TC	TB	TB	TB
EPICHLOROHYDRIN	C	B	B	A	C	C	D	B	B	B
ETHANOL	B	C	B	B	C	C	C	C	C	B
ETHANOLAMINE	B	B	C	A	D	D	D	B	B	B
ETHYL ACETATE	A	A	B	A	C	C	C	A	A	A
ETHYL ACRYLATE	A	A	B	A	C	C	C	A	A	A
ETHYLAMINE	A	A	TB	A	TC	TC	TC	A	A	A
ETHYL BENZENE	TB	TB	TB	A	TD	TD	TD	TB	TB	TB
ETHYL BROMIDE	A	A	A	A	B	B	B	A	A	A
ETHYL CHLORIDE	A	A	A	A	B	B	B	A	A	A
ETHYL DICHLORIDE	A	A	A	A	TB	TB	TB	A	A	A
ETHYLENE GLYCOL	D	C	D	C	E	E	E	D	D	D
ETHYL SULFATE	TB	TB	TB	A	TD	TD	TD	TB	TB	TB
FATTY ACIDS	TC	TB	TB	TB	TD	TD	TD	TB	TB	TB
FERRIC CHLORIDE	D	C	E	D	E	E	E	E	E	E
FERRIC SULFATE	D	C	E	D	E	E	E	E	E	E
FERROUS NITRATE	C	C	C	B	E	E	E	C	C	C
FERROUS CHLORIDE	TD	TB	TD	TC	TD	TD	TD	TD	TD	TD
FERROUS SULFATE	TE	TD	TD	TD	TE	TE	TE	TE	TE	TE
FLUOSILICIC ACID 10-25%	A	A	A	A	A	A	A	A	A	A
FORMALDEHYDE	C	C	B	B	D	D	E	C	C	C
FORMIC ACID 10%	C	B	C	A	D	D	D	B	B	B
FORMIC ACID 50%	B	A	A	A	B	B	B	A	A	A
FUEL OIL	C	B	C	B	E	E	E	C	C	C
FURFURAL ALCOHOL	TB	A	TB	A	TC	TC	TC	TB	TB	TB
GASOLINE AVIATION	C	B	D	C	D	D	D	B	B	B
GASOLINE DIESEL	C	B	D	C	D	D	D	B	B	B
GASOLINE JET FUEL	C	B	D	C	D	D	D	B	B	B
GASOLINE UNLEADED	C	B	D	C	E	E	E	C	C	C

This data is provided as a service of Applied Polymer Solutions and is believed to be accurate. However this information is neither recommendations by APS nor product specifications. APS reserves the right to change or modify data as necessary.

CHEMICAL RESISTANCE CHART

	ST 4283 c	ST 4301	ST 4349	ST 4405	ST 4409	ST 4453	ST 4456	ST 4700	ST 4710	ST 4805
GLUCOSE	D	E	D	D	E	E	E	E	E	E
GLYCERINE	TC	TC	TD	TC	TE	TE	TE	TD	TD	TC
GLYCOLIC ACID 70%	A	A	A	A	TB	TB	TB	A	A	A
GREEN LIQUOR (PAPER)	C	B	C	B	E	E	E	C	C	C
HEPTANE	C	C	D	C	E	E	E	D	D	D
HEXANE	D	C	D	C	E	E	E	D	D	D
HYDRAULIC FLUID	C	B	C	B	E	E	E	C	C	C
HYDRAZINE 35%	TB	TB	TB	A	TC	TC	TC	TB	TB	TB
HYDRIODIC ACID 20%	C	A	C	A	D	D	D	C	C	B
HYDROBROMIC ACID 18%	A	A	A	A	C	C	C	A	A	A
HYDROBROMIC ACID 40%	A	A	A	A	TB	TB	TC	A	A	A
HYDROBROMIC ACID 60%	A	A	A	A	TB	TB	TB	A	A	A
HYDROCHLORIC ACID 10%	C	C	C	C	D	D	D	C	C	C
HYDROCHLORIC ACID 36%	C	A	C	B	D	D	D	B	B	B
HYDROFLUORIC ACID	A	A	A	A	A	A	A	A	A	A
HYDROGEN PEROXIDE 10%	A	A	C	A	C	C	C	B	B	B
HYDROGEN PEROXIDE 50%	A	A	A	A	A	A	A	A	A	A
HYDROGEN SULFIDE 5%	C	C	D	B	D	D	D	C	C	C
HYDROGEN SULFIDE 100%	TB	TB	TB	TB	TD	TD	TD	TC	TC	TC
HYPOCHLOROUS ACID	A	A	A	A	A	A	A	A	A	A
IODINE CRYSTALS/VAPOR	TC	TB	TC	TC	TD	TD	TD	TC	TC	TC
ISOPHORONE	C	C	C	C	E	E	E	C	C	C
ISOPROPYL ACETATE	C	C	C	C	E	E	E	C	C	C
ISOPROPYL ALCOHOL	C	C	C	B	E	E	E	C	C	C
JET FUEL (JP-4)	B	B	D	C	D	D	D	B	B	B
KEROSENE	C	B	C	B	D	D	D	C	C	C
LACTIC ACID 10-20%	C	C	D	D	D	D	D	C	C	C
LACTIC ACID 50%	A	A	A	A	C	C	C	A	A	A
LACTIC ACID 85%	A	A	A	A	A	A	A	A	A	A
LAURIC ACID	TB	A	TB	A	TD	TD	TD	TB	TB	TB
LEAD ACETATE	TD	TB	TD	TC	TE	TE	TE	TD	TD	TD

This data is provided as a service of Applied Polymer Solutions and is believed to be accurate. However this information is neither recommendations by APS nor product specifications. APS reserves the right to change or modify data as necessary.

CHEMICAL RESISTANCE CHART

	ST 4283 c	ST 4301	ST 4349	ST 4405	ST 4409	ST 4453	ST 4456	ST 4700	ST 4710	ST 4805
LEVULINIC ACID	TC	TB	TC	TC	TD	TD	TD	TC	TC	TC
LINSEED OIL	C	B	C	B	D	D	D	B	B	B
LITHIUM BROMIDE	TC	TC	TB	TB	TD	TD	TD	TC	TC	TC
LITHIUM CHLORIDE SAT'D	B	B	B	B	D	D	D	B	B	B
LITHIUM HYDROXIDE	A	A	TB	A	TC	TC	TD	A	A	A
MAGNESIUM BISULFITE	B	B	C	B	D	D	D	B	B	B
MAGNESIUM CARBONATE	C	C	C	C	D	D	D	C	C	C
MAGNESIUM CHLORIDE	TB	TB	TB	A	TC	TC	TC	TB	TB	TB
MAGNESIUM HYDROXIDE	B	B	B	B	C	C	C	B	B	B
MAGNESIUM NITRATE	TB	TB	TC	TB	TD	TD	TD	TB	TB	TB
MAGNESIUM SULFATE	TB	TB	TB	TB	TD	TD	TD	TB	TB	TB
MALEIC ACID	A	A	B	A	C	C	C	A	A	A
MANGANESE CHLORIDE	TB	A	TB	TB	TD	TD	TD	TB	TB	TB
MANGANESE SULFATE	TB	TB	TB	TB	TD	TD	TD	TB	TB	TB
MERCURIC CHLORIDE	TC	A	TC	TC	TE	TE	TE	TC	TC	TC
MERCUROUS CHLORIDE	TC	A	TC	TC	TE	TE	TE	TC	TC	TC
METHANOL	A	A	B	B	C	C	C	A	A	A
METHYL ACETATE	A	A	B	A	C	C	C	A	A	A
METHYLAMYL ALCOHOL	TC	TB	TC	TC	TD	TD	TD	TC	TC	TC
METHYL BENZOATE	B	B	B	B	D	D	D	B	B	B
METHYL CHLORIDE	A	A	A	A	B	B	B	A	A	A
METHYLENE CHLORIDE	A	A	A	A	A	A	A	A	A	A
METHYL ETHYL KETONE	A	A	A	A	C	C	C	A	A	A
METHYL ISOBUTYL KETONE	B	B	B	B	D	D	D	B	B	B
MILK	D	D	D	D	E	E	E	D	D	D
MOLASSES	D	D	D	E	E	E	E	D	D	D
MINERAL OILS	TD	TC	TD	TD	TE	TE	TE	TC	TC	TC
MINERAL SPIRITS	C	B	C	C	D	D	D	B	B	B
MOTOR OIL	D	C	C	C	D	D	D	C	C	C
M-PYROL	A	A	A	A	A	A	B	A	A	A
NAPHTHA ALIPHATIC	C	B	C	B	E	E	E	B	B	B

This data is provided as a service of Applied Polymer Solutions and is believed to be accurate. However this information is neither recommendations by APS nor product specifications. APS reserves the right to change or modify data as necessary.

CHEMICAL RESISTANCE CHART

	ST 4283 c	ST 4301	ST 4349	ST 4405	ST 4409	ST 4453	ST 4456	ST 4700	ST 4710	ST 4805
NAPHTHA AROMATIC	B	B	B	A	D	D	E	B	B	B
NICKEL CHLORIDE	A	A	TB	TB	TC	TC	TD	A	A	A
NICKEL NITRATE	B	B	C	B	D	D	D	B	B	B
NICKEL SULFATE	TB	TB	TB	TB	TD	TD	TD	TB	TB	TB
NITRIC ACID 5%	C	B	D	C	E	E	E	B	B	C
NITRIC ACID 30%	B	A	C	B	C	C	C	B	B	B
NITRIC ACID 60%	A	A	A	A	A	A	A	A	A	A
NITROBENZENE	A	A	TB	TB	TC	TC	TC	A	A	A
OIL SOUR CRUDE	D	C	C	C	E	E	E	C	C	C
OIL SWEET CRUDE	TC	TC	TC	TC	TE	TE	TE	TC	TC	TC
OLEIC ACID	A	A	B	B	D	D	D	A	A	A
OLEUM	A	A	A	A	B	B	C	A	A	A
OXALIC ACID	A	A	B	B	D	D	D	A	A	A
PERCHLORIC ACID	A	A	A	A	C	C	C	A	A	A
PERCHLOROETHYLENE	B	B	B	B	D	D	D	B	B	B
PHENOL 5%	A	A	B	A	C	C	C	A	A	A
PHENOL 85%	A	A	A	A	A	A	B	A	A	A
PHOSPHORIC ACID 40%	C	A	D	B	D	D	D	B	B	B
PHOSPHORIC ACID 85%	A	A	B	A	B	B	B	A	A	A
PICRIC ACID 10%	TB	TB	TB	TB	TD	TD	TD	TB	TB	TB
POTASSIUM ACETATE	C	C	C	C	E	E	E	C	C	C
POTASSIUM BROMIDE	C	C	D	D	E	E	E	C	C	C
POTASSIUM CARBONATE	C	C	D	D	E	E	E	D	D	D
POTASSIUM CHLORIDE	C	A	C	C	D	D	D	C	C	C
POTASSIUM HYDROXIDE 10%	C	C	D	C	E	E	E	C	C	C
POTASSIUM HYDROXIDE 50%	B	C	C	B	D	D	E	B	B	B
POTASSIUM IODIDE	TC	TB	TB	TB	TD	TD	TD	TB	TB	TB
POTASSIUM NITRATE	C	C	D	C	E	E	E	C	C	C
POTASSIUM PERMANGANATE	TC	TB	TB	TB	TD	TD	TD	TB	TB	TB
POTASSIUM PERSULFATE	B	B	B	B	D	D	D	B	B	B
POTASSIUM SULFATE	C	C	C	C	E	E	E	C	C	C

This data is provided as a service of Applied Polymer Solutions and is believed to be accurate. However this information is neither recommendations by APS nor product specifications. APS reserves the right to change or modify data as necessary.

CHEMICAL RESISTANCE CHART

	ST 4283 c	ST 4301	ST 4349	ST 4405	ST 4409	ST 4453	ST 4456	ST 4700	ST 4710	ST 4805
PROPIONIC ACID	A	B	A	A	C	C	C	A	A	A
PROPYLENE GLYCOL	D	D	D	D	E	E	E	D	D	D
PYRIDINE	A	A	A	A	A	A	A	A	A	A
SALICYLIC ACID	TC	TB	TB	TB	TD	TD	TD	TB	TB	TB
SALT BRINE	D	C	D	C	E	E	E	D	D	D
SILVER NITRATE	A	A	TB	TB	TD	TD	TD	A	A	A
SKYDROL	C	A	C	C	C	C	C	B	B	B
SODIUM ACETATE	D	C	D	D	E	E	E	D	D	D
SODIUM BENZOATE	D	C	D	D	E	E	E	D	D	D
SODIUM BICARBONATE	D	D	D	D	E	E	E	D	D	D
SODIUM BISULFITE	TD	TD	TD	TD	TE	TE	TD	TD	TD	TD
SODIUM BISULFATE	C	C	D	C	E	E	E	C	C	C
SODIUM CARBONATE	C	C	D	C	E	E	E	C	C	C
SODIUM CHLORATE 50%	TB	TB	TC	TB	TD	TD	TD	TB	TB	TB
SODIUM CHLORIDE	B	B	C	C	E	E	E	B	B	B
SODIUM CHLORITE	A	A	C	B	D	D	D	A	A	A
SODIUM CHROMATE	B	B	B	B	D	D	D	B	B	B
SODIUM DICHROMATE	B	B	B	B	D	D	E	B	B	B
SODIUM FERROCYANIDE	TB	TB	TC	TB	TD	TD	TD	TB	TB	TB
SODIUM FLUORIDE	A	A	A	A	TB	TB	TB	A	A	A
SODIUM HYDROXIDE 10%	E	D	E	C	E	E	E	E	E	C
SODIUM HYDROXIDE 50%	E	C	E	C	E	E	E	E	E	C
SODIUM HYPOCHLORITE 3%	A	A	B	A	D	D	D	A	B	A
SODIUM HYPOCHLORITE 5-15%	A	A	A	A	A	A	A	A	A	A
SODIUM OXALATE	D	C	D	D	E	E	E	D	D	D
SODIUM PEROXIDE	C	B	C	C	E	E	E	C	C	B
SODIUM PHOSPHATE 10%	C	B	C	C	E	E	E	C	C	C
SODIUM SILICATE	TC	TC	TC	TB	TD	TD	TD	TC	TC	TC
SODIUM SULFATE	C	C	D	C	E	E	E	C	C	C
SODIUM SULFIDE	C	C	D	C	E	E	E	C	C	C
SODIUM SULFITE	C	C	D	D	E	E	E	C	C	C

This data is provided as a service of Applied Polymer Solutions and is believed to be accurate. However this information is neither recommendations by APS nor product specifications. APS reserves the right to change or modify data as necessary.

CHEMICAL RESISTANCE CHART

	ST 4283 c	ST 4301	ST 4349	ST 4405	ST 4409	ST 4453	ST 4456	ST 4700	ST 4710	ST 4805
SODIUM TARTRATE	C	C	D	C	E	E	E	C	C	C
SODIUM THIOSULFATE	D	C	C	C	E	E	E	C	C	C
STEARIC ACID	C	A	B	B	D	D	E	B	B	B
STYRENE	B	B	B	B	D	D	D	B	B	B
SULFAMIC ACID 25%	A	A	TB	A	TC	TC	TD	A	A	A
SULFURIC ACID 10%	D	B	C	C	E	E	E	C	C	C
SULFURIC ACID 30%	C	A	C	C	D	D	D	B	B	C
SULFURIC ACID 98%	A	A	A	A	C	C	C	A	A	A
TALL OIL	C	C	C	C	E	E	E	C	C	C
TARTARIC ACID	TB	TB	TB	TB	TD	TD	TD	TB	TB	TB
TETROCHLOROETHANE	B	A	B	B	D	D	D	B	B	B
TETRAHYDROFURAN	A	A	A	A	A	A	A	A	A	A
THIONYL CHLORIDE	A	A	A	A	A	A	A	A	A	A
TOLUENE	B	B	C	B	D	D	D	B	B	B
TOLUENE SULFONIC ACID	C	B	B	B	D	D	D	B	B	B
TOLUIDENE	B	B	B	B	D	D	E	B	B	B
TRICHLOROACETIC ACID 20%	A	A	A	A	B	B	B	A	A	A
TRICHLOROETHANE	B	C	B	C	C	C	D	B	B	C
TRICHLOROETHYLENE	A	A	TB	TB	TC	TC	TD	A	A	A
TRICESYL PHOSPHATE	TC	TB	TB	TB	TD	TD	TD	TB	TB	TB
TRISODIUM PHOSPHATE	D	C	C	C	E	E	E	C	C	C
TURPENTINE	B	B	C	B	D	D	D	B	B	B
UREA SOLUTIONS	TC	TC	TC	TC	TE	TE	TE	TC	TC	TC
WHITE LIQUOR (PAPER)	TB	TB	TC	TB	TD	TD	TE	TB	TB	TB
XYLENE	B	C	C	C	D	D	D	C	C	C
ZINC CHLORATE	TB	TB	TC	TB	TD	TD	TD	TB	TB	TB
ZINC SULFATE	B	B	C	C	E	E	E	B	B	B

This data is provided as a service of Applied Polymer Solutions and is believed to be accurate. However this information is neither recommendations by APS nor product specifications. APS reserves the right to change or modify data as necessary.